STATE OF ILLINOIS
DEPARTMENT OF REGISTRATION AND EDUCATION

DIVISION OF THE
STATE GEOLOGICAL SURVEY
FRANK W. DE WOLF, Chief

Cooperative Mining Series

EXTRACT A FROM BULLETIN No. 27

ANALYSES OF ILLINOIS COALS

COMPILED BY

G. W. HAWLEY

ILLINOIS MINING INVESTIGATIONS

Prepared under a cooperative agreement between the Illinois State Geological Survey Division, the Engineering Experiment Station of the University of Illinois, and the U. S. Bureau of Mines

PRINTED BY AUTHORITY OF THE STATE OF ILLINOIS

URBANA, ILLINOIS
1923

The Forty-seventh General Assembly of the State of Illinois, with a view of conserving the lives of the mine workers and the mineral resources of the State, authorized an investigation of the coal resources and mining practices of Illinois by the Department of Mining Engineering of the University of Illinois and the State Geological Survey Division in cooperation with the United States Bureau of Mines. A cooperative agreement was approved by the Secretary of the Interior and by representatives of the State of Illinois.

The direction of this investigation is vested in the Director of the United States Bureau of Mines, the Chief of the State Geological Survey Division, and the Director, Engineering Experiment Station, University of Illinois, who jointly determined the methods to be employed in the conduct of the work and exercise general editorial supervision over the publication of the results, but each party to the agreement directs the work of its agent in carrying on the investigation thus mutually agreed on.

The reports of the investigation are issued in the form of bulletins, either by the State Geological Survey Division, the Engineering Experiment Station, University of Illinois, or the United States Bureau of Mines. For copies of the bulletins issued by the State Geological Survey Division, address State Geological Survey Division, Urbana, Illinois; for those issued by the Engineering Station, address Engineering Station, University of Illinois, Urbana, Illinois; and for those issued by U. S. Bureau of Mines, address Director, U. S. Bureau , D. C. (See list at end of book.)

STATE OF ILLINOIS
DEPARTMENT OF REGISTRATION AND EDUCATION

DIVISION OF THE
STATE GEOLOGICAL SURVEY
FRANK W. DE WOLF, Chief

Cooperative Mining Series
EXTRACT FROM BULLETIN No. 27

ANALYSES OF ILLINOIS COALS

COMPILED BY

G. W. HAWLEY

ILLINOIS MINING INVESTIGATIONS

Prepared under a cooperative agreement between the Illinois State Geological Survey Division, the Engineering Experiment Station of the University of Illinois, and the U. S. Bureau of Mines

PRINTED BY AUTHORITY OF THE STATE OF ILLINOIS

URBANA, ILLINOIS
1923

STATE OF ILLINOIS
DEPARTMENT OF REGISTRATION AND EDUCATION

DIVISION OF THE
STATE GEOLOGICAL SURVEY
FRANK W. DeWOLF, *Chief*

Committee of the Board of Natural Resources and Conservation

A. M. SHELTON, *Chairman*
Director of Registration and Education

KENDRIC C. BABCOCK
Representing the President of the University of Illinois

EDSON S. BASTIN
Geologist

ILLINOIS STATE JOURNAL CO.
SPRINGFIELD, ILLINOIS
1923

84573—3000

CONTENTS

ILLUSTRATIONS

TABLES

ANALYSES OF ILLINOIS COALS

Compiled by G. W. Hawley

INTRODUCTION

A study of the chemical character of Illinois coals based on new face samples collected in 1921 from approximately 100 mines in various parts of the State was begun with a view to extending our knowledge of the chemical properties, heating quality, and special adaptability of all Illinois coals. A bulletin will be issued at an early date which will present the conclusions based on these data, but it seems desirable to publish the analytical data prior to the complete report. The analyses have been combined with data previously published by the State Geological Survey[1] [2] and also by the United States Bureau of Mines. References to the bulletins in which the analytical results of coal samples collected by the United States Bureau of Mines have been published, are indicated throughout the tables of analyses in order that the detailed descriptions of the samples may be consulted.

ANALYTICAL DATA

Analyses of Mine Samples

Table 1, which gives an alphabetical list of counties including the district classification (see fig. 1) and the coal beds for each county, serves as a cross reference.

The complete analyses of mine samples grouped by coal beds, under which the counties represented are arranged alphabetically, are given in Table 2. Analyses having the same index number are of samples for a single mine. Obviously, not as much dependence can be placed on a single analysis from a given mine as may be placed on a group from one mine. Two sets of values are given for each sample—one including the normal or coal-bed moisture, and the other calculated to the dry-coal or moisture-free basis. There is also given the value of the unit-coal in British thermal units as derived by the formula previously explained[2].

1. Parr, S. W., Chemical study of Illinois coals: Ill. Mining Investigations Bull. 3, 1916.
2. Parr, S. W., Purchase and sale of Illinois coal on specification: Ill. State Geol. Surv. Bull. 29, 1914.



FIG. 1.—Districts for classification of coal samples

In Table 3 are presented the average analyses and heat values for separate mines and by counties grouped according to the districts shown in figure 1.

TABLE 1.—*Alphabetical arrangement of counties.*

County	Coal bed	District	County	Coal bed	District
Bond	6	VII	McLean	2, 5	IV
Bureau	2	I	Menard	5	IV
Calhoun	2	III	Mercer	1	III
Christian	1, 2, 6	IV, VII	Montgomery	6	VII
Clinton	6	VII	Moultrie	6	VII
Franklin	6	VI	Peoria	5	IV
Fulton	1, 5	III, IV	Perry	6	VI, VII
Gallatin	5, 6	V	Randolph	6	VII
Grundy	2	I	St. Clair	6	VII
Jackson	2, 6	II, VI	Saline	5	V
LaSalle	2, 5, 7	I	Sangamon	5, 6	IV, VII
Livingston	2, 5	I	Schuyler	1, 2	III
Logan	5	IV	Shelby	6	VII
Macon	5	IV	Tazewell	5	IV
Macoupin	6	VII	Vermilion	6, 7	VIII
Madison	6	VII	Washington	6	VII
Marion	6	VII	White	6	V
Marshall	2	I	Williamson	6	VI
McDonough	2	III			

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output).*

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
No. 1 Coal.												
5229	21	7/12	Christian	1	11.27	38.68	40.55	9.50	2.07	.33	11445	------
					Dry 43.59	45.70	10.71		2.33	.37	12898	14666
5230	21	7/12	Christian	1	11.52	38.78	41.01	8.69	2.42	.97	11648	------
					Dry 43.83	46.35	9.82		2.73	1.10	13163	14707
5231	21	7/12	Christian	1	11.13	39.21	41.26	8.40	2.56	.61	11715	------
					Dry 44.12	46.43	9.45		2.88	.69	13183	14779
12469	105	3/21	Fulton	1	11.38	38.66	39.51	10.45	4.52	.87	11436	------
					Dry 43.62	44.58	11.80		5.10	.98	12905	14979
12470	105	3/21	Fulton	1	11.42	38.17	40.07	10.34	4.76	.45	11409	------
					Dry 43.09	45.24	11.67		5.37	.51	12880	14934
12471	105	3/21	Fulton	1	10.84	38.42	40.91	9.83	5.61	.54	11554	------
					Dry 43.09	45.88	11.03		6.29	.61	12959	14939
5338	19	8/12	Mercer	1	13.23	40.29	37.20	9.28	4.37	.41	11104	------
					Dry 46.43	42.88	10.69		5.04	.47	12797	14641
5339	19	8/12	Mercer	1	15.24	37.66	35.73	11.37	4.80	1.47	10353	------
					Dry 44.44	42.15	13.41		5.66	1.73	12214	14478
5340	19	8/12	Mercer	1	15.15	39.06	38.48	7.31	3.30	.17	11252	------
					Dry 44.44	42.15	14.41		5.66	1.73	12214	14478
5363	19	8/12	Mercer	1	14.97	38.27	37.07	9.69	3.75	.33	9637	------
					Dry 46.03	45.36	8.61		3.89	.19	13260	14760
5364	19	8/12	Mercer	1	14.46	40.42	35.33	9.79	4.23	.69	10780	------
					Dry 44.99	43.61	11.40		4.95	.43	12749	14712
5365	19	8/12	Mercer	1	14.07	39.95	34.01	11.97	4.55	.78	10525	------
					Dry 47.24	41.32	11.44		4.94	.59	12603	14551
5359	18	8/12	Mercer	1	14.58	39.49	36.82	9.11	5.60	.15	10894	------
					Dry 46.49	39.59	13.92		5.29	.91	12247	14604
5360	18	8/12	Mercer	1	15.07	38.14	37.44	9.35	4.85	.34	10790	------
					Dry 46.23	43.09	10.68		6.56	.18	12754	14642
5361	18	8/12	Mercer	1	14.10	39.60	36.73	9.57	3.92	.23	10956	------
					Dry 44.91	44.01	11.02		5.71	.38	12705	14618
5371	17	8/12	Mercer	1	17.75	39.50	34.61	8.14	5.53	.86	10435	------
					Dry 48.03	42.08	9.89		6.72	1.05	12687	14373
5372	17	8/12	Mercer	1	17.50	38.78	33.66	10.06	4.51	.29	10238	------
					Dry 47.00	40.80	12.20		5.46	.35	12409	14372
No. 2 Coal.												
5324	1	8/12	Bureau	2	16.65	36.66	38.58	8.11	3.40	.67	10740	------
					Dry 43.99	46.29	9.72		4.07	.80	12884	14533
5325	1	8/12	Bureau	2	15.08	40.12	36.35	8.45	3.68	.91	10831	------
					Dry 47.25	42.80	9.95		4.33	1.07	12754	14431
5326	1	8/12	Bureau	2	16.83	36.54	39.19	7.44	2.64	.89	10788	------
					Dry 43.93	47.12	8.95		3.17	1.07	12970	14463
5312	10	8/12	Bureau	2	14.88	38.69	37.25	9.08	3.83	1.07	10685	------
					Dry 45.45	43.76	10.79		4.50	1.25	12553	14357

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5313	10	8/12	Bureau	2	17.43	38.07	39.44	5.06	2.68	.52	11070	
					Dry	46.10	47.76	6.14	3.25	.63	13407	14462
5314	10	8/12	Bureau	2	16.07	39.68	38.36	5.89	2.96	.57	11216	
					Dry	47.28	45.71	7.01	3.53	.63	13363	14571
5348	8	8/12	Bureau	2	15.19	39.67	38.69	6.45	2.20	.99	11206	
					Dry	46.78	45.60	7.62	2.62	1.17	13213	14480
5349	8	8/12	Bureau	2	17.34	37.12	39.28	6.26	2.80	.49	11006	
					Dry	44.90	47.52	7.58	3.38	.59	13314	14612
5350	8	8/12	Bureau	2	16.97	38.66	34.83	9.54	2.25	2.29	10397	
					Dry	46.56	41.95	11.49	2.71	2.91	12522	14386
2641	230	7/09	Calhoun	2	10.62	38.13	39.65	11.60	4.96		11224	
					Dry	42.67	44.36	12.97	5.55		12557	14806
5205	21	7/12	Christian	2	12.07	39.36	41.91	6.66	3.74	.07	11776	
					Dry	44.77	47.66	7.57	4.26	.09	13393	14730
5206	21	7/12	Christian	2	12.53	38.00	40.62	8.25	3.67	.31	11389	
					Dry	44.12	46.44	9.44	4.22	.35	13020	14641
5207	21	7/12	Christian	2	14.30	39.54	40.30	5.86	2.00	.24	11609	
					Dry	46.14	47.02	6.84	2.33	.28	13544	14702
5367	6	8/12	Grundy	2	19.97	38.16	37.45	4.42	1.82	.65	10936	
					Dry	47.68	46.79	5.53	2.27	.79	13664	14603
5368	6	8/12	Grundy	2	18.95	37.60	38.23	5.22	2.46	.64	10787	
					Dry	46.39	47.16	6.45	3.04	.79	13309	14400
5369	6	8/12	Grundy	2	19.66	37.01	38.16	5.17	2.03	.83	10734	
					Dry	46.06	47.50	6.44	2.53	1.03	13360	14337
5373	5	8/12	Grundy	2	17.29	38.61	36.69	7.41	2.87	1.44	10708	
					Dry	46.68	44.36	8.96	3.47	1.74	12947	14447
5374	5	8/12	Grundy	2	13.73	39.87	42.19	4.21	2.04	1.47	11787	
					Dry	46.22	48.90	4.88	2.37	1.71	13662	14466
5377	5	8/12	Grundy	2	17.01	39.48	36.74	6.77	3.32	1.05	10834	
					Dry	47.57	44.27	8.16	4.00	1.27	13055	14446
5375	7	8/12	Grundy	2	16.84	38.37	41.19	3.60	1.74	.04	11508	
					Dry	46.13	49.53	4.34	2.09	.05	13838	14583
5376	7	8/12	Grundy	2	15.81	39.28	39.77	6.13	2.30	.24	11212	
					Dry	45.48	47.24	7.28	2.73	.28	13318	14545
5378	7	8/12	Grundy	2	16.23	38.71	40.61	4.45	2.47	.32	11461	
					Dry	46.22	48.47	5.31	2.94	.38	13683	14610
5225	14	7/12	Jackson	2	7.72	35.09	48.56	8.63	2.01	.29	12248	
					Dry	38.02	52.62	9.36	2.18	.31	13272	14839
5226	14	7/12	Jackson	2	8.77	32.78	50.58	7.87	2.00	.02	12253	
					Dry	35.93	55.44	8.63	2.19	.03	13430	14885
5228	14	7/12	Jackson	2	9.18	34.70	51.58	4.54	.60	.05	12752	
					Dry	38.20	56.80	5.00	.66	.06	14040	14867
5248	13	7/12	Jackson	2	9.88	33.23	52.43	4.46	.70	.33	12709	
					Dry	36.87	58.18	4.95	.77	.36	14103	14926
5249	13	7/12	Jackson	2	10.91	33.51	51.20	4.38	1.14	.20	12503	
					Dry	37.61	57.47	4.92	1.28	.23	14034	14863

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5250	13	7/12	Jackson	2	9.76	33.45	52.07	4.72	1.08	.51	12629	
					Dry	37.06	57.71	5.23	1.20	.56	13996	14874
5351	12	7/12	Jackson	2	9.51	33.13	52.12	5.24	.66	.94	12500	
					Dry	36.62	57.59	5.79	.73	1.03	13814	14758
5252	12	7/12	Jackson	2	9.37	33.39	49.29	7.95	2.11	.94	11972	
					Dry	36.48	54.38	8.78	2.32	1.03	13208	14671
5253	12	7/12	Jackson	2	9.99	32.51	51.88	5.62	.62	.20	12308	
					Dry	36.12	57.63	6.25	.69	.22	13673	14686
5496	16	8/12	Jackson	2	9.25	34.67	50.53	5.55	1.41	.13	12528	
					Dry	38.20	55.68	6.12	1.56	.14	13804	14834
5497	16	8/12	Jackson	2	9.56	34.52	50.47	5.45	1.32	.27	12483	
					Dry	38.16	55.83	6.01	1.46	.30	13781	14811
5498	16	8/12	Jackson	2	9.20	34.48	50.54	5.78	1.44	.19	12481	
					Dry	37.97	55.66	6.37	1.59	.21	13746	14814
5286	15	8/12	Jackson	2	8.32	35.28	51.10	5.30	1.39	.19	12671	
					Dry	38.49	55.74	5.77	1.53	.21	13822	14791
5287	15	8/12	Jackson	2	8.86	35.00	49.74	6.40	1.69	.07	12436	
					Dry	38.40	54.57	7.03	1.85	.08	13645	14830
5288	15	8/12	Jackson	2	8.91	34.03	53.17	3.89	1.15	.07	12844	
					Dry	37.36	58.37	4.27	1.26	.08	14101	14823
12662	104	6/21	Jackson	2	4.56	37.90	44.23	13.31	6.62	.03	11886	
					Dry	39.71	46.35	13.94	6.94	.03	12106	14921
12663	104	6/21	Jackson	2	4.57	34.75	46.22	14.49	7.63	.04	11670	
					Dry	36.41	48.41	15.18	8.00	.04	12229	14934
5388	2	8/12	LaSalle	2	14.22	39.49	36.94	9.35	4.46	.80	10887	
					Dry	46.03	43.06	10.91	5.20	.93	12691	14562
5389	2	8/12	LaSalle	2	15.16	40.13	38.10	6.61	2.99	.64	11147	
					Dry	47.32	44.88	7.80	3.51	.70	13138	14458
5390	2	8/12	LaSalle	2	14.43	40.01	35.89	9.67	4.47	1.03	10678	
					Dry	46.75	41.94	11.31	5.23	1.21	12476	14404
5306	3	8/12	LaSalle	2	14.29	41.35	38.73	5.63	2.09	.19	11487	
					Dry	48.24	45.18	6.58	2.44	.22	13401	14504
5307	3	8/12	LaSalle	2	16.05	37.03	37.06	9.86	4.35	.59	10459	
					Dry	44.11	44.16	11.73	5.18	.70	12458	14440
5311	3	8/12	LaSalle	2	14.82	40.93	35.20	9.05	3.42	.99	10760	
					Dry	48.05	41.33	10.62	4.02	1.17	12632	14401
5351	9	8/12	LaSalle	2	16.52	38.88	36.50	8.10	2.87	1.02	10686	
					Dry	46.57	43.72	9.71	3.44	1.22	12800	14412
5352	9	8/12	LaSalle	2	17.77	39.05	34.15	9.03	3.92	1.25	10279	
					Dry	47.48	41.55	10.97	4.76	1.52	12500	14334
5353	9	8/12	LaSalle	2	18.06	39.02	32.94	9.98	2.74	2.20	10209	
					Dry	47.62	40.20	12.18	3.34	2.69	12460	14460
84450	102	3/22	LaSalle	2	14.5	36.0	41.7	7.8	3.5	.67	11130	
					Dry	42.0	48.9	9.1	4.1	.79	13010	15564
84451	102	3/22	LaSalle	2	14.0	34.9	43.2	7.9	2.3	.90	11240	
					Dry	40.6	50.3	9.1	2.7	1.04	13070	14584

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
84452	102	3/22	LaSalle	2	15.7	33.9	41.9	8.5	4.0	.59	10800	
					Dry	40.2	49.7	10.1	4.8	.70	12800	14528
10264	103	9/17	LaSalle	2	12.61	38.89	42.36	6.14	2.66		11892	
					Dry	44.51	48.46	7.03	3.04		13608	14830
10263	103	9/17	LaSalle	2	12.19	39.92	40.18	7.17	2.56		11667	
					Dry	45.47	45.75	8.78	2.91		13289	14780
1741	[1]B. M.	6/05	LaSalle	2	13.87	37.26	38.56	10.31	3.44		10985	
					Dry	43.26	44.77	11.97	3.99		12755	14792
1742	[1]B. M.	6/05	LaSalle	2	15.55	36.21	40.66	7.58	3.01			
					Dry	42.88	48.14	8.98	3.56			
1779	[1]B. M.	6/05	LaSalle	2	12.39	36.89	41.80	8.92	3.92		11399	
					Dry	42.11	47.71	10.18	4.47		13012	14743
5357	4	8/12	Marshall	2	16.46	38.48	38.27	6.79	2.91	.28	11162	
					Dry	46.06	45.80	8.14	3.48	.34	13360	14764
5356	4	8/12	Marshall	2	16.79	36.81	40.34	6.06	2.59	.41	11130	
					Dry	44.23	48.49	7.28	3.11	.49	13375	14620
5358	4	8/12	Marshall	2	17.54	37.42	40.11	4.93	2.19	.42	11273	
					Dry	45.37	48.63	6.00	2.56	.50	13669	14703
5412	11	8/12	Marshall	2	12.92	41.69	37.60	7.78	2.38	.64	11597	
					Dry	47.87	43.19	8.94	2.73	.73	13319	14836
5413	11	8/12	Marshall	2	13.10	38.73	39.64	8.53	3.47	.65	11414	
					Dry	44.56	45.61	9.83	3.99	.75	13134	14832
5414	11	8/12	Marshall	2	13.82	41.34	35.88	8.96	3.28	.50	11296	
					Dry	47.97	41.64	10.39	3.81	.59	13106	14901
5232	22	7/12	McDonough	2	19.35	31.70	40.61	8.34	2.31	.37	10392	
					Dry	39.35	50.40	10.35	2.87	.46	12898	14605
5233	22	7/12	McDonough	2	16.46	33.94	42.46	7.14	1.71	.11	11064	
					Dry	40.63	50.83	8.54	2.04	.14	13246	14660
5234	22	7/12	McDonough	2	16.39	34.26	41.36	7.99	2.04	.33	10977	
					Dry	40.97	49.47	9.56	2.44	.40	13130	14725
9728	213	11/16	McDonough	2	14.89	35.48	40.75	8.88	3.78		10969	
					Dry	41.68	47.88	10.44	4.43		12887	14678
9729	213	11/16	McDonough	2	16.83	34.68	39.79	8.70	3.94		10628	
					Dry	41.71	47.83	10.46	4.74		12778	14565
5426	100	8/12	McLean	2	10.13	45.00	35.92	8.95	3.27	.74	11710	
					Dry	50.07	39.97	9.96	3.59	.82	13029	14723
5427	100	8/12	McLean	2	11.34	40.05	39.18	9.43	3.18	.90	11394	
					Dry	45.17	44.19	10.64	3.58	1.01	12851	14643
5428	100	8/12	McLean	2	10.61	41.87	35.94	11.58	3.79	.92	11225	
					Dry	46.84	40.21	12.95	4.24	1.03	12557	14752
5429	100	8/12	McLean	2	12.31	42.17	38.03	7.49	2.69	.94	11636	
					Dry	48.09	43.37	8.54	3.07	1.07	13270	14722
5430	100	8/12	McLean	2	12.00	42.00	37.96	8.04	2.37	1.23	11634	
					Dry	47.73	43.14	9.13	2.70	1.40	13220	14759

[1] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 85, 1913.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5433	100	8/12	McLean	2	11.27	42.17	39.27	7.29	2.91	1.12	11784	
					Dry	47.53	44.25	8.22	3.28	1.26	13279	14684
3044	[2]B. M. 55	3/06	McLean	2	10.25	35.88	40.11	13.76	2.80		11149	
					Dry	39.98	44.69	15.33	3.12		12422	15028
3045	[2]B. M. 55	3/06	McLean	2	9 88	35.99	38.22	15.91	3.15			
					Dry	39.93	42.42	17.65	3.50			
9709	214	11/16	Schuyler	2	12.34	38.11	42.29	7.26	4.32		11841	
					Dry	43.48	48.24	8.28	4.92		13507	15011
9708	214	11/16	Schuyler	2	12.73	37.56	41.88	7.83	4.77		11621	
					Dry	43.04	47.99	8.97	5.46		13316	14924
					No. 5 Coal.							
5283	31	8/12	Fulton	5	15.18	37.17	35.17	12.48	3.45	1.70	10201	
					Dry	43.82	41.45	14.73	4.07	2.00	12026	14441
5284	31	8/12	Fulton	5	16.94	35.68	37.15	10.23	2.98	1.31	10314	
					Dry	42.95	44.73	12.32	3.59	1.57	12418	14446
5285	31	8/12	Fulton	5	18.42	34.98	37.66	8.94	2.33	.86	10270	
					Dry	42.88	46.15	10.97	2.85	1.06	12587	14371
5296	31	8/12	Fulton	5	16.82	37.28	33.45	12.45	2.84	1.69	10580	
					Dry	44.81	40.23	14.96	3.42	2.02	12038	14479
5298	31	8/12	Fulton	5	16.52	37.17	36.54	9.77	3.91	.81	10394	
					Dry	44.52	43.78	11.70	4.69	.97	12451	14409
5341	31	8/12	Fulton	5	17.37	35.71	37.86	9.06	2.34	1.14	10420	
					Dry	43.22	45.82	10.96	2.83	1.38	12610	14398
5293	29	8/12	Fulton	5	17.13	36.23	34.44	12.20	3.03	1.79	9846	
					Dry	43.72	41.55	14.73	3.66	2.16	11882	14252
5297	29	8/12	Fulton	5	16.59	35.98	37.20	10.23	4.07	1.77	10271	
					Dry	43.14	44.61	12.25	4.88	2.12	12314	14354
5300	29	8/12	Fulton	5	15.41	35.67	39.04	9.88	3.31	.52	10579	
					Dry	42.16	46.15	11.69	3.92	.61	12505	14443
5292	28	8/12	Fulton	5	17.39	37.00	35.69	9.92	2.74	1.14	10273	
					Dry	44.79	43.20	12.01	3.28	1.36	12435	14416
5295	28	8/12	Fulton	5	16.33	36.27	36.58	10.82	3.40	1.94	10246	
					Dry	43.34	43.72	12.94	4.06	2.32	12247	14371
5299	28	8/12	Fulton	5	16.33	36.75	38.02	8.90	2.59	1.02	10604	
					Dry	43.92	45.44	10.64	3.10	1.22	12674	14421
5342	32	8/12	Fulton	5	13.66	38.46	37.06	10.82	3.64	1.26	10689	
					Dry	44.54	42.92	12.54	4.22	1.46	12379	14462
5343	32	8/12	Fulton	5	14.53	37.46	38.35	9.66	3.18	1.60	10804	
					Dry	43.83	44.87	11.30	3.72	1.87	12641	14525
5344	32	8/12	Fulton	5	15.80	35.84	37.67	10.69	3.00	1.79	10460	
					Dry	42.56	44.74	12.70	3.57	2.12	12423	14520
5345	30	8/12	Fulton	5	16.36	33.91	38.19	11.54	2.93	1.27	10186	
					Dry	40.54	45.66	13.80	3.50	1.51	12179	14431
5346	30	8/12	Fulton	5	16.33	35.50	37.01	11.16	2.89	1.84	10220	
					Dry	42.42	44.23	13.35	3.45	2.20	12213	14389

[2] Ibid.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5347	30	8/12	Fulton	5	15.85	36.12	38.12	9.91	3.36	1.47	10494	------
					Dry	42.92	45.30	11.78	4.00	1.75	12471	14386
12442	110	3/21	Fulton	5	15.43	33.62	39.47	11.48	2.50	1.41	10389	------
					Dry	39.76	46.67	13.57	2.66	1.67	12285	14473
12443	111	3/21	Fulton	5	14.43	34.60	39.09	11.88	2.82	2.45	10320	------
					Dry	40.43	45.69	13.88	3.29	2.86	12061	14297
12444	111	3/21	Fulton	5	15.00	33.10	37.31	14.59	3.38	2.86	9834	------
					Dry	38.94	43.89	17.17	3.98	3.36	11569	14300
12445	111	3/21	Fulton	5	14.69	34.07	40.18	11.06	2.83	1.75	10383	------
					Dry	39.94	47.09	12.97	3.32	2.05	12172	14266
12446	111	3/21	Fulton	5	14.52	34.46	37.64	13.38	2.91	2.74	10045	------
					Dry	40.31	44.04	15.65	3.40	3.21	11752	14261
12447	111	3/21	Fulton	5	14.75	33.18	38.89	13.18	3.70	1.54	9869	------
					Dry	38.92	45.62	15.46	4.34	1.81	11577	14298
12448	111	3/21	Fulton	5	14.28	33.93	38.76	12.03	2.56	1.98	10329	------
					Dry	40.75	45.22	14.03	2.99	2.31	12061	14316
12472	112	3/21	Fulton	5	15.32	35.12	38.05	11.51	2.59	1.41	10482	------
					Dry	41.48	44.93	13.59	3.06	1.66	12379	14617
12473	112	3/21	Fulton	5	15.09	35.37	39.41	10.13	2.68	1.79	10741	------
					Dry	41.66	46.41	11.93	3.16	1.66	12650	14631
12474	112	3/21	Fulton	5	15.56	35.68	38.92	9.84	2.43	1.33	10753	------
					Dry	42.26	46.09	11.65	2.88	1.58	12735	14668
12475	112	3/21	Fulton	5	14.56	35.37	38.98	11.09	2.72	1.38	10581	------
					Dry	41.40	45.62	12.98	3.19	1.62	12384	14512
12476	112	3/21	Fulton	5	15.39	33.82	38.77	12.02	3.40	1.67	10338	------
					Dry	39.97	45.82	14.21	4.02	1.97	12219	14565
12477	112	3/21	Fulton	5	15.66	34.65	37.56	12.13	2.93	1.88	10242	------
					Dry	41.08	44.59	14.38	3.47	2.23	12144	14583
12439	113	3/21	Fulton	5	13.37	36.03	39.03	11.57	3.06	1.46	10787	------
					Dry	41.59	45.06	13.35	3.52	1.69	12452	14670
12440	113	3/21	Fulton	5	14.44	34.71	38.58	12.27	2.17	1.80	10578	------
					Dry	40.57	45.09	14.34	2.54	2.10	12364	14683
12441	113	3/21	Fulton	5	14.96	33.65	39.96	11.43	4.32	1.11	10502	------
					Dry	39.57	46.99	13.44	5.08	1.30	12350	14616
12459	114	3/21	Fulton	5	14.57	35.24	39.58	10.61	2.89	1.00	10562	------
					Dry	41.25	46.33	12.42	3.38	1.17	12363	14391
12460	114	3/21	Fulton	5	16.16	35.65	37.89	10.30	2.50	1.56	10422	------
					Dry	42.52	45.19	12.29	2.98	1.86	12931	14434
12461	114	3/21	Fulton	5	13.35	37.84	39.86	8.95	2.22	1.77	10843	------
					Dry	43.67	46.00	10.33	2.56	2.04	12514	14150
12462	114	3/21	Fulton	5	15.86	35.20	37.32	11.62	3.49	1.31	10198	------
					Dry	41.84	44.35	13.81	4.15	1.56	12120	14380
12463	114	3/21	Fulton	5	14.34	35.09	36.72	13.85	3.84	2.47	9944	------
					Dry	40.96	42.87	16.17	4.48	2.89	11609	14217
12464	114	3/21	Fulton	5	14.62	36.18	36.21	9.99	2.43	1.49	10719	------
					Dry	42.38	45.92	11.70	2.85	1.74	12555	14465

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
84406	115	2/22	Fulton	5	15.7	33.2	38.7	12.4	3.6	1.57	10270	------
					Dry	39.3	46.0	14.7	4.3	1.86	12180	14511
84407	115	2/22	Fulton	5	14.8	33.8	42.3	9.1	2.6	.75	10950	------
					Dry	39.7	49.6	10.7	3.1	.88	12860	14649
12436	116	3/21	Fulton	5	15.88	33.96	38.75	11.41	4.38	.92	10330	------
					Dry	40.37	46.07	13.56	5.21	1.10	12280	14569
12437	116	3/21	Fulton	5	16.68	35.46	37.90	9.96	3.82	.61	10464	------
					Dry	42.56	45.49	11.95	4.58	.74	12559	14579
12438	116	3/21	Fulton	5	14.53	35.68	38.23	11.56	3.45	1.00	10608	------
					Dry	41.74	44.73	13.53	4.04	1.17	12411	14679
84409	117	2/22	Fulton	5	13.5	34.4	38.8	13.3	3.5	------	10410	------
					Dry	39.8	44.8	15.4	4.1	------	12040	14589
84446	118	3/22	Fulton	5	11.6	36.4	40.4	11.6	4.1	.92	11070	------
					Dry	41.1	45.7	13.2	4.6	1.04	12510	14758
84447	118	3/22	Fulton	5	13.6	34.7	41.4	10.3	3.3	.83	10950	------
					Dry	40.2	47.9	11.9	3.8	.97	12670	14673
84448	118	3/22	Fulton	5	13.1	34.7	39.5	12.7	4.0	1.34	10690	------
					Dry	39.9	45.4	14.7	4.7	1.54	12310	14808
4345	[3]	12/06	Fulton	5	15.27	32.91	11.46	10.36	3.01	------	------	------
					Dry	38.84	48.93	12.23	3.55	------	------	------
4346	[3]	12/06	Fulton	5	15.67	31.43	43.10	9.80	2.99	------	10620	------
					Dry	37.28	51.11	11.61	3.55	------	12593	14519
5025	47	6/12	Gallatin	5	5.37	36.54	45.10	12.99	3.99	1.38	11883	------
					Dry	38.62	47.65	13.73	4.22	1.45	12558	14900
5029	47	6/12	Gallatin	5	5.57	35.49	48.53	10.41	3.12	.78	12338	------
					Dry	37.59	51.39	11.02	3.31	.83	13066	14953
5032	47	6/12	Gallatin	5	6.21	35.29	46.49	12.02	3.30	.87	11938	------
					Dry	37.61	49.57	12.82	3.52	.93	12728	14903
5492	----------	8/12	Gallatin	5	4.20	34.41	52.63	8.76	2.85	.01	12997	------
					Dry	35.92	54.92	9.16	2.97	.01	13566	15164
5493	----------	8/12	Gallatin	5	4.07	33.59	52.86	8.98	3.61	.03	12975	------
					Dry	35.43	55.21	9.36	3.76	.03	13526	15186
5512	----------	8/12	Gallatin	5	3.68	37.83	48.18	10.32	4.55	.04	12818	------
					Dry	39.26	50.02	10.72	4.73	.04	13307	15078
5521	----------	8/12	Gallatin	5	3.94	38.13	45.95	11.98	3.53	.03	12449	------
					Dry	39.70	47.82	12.48	3.67	.03	12958	15117
5522	----------	8/12	Gallatin	[4]	7.15	34.34	53.32	5.19	.84	.03	13035	------
					Dry	36.99	57.42	5.59	.90	.03	14038	14970
5523	----------	8/12	Gallatin	----	4.73	33.91	48.65	11.71	4.78	.04	12429	------
					Dry	35.59	52.12	12.29	5.02	.04	13045	15240
5530	----------	8/12	Gallatin	----	4.03	33.71	51.84	10.41	4.19	.02	12783	------
					Dry	35.13	54.01	10.86	4.37	.02	13319	15256
12940	135	7/21	Gallatin	5	4.37	34.39	49.23	12.01	3.85	.35	12270	------
					Dry	35.96	51.48	12.56	4.03	.37	12631	14995

[3] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 85, 1913.
[4] This and the two following samples are from the "Ice House" coal of Kentucky reports.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
12941	135	7/21	Gallatin	5	4.04	35.68	50.92	9.36	3.23	.24	12828	
					Dry	37.18	53.06	9.76	3.37	.24	13200	15066
12942	135	7/21	Gallatin	5	3.49	36.09	50.54	9.88	3.04	.18	12707	
					Dry	37.39	52.37	10.24	3.15	.18	13162	14912
23425	[5]B. M. 4	11/15	Gallatin	5	3.93	36.82	51.04	8.21	2.80		13106	
					Dry	38.33	53.12	8.55	2.91		13642	15134
5391		8/12	LaSalle	5	15.52	41.56	32.57	10.35	4.08	.27	10425	
					Dry	49.18	38.55	12.27	4.83	.34	12400	14384
5392		8/12	LaSalle	5	14.13	39.42	35.96	10.49	3.22	.96	10636	
					Dry	45.90	41.89	12.21	3.75	1.12	12387	14393
5393		8/12	LaSalle	5	14.64	43.01	34.25	8.10	2.83	.56	10961	
					Dry	50.38	40.12	9.50	3.32	.66	12841	14415
10519	215	8/18	Livingston	5	10.22	36.56	42.14	11.08	3.09		11630	
					Dry	40.72	46.94	12.34	3.44		12955	15077
10523	215	8/18	Livingston	5	10.05	32.49	37.59	19.87	7.61		10125	
					Dry	38.12	41.80	22.08	8.46		11256	15151
10524	215	8/18	Livingston	5	7.95	38.03	43.55	10.47	3.52		12020	
					Dry	41.31	47.31	11.38	3.82		13057	15026
10520	216	8/18	Livingston	5	13.23	36.90	39.16	11.42	1.46		10924	
					Dry	41.71	45.13	13.16	1.69		12590	14738
10521	216	8/18	Livingston	5	14.03	36.36	39.69	9.92	2.74		11124	
					Dry	42.29	46.17	11.54	3.18		12939	14899
10522	216	8/18	Livingston	5	14.04	34.76	38.03	13.17	5.25		10502	
					Dry	40.44	44.24	15.32	6.11		12216	14871
5263	33	8/12	Logan	5	14.64	37.87	35.56	11.93	3.60	1.10	10400	
					Dry	44.36	41.66	13.98	4.22	1.28	12183	14497
5264	33	8/12	Logan	5	13.98	36.86	37.98	11.18	3.14	1.43	10549	
					Dry	42.84	44.16	13.00	3.65	1.67	12264	14391
5265	33	8/12	Logan	5	13.99	36.85	38.17	10.99	3.26	1.32	10519	
					Dry	42.85	44.37	12.78	3.79	1.53	12230	14313
81591	109	9/21	Logan	5	14.36	35.36	39.95	10.33	2.73	1.20	10750	
					Dry	41.29	46.65	12.06	3.19	1.40	12599	14595
81592	109	9/21	Logan	5	13.70	35.46	40.38	10.46	3.38	1.11	10813	
					Dry	41.09	46.79	12.12	3.92	1.29	12530	14553
81593	109	9/21	Logan	5	12.55	35.93	42.13	9.39	2.76	.84	11169	
					Dry	41.09	48.17	10.74	2.16	.96	12772	14643
2881	[6]B. M. 37	2/06	Logan	5	14.77	32.90	39.75	12.58	3.95		10406	
					Dry	38.60	46.64	14.76	4.63		12209	14687
2882	[6]B. M. 37	2/06	Logan	5	15.52	32.27	39.86	12.35	3.65			
					Dry	38.20	47.18	14.62	4.32			
3003	[6]B. M. 37	2/06	Logan	5	15.68	32.41	39.82	12.09	3.51		10337	
					Dry	38.44	47.22	14.34	4.16		12260	14656
5200	42	7/12	Macon	5	13.52	36.72	39.66	10.10	4.23	.09	10646	
					Dry	42.46	45.86	11.68	4.95	.11	12443	14405

[5] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 123, p. 34, 1918.
[6] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 85, 1913.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5201	42	7/12	Macon	5	13.62	37.72	40.34	8.32	3.39	.00	11046	------
					Dry	43.68	46.70	9.62	3.93	.00	12788	14403
5202	42	7/12	Macon	5	14.36	38.06	39.35	9.33	3.87	.19	10963	------
					Dry	43.88	45.37	10.75	4.46	.22	12638	14447
5244	41	7/12	Macon	5	14.76	35.46	38.08	11.70	3.24	.90	10390	------
					Dry	41.60	44.67	13.73	3.81	1.06	12189	14443
5245	41	7/12	Macon	5	14.54	36.33	38.01	11.12	3.47	.68	10465	------
					Dry	42.51	44.47	13.01	4.06	.79	12244	14385
5346	41	7/12	Macon	5	14.14	36.21	38.07	11.58	3.24	1.12	10493	------
					Dry	42.18	44.34	13.48	3.77	1.31	12210	14433
81595	123	9/21	Macon	5	13.10	34.64	43.36	8.90	2.73	.21	10934	------
					Dry	39.86	49.90	10.24	3.14	.24	12582	14247
81596	123	9/21	Macon	5	12.67	35.75	43.08	8.50	3.32	.03	11103	------
					Dry	40.94	49.33	9.73	3.80	.03	12714	14331
81597	123	9/21	Macon	5	12.71	35.98	42.79	8.52	3.66	.17	11093	------
					Dry	41.22	49.02	9.76	4.19	.19	12708	14338
5190	34	8/12	Menard	5	16.29	36.66	38.73	8.32	3.65	.59	10747	------
					Dry	43.80	46.26	9.94	4.36	.71	12838	14528
5191	34	7/12	Menard	5	15.44	36.38	39.71	8.47	3.34	.26	10841	------
					Dry	43.03	46.96	10.01	3.95	.31	12820	14505
5192	34	7/12	Menard	5	20.27	34.58	37.43	7.72	3.31	.63	9919	------
					Dry	43.37	46.94	9.69	4.16	.79	12441	14402
5431	100	8/12	McLean	5	12.88	38.84	35.80	12.48	3.60	1.17	10601	------
					Dry	44.58	41.09	14.33	4.14	1.35	12168	14544
5432	100	8/12	McLean	5	13.34	38.39	36.72	11.55	3.59	1.31	10743	------
					Dry	44.30	42.37	13.33	4.14	1.51	12397	14629
5434	100	8/12	McLean	5	13.73	36.79	36.14	13.34	3.99	1.19	10399	------
					Dry	42.64	41.89	15.47	4.62	1.30	12054	14639
5289	25	8/12	Peoria	5	14.23	36.65	37.04	12.08	3.39	1.55	10483	------
					Dry	42.73	43.18	14.09	3.96	1.81	12220	14553
5290	25	8/12	Peoria	5	14.54	37.41	37.32	10.73	3.27	1.18	10705	------
					Dry	43.77	43.67	12.56	3.82	1.38	12526	14625
5291	25	8/12	Peoria	5	16.00	36.46	37.28	10.26	3.65	.90	10583	------
					Dry	43.41	44.38	12.21	4.35	1.07	12598	14664
5303	26	8/12	Peoria	5	16.00	36.06	37.54	10.40	2.90	1.27	10515	------
					Dry	42.93	44.69	12.38	3.46	1.51	12518	14773
5304	26	8/12	Peoria	5	14.23	37.41	37.36	11.00	3.14	2.17	10573	------
					Dry	43.62	43.56	12.82	3.66	2.53	12327	14433
5305	26	8/12	Peoria	5	14.76	35.95	35.34	13.95	3.19	2.00	10173	------
					Dry	42.18	41.46	16.36	3.74	2.34	11935	14636
84560	106	3/22	Peoria	5	13.5	30.7	45.5	10.3	3.2	.86	10900	------
					Dry	35.5	52.6	11.9	3.7	1.0	12600	14586
84561	106	3/22	Peoria	5	15.1	29.7	45.8	9.4	3.6	.43	10870	------
					Dry	35.0	53.9	11.1	4.3	.50	12800	14693
84562	106	3/22	Peoria	5	11.6	30.6	43.1	14.7	4.6	1.86	10540	------
					Dry	34.6	48.8	16.6	5.2	2.11	11930	14733

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
84230	107	3/22	Peoria	5	13.0	35.4	40.9	10.7	3.0	1.91	10830	------
					Dry	40.6	47.1	12.3	3.4	2.19	12450	14474
84231	107	3/22	Peoria	5	14.9	33.5	39.1	12.5	3.0	2.17	10450	------
					Dry	39.3	46.0	14.7	3.5	2.55	12280	14728
84232	107	3/22	Peoria	5	14.4	34.8	39.9	10.9	2.9	1.23	10740	------
					Dry	40.6	46.7	12.7	3.3	1.43	12540	14651
21032	[7]B. M. 2	2/15	Peoria	5	15.66	34.74	40.38	9.22	2.64	------	10798	------
					Dry	41.19	47.88	10.93	3.13	------	12803	14804
21033	[7]B. M. 2	2/15	Peoria	5	15.38	34.51	39.48	10.63	2.75	------	10645	------
					Dry	40.78	46.66	12.56	3.25	------	12580	14671
21034	[7]B. M. 2	2/15	Peoria	5	15.34	34.25	40.80	9.61	3.11	------	10741	------
					Dry	40.46	48.19	11.35	3.67	------	12686	14584
21035	[7]B. M. 2	2/15	Peoria	5	15.44	34.72	39.81	10.03	2.85	------	10744	------
					Dry	41.06	47.08	11.86	3.37	------	12706	14691
22982	[7]B. M. 3	10/15	Peoria	5	15.03	34.56	39.05	11.36	2.64	------	10490	------
					Dry	40.67	45.96	13.37	3.11	------	12346	14538
22983	[7]B. M. 3	10/15	Peoria	5	15.41	33.87	38.85	11.87	2.88	------	10386	------
					Dry	40.04	45.93	14.03	3.40	------	12278	14593
22984	[7]B. M. 3	10/15	Peoria	5	15.51	34.77	38.69	11.03	2.62	------	10489	------
					Dry	41.15	45.79	13.06	3.10	------	12415	14562
22985	[7]B. M. 3	10/15	Peoria	5	15.57	34.08	38.18	12.17	3.42	------	10283	------
					Dry	40.36	45.23	14.41	4.05	------	12179	14566
22986	[7]B. M. 3	10/15	Peoria	5	15.41	34.34	38.52	11.73	2.97	------	10422	------
					Dry	40.60	45.53	13.87	3.51	------	12321	14618
4985	43	6/12	Saline	5	6.34	37.72	48.20	7.74	2.03	.61	12620	------
					Dry	40.27	51.46	8.27	2.16	.65	13474	14869
4986	43	6/12	Saline	5	6.40	37.11	49.59	6.90	2.27	.40	12678	------
					Dry	39.65	52.97	7.38	2.43	.43	13546	14800
4987	43	6/12	Saline	5	8.85	32.53	51.52	7.10	.92	.66	12321	------
					Dry	35.65	56.57	7.78	1.00	.72	13502	14774
4989	43	6/12	Saline	5	6.80	35.06	50.39	7.75	2.30	.03	12514	------
					Dry	37.61	54.07	8.32	2.46	.03	13428	14853
4990	43	6/12	Saline	5	6.02	38.23	47.53	8.22	2.67	.45	12538	------
					Dry	40.68	50.58	8.74	2.84	.48	13341	14831
4992	43	6/12	Saline	5	7.39	35.38	50.73	6.50	2.15	.01	12642	------
					Dry	38.20	54.78	7.02	2.32	.01	13650	14848
4991	44	6/12	Saline	5	6.49	35.85	50.46	7.20	2.82	.01	12634	------
					Dry	38.34	53.97	7.69	3.02	.01	13511	14841
4993	44	6/12	Saline	5	6.71	35.68	49.64	7.97	2.69	.00	12482	------
					Dry	38.24	53.21	8.55	2.88	.00	13379	14839
4994	44	6/12	Saline	5	6.90	34.42	48.55	10.13	2.16	.03	12088	------
					Dry	36.97	52.16	10.87	2.32	.03	12984	14793

[7] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 123, p. 35, 1918.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
4997	45	6/12	Saline	5	6.71	35.59	49.98	7.72	2.38	.14	12092	
					Dry	38.14	53.59	8.27	2.55	.16	13332	14725
4909	45	6/12	Saline	5	7.45	34.18	49.88	8.49	2.78	.01	12336	
					Dry	36.94	53.90	9.16	3.01	.01	13329	14901
5001	45	6/12	Saline	5	6.94	34.56	50.93	7.57	2.30	.16	12485	
					Dry	37.14	54.72	8.14	2.46	.18	13415	14792
995	48	6/12	Saline	5	7.57	34.36	48.30	9.77	2.42	1.75	11956	
					Dry	37.18	52.25	10.57	2.62	1.89	12934	14662
5002	48	6/12	Saline	5	7.45	33.71	51.27	7.57	2.63	.31	12400	
					Dry	36.42	55.40	8.18	2.84	.35	13398	14794
5010	48	6/12	Saline	5	7.99	33.63	51.20	7.18	2.61	.05	12346	
					Dry	36.55	55.65	7.80	2.84	.05	13419	14732
5012	49	6/12	Saline	5	5.19	38.37	45.92	10.52	4.06	.46	12260	
					Dry	40.47	48.43	11.10	4.28	.49	12932	14847
5015	49	6/12	Saline	5	5.52	36.89	45.89	11.70	4.97	.72	11962	
					Dry	39.04	48.58	12.38	5.26	.76	12662	14809
5016	49	6/12	Saline	5	4.90	38.93	45.90	10.27	4.77	.47	12355	
					Dry	40.94	48.26	10.80	5.01	.49	12991	14815
5019	46	6/12	Saline	5	8.08	35.26	48.25	8.41	2.60	.38	12192	
					Dry	38.35	52.50	9.15	2.83	.41	13263	14818
5020	46	6/12	Saline	5	7.70	35.48	48.66	8.16	2.52	.32	12304	
					Dry	38.44	52.72	8.84	2.74	.36	13331	14833
5021	46	6/12	Saline	5	8.25	34.98	47.73	9.04	2.40	.85	11964	
					Dry	38.12	52.03	9.85	2.61	.92	13040	14684
5022	46	6/12	Saline	5	7.72	34.09	49.22	8.97	3.31	.23	12050	
					Dry	36.94	53.34	9.72	3.58	.25	13057	14716
5023	46	6/12	Saline	5	8.14	34.60	48.10	9.16	2.42	.74	11989	
					Dry	37.66	52.36	9.98	2.64	.80	13051	14717
5024	46	6/12	Saline	5	7.85	33.72	49.30	9.13	3.48	.24	11971	
					Dry	36.59	53.50	9.91	3.78	.26	12990	14676
12931	124	7/21	Saline	5	7.10	33.34	51.33	8.14	2.58	.13	12354	
					Dry	35.93	55.30	8.77	2.78	.14	13313	14798
12932	124	7/21	Saline	5	6.78	33.62	51.96	7.64	2.40	.11	12490	
					Dry	36.07	55.74	8.19	2.58	.11	13399	14788
12933	124	7/21	Saline	5	6.62	32.79	52.27	8.32	1.74	.42	12463	
					Dry	35.11	55.98	8.91	1.86	.45	13347	14832
12934	125	7/21	Saline	5	6.65	33.52	52.48	7.35	1.93	.13	12609	
					Dry	35.91	56.22	7.87	2.07	.13	13507	14834
12935	125	7/21	Saline	5	6.28	33.35	51.48	8.89	3.07	.09	12357	
					Dry	35.58	54.93	9.49	3.28	.09	13185	14805
12936	125	7/21	Saline	5	6.85	33.65	52.28	7.22	2.11	.05	12612	
					Dry	36.13	56.12	7.75	2.27	.05	13539	14854
12937	126	7/21	Saline	5	5.75	33.90	53.21	7.14	2.29	.04	12624	
					Dry	35.97	56.46	7.57	2.43	.04	13394	14668
12938	126	7/21	Saline	5	6.13	34.28	51.83	7.76	2.75	.27	12615	
					Dry	36.52	55.22	8.26	2.60	.29	13439	14830

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
12939	126	7/21	Saline	5	6.18	33.97	51.99	7.86	2.65	.16	12508	------
					Dry	36.21	55.42	8.37	2.82	.17	13191	14753
12901	127	7/21	Saline	5	5.51	33.34	53.39	7.76	1.92	.34	12687	------
					Dry	35.28	56.51	8.21	2.03	.36	13427	14771
12902	127	7/21	Saline	5	6.05	34.38	51.87	7.70	1.98	.42	12580	------
					Dry	36.59	55.21	8.20	2.11	.44	13390	14765
12903	127	7/21	Saline	5	5.50	33.64	52.49	8.37	2.51	.51	12576	------
					Dry	35.60	55.54	8.86	2.66	.54	13308	14806
12911	128	7/21	Saline	5	6.52	33.57	52.37	7.54	2.57	.03	12552	------
					Dry	35.91	56.02	8.07	2.75	.03	13428	14805
12912	128	7/21	Saline	5	6.84	30.30	48.02	14.84	1.46	.03	11343	------
					Dry	32.52	51.55	15.93	1.57	.03	12176	14764
12913	128	7/21	Saline	5	6.17	32.87	53.54	7.42	1.60	.13	12631	------
					Dry	35.03	57.06	7.91	1.71	.14	13462	14777
12917	129	7/21	Saline	5	5.62	34.61	52.52	7.25	2.02	.08	12781	------
					Dry	36.67	55.65	7.68	2.14	.09	13542	14840
12918	129	7/21	Saline	5	5.75	35.01	52.65	6.59	2.05	.05	12800	------
					Dry	37.15	55.86	6.99	2.18	.05	13581	14927
12919	129	7/21	Saline	5	6.58	32.89	53.29	7.24	2.06	.14	12565	------
					Dry	35.21	57.14	7.75	2.20	.15	13450	14754
12914	130	7/21	Saline	5	6.05	33.67	51.48	8.80	2.72	.34	12401	------
					Dry	35.84	54.79	9.37	2.90	.35	13200	14786
12915	130	7/21	Saline	5	6.69	32.54	51.44	9.33	2.62	.06	12225	------
					Dry	34.88	55.13	9.99	2.81	.07	13101	14785
12916	130	7/21	Saline	5	5.93	33.79	51.51	8.77	2.63	.10	12393	------
					Dry	35.92	54.76	9.32	2.80	.11	13774	14746
5494	131	8/12	Saline	5	3.72	34.44	52.91	8.93	3.76	.03	13032	------
					Dry	35.77	54.96	9.27	3.90	.03	13535	15186
5530	132	8/12	Saline	5	4.03	33.71	51.84	10.42	4.19	.02	12783	------
					Dry	35.13	54.01	10.86	4.37	.02	13319	15255
5529	133	8/12	Saline	5	3.40	33.33	55.18	8.09	4.25	.03	13401	------
					Dry	34.50	57.12	8.38	4.40	.03	13872	15420
4413	[8]B. M. 5	1/07	Saline	5	7.55	33.85	51.45	7.15	1.56	------	------	------
					Dry	36.61	55.66	7.73	1.69	------	------	------
4414	[8]B. M. 5	1/07	Saline	5	7.51	32.81	52.20	7.48	1.58	------	12686	------
					Dry	35.47	56.44	8.09	1.71	------	13716	15090
7420	[8]B. M. 5	1/07	Saline	5	6.98	31.64	53.41	7.97	------	------	------	------
					Dry	34.01	57.42	8.57	------	------	------	------
7421	[8]B. M. 5	1/07	Saline	5	7.40	31.28	54.74	6.58	------	------	------	------
					Dry	33.78	59.11	7.11	------	------	------	------
4622	[8]B. M. 5	1/07	Saline	5	7.81	33.54	50.27	8.38	2.36	------	12418	------
					Dry	36.38	54.53	9.09	2.56	------	13469	15552
4636	[8]B. M. 5	1/07	Saline	5	9.33	30.92	47.86	11.89	2.76	------	11572	------
					Dry	34.10	52.79	13.11	3.04	------	12764	14984

[8] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 90, 1913.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
7501	[8]B. M. 6	3/09	Saline	5	6.01 Dry	32.37 34.44	54.32 57.79	7.30 7.77	1.66 1.77	------ ------	12793 13610	------ 14916
7502	[8]B. M. 6	3/09	Saline	5	5.56 Dry	34.41 36.44	51.31 54.33	8.72 9.23	2.87 3.04	------ ------	12643 13386	------ 15324
12794	[9]B. M. 7	8/11	Saline	5	7.12 Dry	34.55 37.20	50.68 54.56	7.65 8.24	2.23 2.40	------ ------	12481 13439	------ 14835
12795	[9]B. M. 7	8/11	Saline	5	7.02 Dry	34.58 37.19	51.46 55.35	6.94 7.46	2.07 2.23	------ ------	12640 13594	------ 14862
28448	[10]B. M. 8	7/17	Saline	5	4.73 Dry	37.88 39.76	47.70 50.07	9.69 10.17	4.13 4.33	------ ------	12463 13081	------ 14844
28449	[10]B. M. 8	7/17	Saline	5	4.94 Dry	39.50 41.55	45.79 48.17	9.77 10.28	3.94 4.14	------ ------	12420 13066	------ 14840
1704	[11]B. M. 41	6/05	Sangamon	5	13.89 Dry	33.96 39.43	40.89 47.49	11.26 13.08	3.83 4.45	------ ------	10636 12352	------ 14543
1705	[11]B. M. 41	6/05	Sangamon	5	14.45 Dry	34.79 40.67	40.10 46.87	10.66 12.46	3.46 4.04	------ ------	------ ------	------ ------
1740	[11]B. M. 41	6/05	Sangamon	5	12.77 Dry	34.68 39.76	40.77 46.74	11.78 13.50	4.16 4.77	------ ------	10757 12332	------ 13395
5118	36	7/12	Sangamon	5	16.05 Dry	35.82 42.66	37.14 44.25	10.99 13.09	3.55 4.22	.67 .80	10330 12306	------ 14476
5119	36	7/12	Sangamon	5	15.53 Dry	36.36 43.04	38.05 45.05	10.06 11.91	3.86 4.57	.55 .66	10522 12457	------ 14450
5120	36	7/12	Sangamon	5	14.45 Dry	37.46 43.79	38.27 44.73	9.82 11.48	3.59 4.19	.55 .65	10704 12512	------ 14423
5128	37	7/12	Sangamon	5	14.08 Dry	37.38 43.51	37.56 43.71	10.98 12.78	3.97 5.17	.38 .49	9471 12337	------ 14492
5129	37	7/12	Sangamon	5	13.86 Dry	37.11 43.08	39.05 45.34	9.98 11.58	2.57 4.07	.52 .61	10726 12451	------ 14365
5166	39	7/12	Sangamon	5	13.38 Dry	37.20 42.95	36.40 42.03	13.01 15.02	4.78 5.52	.96 1.10	10338 11934	------ 14439
5167	39	7/12	Sangamon	5	13.35 Dry	36.64 42.27	37.12 42.85	12.89 14.88	4.80 5.53	.84 .97	10348 11942	------ 14423
5168	39	7/12	Sangamon	5	13.19 Dry	38.44 44.28	36.47 42.00	11.90 13.72	4.61 5.31	1.05 1.20	10513 12110	------ 14397
5187	40	7/12	Sangamon	5	14.82 Dry	37.18 43.65	38.22 44.87	9.78 11.48	4.30 4.52	.72 .84	10683 12541	------ 14483
5188	40	7/12	Sangamon	5	16.05 Dry	35.58 42.38	38.04 45.32	10.33 12.30	4.18 4.98	.17 .20	10413 12404	------ 14476
5189	40	7/12	Sangamon	5	14.31 Dry	37.31 43.54	38.20 44.58	10.18 11.88	4.21 4.91	.90 1.05	10655 12434	------ 14251
5196	38	7/12	Sangamon	5	14.25 Dry	37.25 43.44	37.07 43.24	11.43 13.32	4.76 5.55	.98 1.15	10414 12147	------ 14381
5197	38	7/12	Sangamon	5	14.10 Dry	38.74 45.09	37.66 43.85	9.50 11.06	3.86 4.50	.75 .87	10790 12564	------ 14415

[9] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 85, p. 37, 1914.
[10] U. S. Bureau of Mines, unpublished analyses.
[11] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 91, 1913.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5198	38	7/12	Sangamon	5	14.44	38.22	37.68	9.66	3.79	.63	10746	
					Dry	44.67	44.04	11.29	4.43	.73	12549	14435
5199	38	7/12	Sangamon	5	14.08	38.05	35.30	12.57	5.87	.60	10228	
					Dry	44.28	41.09	14.63	6.83	.69	11903	14366
81448	119	9/21	Sangamon	5	13.79	34.86	39.58	11.77	3.88	.58	10576	
					Dry	40.44	45.91	13.65	4.50	.67	12268	14546
81449	119	9/21	Sangamon	5	14.78	35.20	39.74	10.28	3.72	.33	10606	
					Dry	41.30	46.64	12.06	4.37	.39	12445	14454
81450	119	9/21	Sangamon	5	13.62	37.50	39.30	9.58	3.62	.39	10876	
					Dry	43.41	45.50	11.09	4.06	.45	12591	14439
81452	120	9/21	Sangamon	5	13.19	36.95	41.18	8.68	3.65	.44	11120	
					Dry	42.56	47.44	10.00	4.20	.51	12810	14381
81453	120	9/21	Sangamon	5	13.75	37.20	37.60	11.45	4.38	1.09	10567	
					Dry	43.13	43.59	13.28	5.08	1.26	12252	14478
81454	120	9/21	Sangamon	5	13.84	36.29	38.94	10.83	3.76	.85	10672	
					Dry	42.17	45.25	12.58	4.37	.99	12401	14499
81456	121	9/21	Sangamon	5	13.26	34.27	41.93	10.54	3.71	.16	10824	
					Dry	39.51	48.34	12.15	4.28	.18	12479	14509
81457	121	9/21	Sangamon	5	14.14	35.08	40.61	10.17	3.87	.67	10709	
					Dry	40.86	47.30	11.84	4.51	.78	12473	14453
81458	121	9/21	Sangamon	5	14.79	34.30	40.77	10.14	3.68	.53	10691	
					Dry	40.25	47.85	11.90	4.32	.62	12547	14544
81440	122	9/21	Sangamon	5	13.09	36.51	41.14	9.26	3.77	.70	10935	
					Dry	42.01	47.34	10.65	4.34	.81	12582	14609
81441	122	9/21	Sangamon	5	12.76	35.36	41.92	9.96	3.98	.82	10907	
					Dry	40.53	48.05	11.42	4.56	.94	12502	14411
81442	122	9/21	Sangamon	5	13.62	35.00	40.80	10.58	3.95	.35	10594	
					Dry	40.52	47.23	12.25	4.57	.41	12264	14282
81311	217	9/21	Shelby	5	12.10	35.78	40.71	11.41	3.46	.78	10807	
					Dry	40.71	46.31	12.98	3.94	.89	12295	14506
81312	217	9/21	Shelby	5	10.42	36.85	42.83	9.90	3.48	.23	11335	
					Dry	41.14	47.81	11.05	3.88	.26	12653	14499
81313	217	9/21	Shelby	5	10.71	37.16	40.91	11.22	4.16	.57	11009	
					Dry	41.62	45.81	12.57	4.66	.64	12330	14701
5277	27	7/12	Tazewell	5	14.71	37.46	38.57	10.26	3.51	1.15	10801	
					Dry	44.06	44.03	11.91	4.07	1.33	12516	14500
5278	27	7/12	Tazewell	5	13.88	37.58	40.01	8.53	2.55	.95	11076	
					Dry	43.64	46.45	9.91	2.96	1.10	12860	14499
5281	27	8/12	Tazewell	5	15.56	37.60	36.70	10.14	3.23	1.50	10552	
					Dry	44.53	43.46	12.01	3.83	1.78	12496	14488
84483	108	3/22	Tazewell	5	15.4	35.1	40.4	9.1	2.6	1.26	10720	
					Dry	41.5	47.8	10.7	3.0	1.49	12670	14261
84484	108	3/22	Tazewell	5	16.5	32.8	41.6	9.1	3.1	.57	10590	
					Dry	39.3	49.8	10.9	3.7	.68	12690	14508
84485	108	3/22	Tazewell	5	15.4	35.2	39.8	9.6	4.2	.42	10670	
					Dry	41.6	47.1	11.3	5.0	.50	12610	15524

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
					No. 6 Coal.							
80788	218	8/21	Bond	6	11.69	34.15	43.22	10.94	3.55	.80	10784	------
					Dry	38.67	48.94	12.39	4.02	.91	12212	14229
80789	218	8/21	Bond	6	12.55	35.58	41.60	10.27	3.51	.41	10745	------
					Dry	40.69	47.57	11.74	4.01	.47	12287	14199
80790	218	8/21	Bond	6	11.64	35.55	42.12	10.69	3.09	.79	10890	------
					Dry	40.23	47.67	12.10	3.50	.89	12325	14294
81315	219	9/21	Christian	6	11.96	36.12	42.08	9.84	3.31	.21	10989	------
					Dry	41.03	47.79	11.18	3.76	.24	12482	14318
81316	219	9/21	Christian	6	11.74	37.52	37.67	13.07	5.23	.39	10482	------
					Dry	42.51	42.68	14.81	5.93	.44	11876	14706
81317	219	9/21	Christian	6	12.30	38.02	39.56	10.12	3.03	.76	10824	------
					Dry	43.35	45.11	11.54	3.45	.87	12456	14343
81444	220	9/21	Christian	6	13.34	36.44	39.03	11.19	3.63	.77	10679	------
					Dry	42.05	45.04	12.91	4.19	.89	12323	14382
81445	220	9/21	Christian	6	13.67	35.65	39.60	11.08	4.17	.57	10622	------
					Dry	41.30	45.87	12.83	4.83	.66	12304	14448
81446	220	9/21	Christian	6	14.74	37.10	39.34	8.82	4.20	.30	10745	------
					Dry	43.51	46.15	10.34	4.93	.35	12603	14649
81138	221	8/21	Christian	6	11.12	37.81	41.16	9.91	4.15	.17	11070	------
					Dry	42.54	46.31	11.15	4.67	.19	12455	14311
81139	221	8/21	Christian	6	12.21	37.30	40.87	9.62	4.08	.05	10951	------
					Dry	42.49	46.55	10.96	4.65	.06	12474	14299
81140	221	8/21	Christian	6	12.81	36.18	39.79	11.22	4.28	.46	10642	------
					Dry	41.50	45.63	12.87	4.91	.53	12206	14340
81142	222	8/21	Christian	6	12.27	37.17	40.67	9.89	3.49	.08	10917	------
					Dry	42.37	46.36	11.27	3.98	.09	12444	14298
81143	222	8/21	Christian	6	11.75	37.46	41.33	9.46	4.38	.23	11089	------
					Dry	42.45	46.83	10.72	4.96	.26	12565	14372
81144	222	8/21	Christian	6	12.31	38.31	41.22	8.16	3.27	.04	11124	------
					Dry	43.69	47.00	9.31	3.73	.05	12686	13083
25748	[12]B. M. 56	9/16	Christian	6	13.62	37.60	39.62	9.16	3.78	------	11020	------
					Dry	43.53	45.87	10.60	4.38	------	12757	14553
25749	[12]B. M. 56	9/16	Christian	6	13.72	37.42	39.05	9.81	4.11	------	10847	------
					Dry	43.37	45.26	11.37	4.76	------	12571	14490
25750	[12]B. M. 56	9/16	Christian	6	12.52	34.74	39.06	13.68	3.40	------	10386	------
					Dry	39.71	44.65	15.64	3.89	------	11873	14245
25751	[12]B. M. 56	9/16	Christian	6	12.31	38.59	39.15	9.95	3.54	------	11086	------
					Dry	44.00	44.65	11.35	4.04	------	12641	14544
26336	[12]B. M. 56	11/16	Christian	6	11.89	37.14	40.58	10.39	3.88	------	11056	------
					Dry	42.15	46.06	11.79	4.40	------	12548	14529
26337	[12]B. M. 56	11/16	Christian	6	11.98	38.52	39.18	10.32	4.21	------	11120	------
					Dry	43.76	44.72	11.72	4.78	------	12634	14293

[12] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 193, p. 30, 1922.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5052	85	8/12	Clinton	6	12.60	36.78	40.48	10.14	2.88	.77	10827	------
					Dry	42.07	46.32	11.61	3.29	.88	12388	14269
5053	85	7/12	Clinton	6	12.15	37.74	40.52	9.59	3.51	.29	10949	------
					Dry	42.96	46.13	10.91	3.99	.33	12464	14256
5054	85	7/12	Clinton	6	12.43	37.23	39.93	10.41	4.19	.38	10730	------
					Dry	41.28	46.84	11.88	4.79	.44	12253	14211
5073	84	7/12	Clinton	6	13.32	37.43	39.02	10.23	4.06	.69	10726	------
					Dry	43.18	45.02	11.80	4.68	.80	12374	14336
5074	84	7/12	Clinton	6	12.40	37.94	39.04	10.62	4.24	.58	10796	------
					Dry	43.32	44.56	12.12	4.84	.69	12323	14380
80744	198	8/21	Clinton	6	11.78	36.43	40.93	10.86	4.22	.63	10771	------
					Dry	41.29	46.40	12.31	4.78	.71	12209	14234
80745	198	8/21	Clinton	6	11.40	36.59	41.07	10.94	3.74	.62	10817	------
					Dry	41.30	46.35	12.35	4.22	.70	12209	14887
80746	198	8/21	Clinton	6	10.11	37.97	41.14	10.78	2.58	.60	11064	------
					Dry	42.24	45.77	11.99	2.87	.67	12308	14231
80767	199	8/21	Clinton	6	10.52	34.59	43.42	11.47	3.80	.35	10953	------
					Dry	38.66	48.52	12.82	4.25	.39	12241	13151
80768	199	8/21	Clinton	6	11.73	35.25	43.87	9.15	3.48	.22	11034	------
					Dry	39.93	49.70	10.37	3.94	.25	12500	14201
80769	199	8/21	Clinton	6	11.26	34.94	42.49	11.31	3.46	.77	10774	------
					Dry	39.38	47.87	12.75	3.90	.87	12141	14207
2856	[13]B. M. 46	2/06	Clinton	6	11.64	35.41	44.29	8.66	3.41	------	11290	------
					Dry	40.07	50.13	9.80	3.86	------	12776	14415
2857	[13]B. M. 46	2/06	Clinton	6	12.15	35.60	42.97	9.28	4.01	------	------	------
					Dry	40.52	48.92	10.56	4.56	------	------	------
2991	[13]B. M. 46	2/06	Clinton	6	11.35	34.62	40.63	13.40	4.76	------	10733	------
					Dry	39.05	45.83	15.12	5.37	------	12107	14312
2854	[13]B. M. 47	2/06	Clinton	6	13.43	33.02	44.37	9.18	3.35	------	10937	------
					Dry	38.14	51.26	10.60	3.87	------	12634	14619
2855	[13]B. M. 47	2/06	Clinton	6	12.73	33.35	44.32	9.60	3.60	------	------	------
					Dry	38.21	50.79	11.00	4.13	------	------	------
2972	[13]B. M. 47	2/06	Clinton	6	11.44	33.93	43.92	10.71	4.94	------	10958	------
					Dry	38.31	49.60	13.09	5.58	------	12373	14983
4384	[13]B. M. 48	1/07	Clinton	6	14.45	29.76	46.16	9.63	2.09	------	------	------
					Dry	34.79	53.95	11.26	2.44	------	------	------
4385	[13]B. M. 48	1/07	Clinton	6	15.06	29.48	45.81	9.65	1.05	------	10726	------
					Dry	34.71	53.93	11.36	1.24	------	12629	14447
4785	53	4/12	Franklin	6	10.57	33.37	43.09	12.97	.83	4.38	10714	------
					Dry	37.30	48.19	14.51	.93	4.89	11980	14236
4786	53	4/12	Franklin	6	10.00	32.80	50.92	6.27	.66	.33	12001	------
					Dry	36.45	56.59	6.96	.73	.36	13334	14453
4787	53	4/12	Franklin	6	10.15	32.88	50.56	6.41	.59	.22	12000	------
					Dry	36.59	56.27	7.14	.65	.25	13356	14494

[13] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 83, 1913.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
4789	53	4/12	Franklin	6	10.00	32.08	50.93	6.98	.47	.17	11935	
					Dry	35.65	56.60	7.75	.52	.20	13261	14492
4791	58	4/12	Franklin	6	8.70	34.62	48.92	7.76	.62	.31	11945	
					Dry	37.92	53.59	8.49	.68	.34	13084	14426
4793	58	4/12	Franklin	6	9.04	34.46	48.73	7.77	.68	.23	11946	
					Dry	37.88	53.59	8.53	.74	.25	13133	14490
4794	58	4/12	Franklin	6	9.05	34.45	48.75	7.75	.91	.37	11923	
					Dry	37.88	53.59	8.53	1.00	.41	13108	14472
4810	52	4/12	Franklin	6	6.96	38.42	44.16	10.46	2.98	.92	11848	
					Dry	41.29	47.47	11.24	3.21	.99	12733	14568
4811	52	4/12	Franklin	6	7.34	38.11	44.23	10.32	3.26	1.41	11771	
					Dry	41.13	47.73	11.14	3.51	1.53	12703	14561
4812	52	4/12	Franklin	6	6.00	38.55	45.46	9.99	3.16	1.20	11998	
					Dry	41.01	48.36	10.63	3.36	1.28	12776	14534
5008	51	6/12	Franklin	6	10.63	33.23	48.79	7.35	1.40	.38	11800	
					Dry	37.18	54.59	8.23	1.19	.43	13207	14534
5009	51	6/12	Franklin	6	9.83	33.91	49.14	7.12	1.13	.18	11942	
					Dry	37.62	54.48	7.90	1.25	.20	13245	14522
5011	51	6/12	Franklin	6	10.39	33.13	49.23	7.25	1.37	.06	11920	
					Dry	36.97	54.93	8.10	1.53	.06	13303	14629
5208	56	7/12	Franklin	6	6.43	37.62	44.77	11.18	2.64	.64	11834	
					Dry	40.20	47.85	11.95	2.82	.68	12646	14620
5209	56	7/12	Franklin	6	10.15	35.55	45.82	8.48	1.41	.80	11691	
					Dry	39.56	51.01	9.43	1.57	.89	13011	14539
5211	56	7/12	Franklin	6	7.71	35.75	45.38	11.16	3.50	.89	11644	
					Dry	38.74	49.17	12.09	3.79	.96	12616	14644
5222	50	7/12	Franklin	6	9.66	34.55	47.85	7.95	1.04	.31	11916	
					Dry	38.24	52.97	8.79	1.15	.34	13190	14613
5223	50	7/12	Franklin	6	9.00	35.10	47.35	8.55	1.08	.40	11973	
					Dry	38.58	53.03	9.39	1.19	.44	13159	14684
5224	50	7/12	Franklin	6	9.36	34.86	48.90	6.88	1.01	.43	12122	
					Dry	38.46	53.96	7.58	1.12	.48	13373	14603
5507	57	8/12	Franklin	6	9.83	31.82	49.78	8.57	.79	.35	11702	
					Dry	35.28	55.22	9.50	.88	.39	12977	14490
5508	57	8/12	Franklin	6	9.44	32.57	50.09	7.90	.67	.29	11914	
					Dry	35.97	55.31	8.72	.74	.32	13156	14547
5509	57	8/12	Franklin	6	9.75	32.33	48.77	9.15	1.39	.32	11652	
					Dry	35.83	54.03	10.14	1.54	.35	12911	14550
12701	134	6/21	Franklin	6	8.88	32.17	50.84	8.11	.78	.11	11862	
					Dry	35.31	55.80	8.89	.86	.12	13018	14428
12702	134	6/21	Franklin	6	7.11	34.23	48.83	9.83	1.30	.35	11883	
					Dry	36.85	52.57	10.58	1.40	.37	12716	14483
12703	134	6/21	Franklin	6	8.31	34.07	49.44	8.18	1.02	.21	12010	
					Dry	37.16	53.91	8.93	1.12	.23	13043	14534
12720	134	6/21	Franklin	6	9.24	32.39	49.49	8.88	1.50	.21	11722	
					Dry	35.69	54.53	9.78	1.65	.23	12833	14496

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
12721	134	6/21	Franklin	6	7.61	34.77	48.96	8.66	1.70	.05	12038	------
					Dry	37.63	53.00	9.37	1.85	.05	12937	14559
12722	134	6/21	Franklin	6	8.56	31.76	50.52	9.16	1.29	.32	11662	------
					Dry	34.73	55.26	10.01	1.41	.35	12683	14346
12729	136	6/21	Franklin	6	6.72	35.94	46.32	11.02	3.11	.72	11599	------
					Dry	38.53	49.65	11.82	3.33	.78	12268	14365
12730	136	6/21	Franklin	6	6.95	35.53	46.19	11.33	3.42	.51	11469	------
					Dry	38.18	49.65	12.17	3.68	.55	12444	14450
12731	136	6/21	Franklin	6	8.36	32.98	51.49	7.17	1.28	.26	12070	------
					Dry	35.99	56.19	7.82	1.40	.28	13100	14430
12732	136	6/21	Franklin	6	6.23	36.30	46.99	10.08	3.63	.39	11797	------
					Dry	38.88	50.32	10.80	3.89	.42	12440	14433
12733	136	6/21	Franklin	6	8.46	35.77	46.51	9.26	2.40	.15	11712	------
					Dry	39.08	50.80	10.12	2.73	.17	12607	14487
12734	136	6/21	Franklin	6	7.52	34.46	48.88	9.14	1.20	.22	11895	------
					Dry	37.26	52.86	9.88	1.30	.24	12797	14440
30892	137	9/18	Franklin	6	10.04	35.48	47.29	7.19	.77	------	11945	------
					Dry	39.44	52.57	7.99	.86	------	13279	14608
30893	137	9/18	Franklin	6	11.33	32.38	47.18	9.11	.59	------	11430	------
					Dry	36.52	53.21	10.27	.67	------	12892	14521
30894	137	9/18	Franklin	6	9.04	36.20	47.86	6.90	1.28	------	12164	------
					Dry	39.80	52.61	7.59	1.41	------	13374	14615
30895	137	9/18	Franklin	6	10.43	32.10	48.50	7.97	.52	------	11713	------
					Dry	36.95	54.15	8.90	.58	------	13075	14482
29741	138	2/18	Franklin	6	9.73	34.19	48.97	7.09	1.08	------	11997	------
					Dry	37.88	54.27	7.85	1.20	------	13289	14559
29742	138	2/18	Franklin	6	10.34	33.70	46.90	9.06	.54	------	11529	------
					Dry	37.59	52.31	10.10	.60	------	12857	14451
29743	138	2/18	Franklin	6	9.28	34.17	48.77	7.78	.74	------	11885	------
					Dry	37.67	53.75	8.58	.82	------	13100	14465
29744	138	2/18	Franklin	6	9.17	34.29	49.15	7.39	1.17	------	12163	------
					Dry	37.75	54.11	8.14	1.29	------	13390	14723
29745	138	2/18	Franklin	6	10.56	34.81	44.74	9.90	.45	------	11354	------
					Dry	38.92	50.01	11.07	.50	------	12695	14271
29746	138	2/18	Franklin	6	10.36	32.12	47.21	10.31	.56	------	11326	------
					Dry	35.83	52.67	11.50	.62	------	12634	14446
29754	138	2/18	Franklin	6	9.50	36.82	49.82	3.86	.79	------	12515	------
					Dry	40.69	55.04	4.27	.87	------	13829	13831
12682	139	6/21	Franklin	6	7.06	35.69	45.24	12.01	3.50	.33	11487	------
					Dry	38.41	48.67	12.92	3.77	.35	12171	14494
12683	139	6/21	Franklin	6	10.07	32.64	50.15	7.14	.76	.22	11850	------
					Dry	36.29	55.77	7.94	.85	.24	13177	14441
12684	139	6/21	Franklin	6	8.28	34.98	49.38	7.36	1.13	.25	12047	------
					Dry	38.14	53.84	8.02	1.24	.27	13072	14419
12698	139	6/21	Franklin	6	6.79	37.24	46.38	9.59	3.38	.31	11858	------
					Dry	39.96	49.76	10.28	3.63	.33	12541	14430

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
12699	139	6/21	Franklin	6	8.07	33.85	49.71	8.37	1.02	.05	11908	------
					Dry	36.82	54.08	9.10	1.11	.05	12900	14420
12700	139	6/21	Franklin	6	6.96	36.53	44.79	11.72	3.95	.20	11590	------
					Dry	39.27	48.13	12.60	4.24	.22	12245	14567
12738	140	6/21	Franklin	6	5.74	36.04	48.19	10.03	3.37	.36	11960	------
					Dry	38.23	51.13	10.64	3.57	.38	12509	14453
12739	140	6/21	Franklin	6	6.64	36.34	48.38	8.64	2.75	.05	12043	------
					Dry	38.92	51.83	9.25	2.94	.05	12753	14444
12740	140	6/21	Franklin	6	8.15	32.79	51.10	7.96	1.51	.14	11890	------
					Dry	35.70	55.63	8.67	1.64	.16	12863	14337
30882	141	10/18	Franklin	6	9.94	33.39	48.99	7.68	1.14	------	11880	------
					Dry	37.08	54.39	8.53	1.27	------	13192	14571
30883	141	10/18	Franklin	6	10.04	33.08	49.42	7.46	1.24	------	11898	------
					Dry	36.77	54.94	8.29	1.38	------	13226	14677
30884	141	10/18	Franklin	6	10.73	33.02	47.65	8.60	1.61	------	11637	------
					Dry	36.99	53.38	9.63	1.80	------	13036	14609
30885	141	10/18	Franklin	6	10.05	33.93	48.58	7.44	1.40	------	11884	------
					Dry	37.72	54.01	8.27	1.56	------	13210	14674
23442	142	12/15	Franklin	6	9.72	32.91	48.92	8.45	.87	------	11866	------
					Dry	36.45	54.19	9.36	.96	------	13144	14653
23443	142	12/15	Franklin	6	10.24	32.54	49.49	7.73	.80	------	11941	------
					Dry	36.25	55.14	8.61	.89	------	13304	14697
30887	143	10/18	Franklin	6	11.15	33.95	47.50	7.40	1.36	------	11734	------
					Dry	38.21	53.46	8.33	1.53	------	13207	14681
30888	143	10/18	Franklin	6	9.08	34.99	48.21	7.72	1.43	------	12019	------
					Dry	38.49	53.02	8.49	1.57	------	13219	14723
30889	143	10/18	Franklin	6	10.31	33.54	49.91	6.24	1.11	------	12055	------
					Dry	37.40	55.64	6.96	1.24	------	13441	14574
30867	144	9/18	Franklin	6	10.74	32.20	50.91	6.15	.83	------	12001	------
					Dry	36.07	57.04	6.89	.93	------	13444	14555
30868	144	9/18	Franklin	6	10.36	32.52	47.17	9.95	.63	------	11356	------
					Dry	36.28	52.62	11.10	.70	------	12668	14416
30869	144	9/18	Franklin	6	9.86	32.38	49.68	8.08	.93	------	11925	------
					Dry	35.92	55.12	8.96	1.03	------	13230	14682
30870	144	9/18	Franklin	6	10.91	32.32	50.89	5.88	.56	------	12049	------
					Dry	36.28	57.12	6.60	.63	------	13525	14548
12865	145	7/21	Franklin	6	8.33	31.23	51.35	9.09	1.24	.25	11846	------
					Dry	34.07	56.02	9.91	1.35	.27	12859	14512
12866	145	7/21	Franklin	6	8.17	32.54	50.60	8.69	1.20	.15	11942	------
					Dry	35.43	55.11	9.46	1.31	.17	12945	14525
12867	145	7/21	Franklin	6	8.96	32.71	50.71	7.62	.67	.08	11964	------
					Dry	35.93	55.70	8.37	.74	.08	13104	14472
20080	146	11/14	Franklin	6	9.33	31.15	50.36	9.16	.56	------	11806	------
					Dry	34.36	55.54	10.10	.62	------	13021	14636
20081	146	11/14	Franklin	6	10.01	29.93	50.08	9.98	.52	------	11522	------
					Dry	33.26	55.65	11.09	.58	------	12803	14564

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
20082	146	11/14	Franklin	6	9.25	31.03	51.02	8.70	.48	------	11857	------
					Dry	34.19	56.22	9.59	.53	------	13064	14478
20723	146	1/15	Franklin	6	8.21	32.46	49.00	10.33	.96	------	11770	------
					Dry	35.36	53.39	11.25	1.05	------	12823	14525
20724	146	1/15	Franklin	6	9.07	32.24	48.42	10.27	1.14	------	11606	------
					Dry	35.45	53.26	11.29	1.25	------	12764	14578
20725	146	1/15	Franklin	6	9.83	31.44	51.53	7.20	.50	------	11990	------
					Dry	34.87	57.15	7.98	.55	------	13297	14568
30877	147	10/18	Franklin	6	8.72	34.31	46.15	10.82	3.81	------	11543	------
					Dry	37.59	50.56	11.85	4.17	------	12645	14645
30878	147	9/18	Franklin	6	10.04	33.77	47.53	8.66	2.43	------	11725	------
					Dry	37.54	52.83	9.63	2.70	------	13034	14791
30879	147	10/18	Franklin	6	9.67	33.32	46.67	10.34	3.07	------	11547	------
					Dry	36.89	51.66	11.45	3.40	------	12784	14485
30880	147	10/18	Franklin	6	9.27	34.27	45.48	10.98	3.79	------	11461	------
					Dry	37.77	50.13	12.10	4.18	------	12632	14677
1695	[14]B. M. 9	/05	Franklin	6	10.28	32.04	49.74	7.94	1.06	------	------	------
					Dry	35.71	55.44	8.85	1.18	------	------	------
1694	[14]B. M. 9	/05	Franklin	6	9.46	33.55	48.87	8.12	1.63	------	11990	------
					Dry	37.06	53.97	8.97	1.80	------	13243	14725
1786	[14]B. M. 9	/05	Franklin	6	8.31	31.65	49.56	10.48	1.55	------	11727	------
					Dry	34.52	54.05	11.43	1.69	------	12789	14647
477D	[14]B. M. 10	8/08	Franklin	6	9.15	34.98	47.27	8.60	.99	------	------	------
					Dry	38.50	52.03	9.47	1.09	------	------	------
478D	[14]B. M. 10	8/08	Franklin	6	8.59	32.15	51.03	8.23	1.29	------	12114	------
					Dry	35.17	55.83	9.00	1.41	------	13253	14728
486D	[14]B. M. 10	8/08	Franklin	6	8.12	34.46	48.79	8.63	1.13	------	12064	------
					Dry	37.51	53.10	9.39	1.23	------	13131	14654
495D	[14]B. M. 10	8/08	Franklin	6	8.61	33.19	46.82	11.38	.95	------	11585	------
					Dry	36.32	51.23	12.45	1.04	------	12676	14682
1648	[15]B. M. 11	8/08	Franklin	6	9.50	31.98	47.08	11.44	1.45	------	11506	------
					Dry	35.34	52.02	12.64	1.60	------	12713	14780
1871	[15]B. M. 12	7/06	Franklin	6	9.90	28.67	53.69	7.74	.48	------	12001	------
					Dry	31.82	59.59	8.59	.53	------	13320	14700
1872	[15]B. M. 12	7/06	Franklin	6	10.53	29.06	53.01	7.40	.47	------	------	------
					Dry	32.48	59.25	8.27	.53	------	------	------
3408	[15]B. M. 12	7/06	Franklin	6	9.65	30.87	53.23	6.25	.45	------	------	------
					Dry	34.17	58.91	6.92	.50	------	------	------
1926	[15]B. M. 12	7/06	Franklin	6	14.91	26.66	49.50	8.93	.52	------	10958	------
					Dry	31.33	58.18	10.49	.61	------	12879	14545
2020	[15]B. M. 12	7/06	Franklin	6	10.72	29.86	50.06	9.36	.91	------	11686	------
					Dry	33.45	56.07	10.48	1.02	------	13088	14794
3447	[15]B. M. 12	7/06	Franklin	6	9.58	29.18	50.24	11.00	.52	------	11428	------
					Dry	32.27	55.56	12.17	.58	------	12632	14561

[14] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 83, 1913.
[15] Ibid., p. 84.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
3448	[15]B. M. 12	7/06	Franklin	6	9.45	29.49	51.99	9.07	.60	------	11695	------
					Dry	32.57	57.41	10.02	.66	------	12915	14503
3451	[15]B. M. 12	7/06	Franklin	6	8.30	30.23	50.90	10.57	.52	------	11543	------
					Dry	32.97	55.50	11.53	.57	------	12587	14394
5214	[15]B. M. 12	7/06	Franklin	6	11.82	27.66	55.10	5.42	.46	------	11961	------
					Dry	31.37	62.47	6.16	.52	------	13565	14547
5237	[15]B. M. 12	7/06	Franklin	6	11.50	26.70	52.67	9.13	.60	------	11410	------
					Dry	30.17	59.51	10.32	.68	------	12893	14531
23473	[16]B. M. 13	11/15	Franklin	6	9.28	34.21	47.76	8.75	1.10	------	11950	------
					Dry	37.71	52.64	9.65	1.21	------	13172	14745
23474	[16]B. M. 13	11/15	Franklin	6	8.91	35.51	47.46	8.12	.80	------	12083	------
					Dry	38.98	52.11	8.91	.88	------	13266	14707
23475	[16]B. M. 13	11/15	Franklin	6	8.82	33.91	48.87	8.40	.81	------	12038	------
					Dry	37.19	53.60	9.21	.89	------	13203	14691
23476	[16]B. M. 13	11/15	Franklin	6	9.25	33.76	48.08	8.91	1.07	------	11898	------
					Dry	37.20	52.98	9.82	1.18	------	13111	14706
23477	[16]B. M. 13	11/15	Franklin	6	8.75	33.71	48.44	9.10	1.55	------	11943	------
					Dry	36.94	53.09	9.97	1.70	------	13088	14725
23478	[16]B. M. 13	11/15	Franklin	6	9.01	34.52	47.87	8.60	1.08	------	11970	------
					Dry	37.94	52.61	9.45	1.19	------	13154	14675
22686	[16]B. M. 14	7/15	Franklin	6	9.33	33.60	48.48	8.59	.82	------	11824	------
					Dry	37.06	53.47	9.47	.90	------	13041	14556
22687	[16]B. M. 14	7/15	Franklin	6	9.05	33.74	48.65	8.56	.96	------	11858	------
					Dry	37.10	53.49	9.41	1.06	------	13039	14548
22688	[16]B. M. 14	7/15	Franklin	6	8.59	34.66	48.89	7.86	.92	------	12089	------
					Dry	37.92	53.48	8.60	1.01	------	13225	14612
22689	[16]B. M. 14	7/15	Franklin	6	8.91	33.87	49.21	8.01	.99	------	12017	------
					Dry	37.18	54.03	8.79	7.09	------	13192	14610
22690	[16]B. M. 14	7/15	Franklin	6	10.06	33.92	47.26	8.76	.92	------	11756	------
					Dry	37.72	52.54	9.74	1.02	------	13072	14775
22691	[16]B. M. 14	7/15	Franklin	6	9.19	33.80	48.61	8.40	.92	------	11925	------
					Dry	37.22	53.53	9.25	1.01	------	13131	14622
23442	[16]B. M. 15	11/15	Franklin	6	9.72	32.91	48.92	8.45	.87	------	11866	------
					Dry	36.45	54.19	9.36	.96	------	13144	14653
23443	[16]B. M. 15	11/15	Franklin	6	10.24	32.54	49.49	7.73	.80	------	11941	------
					Dry	36.25	55.14	8.61	.89	------	13304	14697
23444	[16]B. M. 15	11/15	Franklin	6	9.93	33.13	48.77	8.17	.75	------	11896	------
					Dry	36.78	54.15	9.07	.83	------	13207	14668
20080	[16]B. M. 16	11/14	Franklin	6	9.33	31.15	50.36	9.16	.56	------	11806	------
					Dry	34.36	55.54	10.10	.62	------	13021	14636
20081	[16]B. M. 16	11/14	Franklin	6	10.01	29.93	50.08	9.98	.52	------	11522	------
					Dry	33.26	55.65	11.09	.58	------	12803	14564
20082	[16]B. M. 16	11/14	Franklin	6	9.25	31.03	51.02	8.70	.48	------	11857	------
					Dry	34.19	56.22	9.59	.53	------	13064	14606

[16] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 123, p. 33, 1918.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
20083	[16]B. M. 16	11/14	Franklin	6	9.61	30.68	50.44	9.27	.50		11725	
					Dry	33.94	55.80	10.26	.55		12971	14604
20723	[16]B. M. 17	11/14	Franklin	6	8.21	32.46	49.00	10.33	.96		11770	
					Dry	35.36	53.39	11.25	1.05		12823	14632
20724	[16]B. M. 17	11/14	Franklin	6	9.07	32.24	48.42	10.27	1.14		11606	
					Dry	35.45	53.26	11.29	1.25		12764	14578
20725	[16]B. M. 17	11/14	Franklin	6	9.83	31.44	51.53	7.20	.50		11990	
					Dry	34.87	57.15	7.98	.55		13297	14568
20726	[16]B. M. 17	11/14	Franklin	6	8.87	32.72	49.05	9.36	.94		11785	
					Dry	35.90	53.83	10.27	1.03		12931	14915
22915	[16]B. M. 18	8/15	Franklin	6	9.78	32.29	49.73	8.20	1.02		11860	
					Dry	35.79	55.12	9.09	1.13		13145	14613
22916	[16]B. M. 18	8/15	Franklin	6	10.23	31.97	49.87	7.93	.91		11839	
					Dry	35.61	55.56	8.83	1.01		13189	14613
22917	[16]B. M. 18	8/15	Franklin	6	10.48	33.53	49.02	6.97	1.22		11932	
					Dry	37.46	54.75	7.79	1.36		13329	14598
22918	[16]B. M. 18	8/15	Franklin	6	8.86	33.27	49.48	8.39	.86		11970	
					Dry	36.50	54.29	9.21	.94		13133	14614
22919	[17]B. M. 19	8/15	Franklin	6	10.48	31.87	49.10	8.55	1.16		11678	
					Dry	35.60	54.85	9.55	1.30		13046	14590
22320	[17]B. M. 19	8/15	Franklin	6	10.16	32.66	49.63	7.56	.99		11921	
					Dry	36.35	55.23	8.42	1.10		13270	14634
22321	[17]B. M. 19	8/15	Franklin	6	9.99	32.82	49.27	7.92	1.03		11857	
					Dry	36.46	54.74	8.80	1.14		13172	14593
26129	[18]B. M. 58	10/16	Franklin	6	10.61	33.39	48.37	7.63	1.02		11855	
					Dry	37.35	54.11	8.54	1.14		13262	14646
30266	[18]B. M. 58	5/18	Franklin	6	7.86	34.10	49.62	8.42	1.18		12141	
					Dry	37.01	53.85	9.14	1.28		13176	14709
30267	[19]B. M. 58	4/18	Franklin	6	7.83	34.70	47.96	9.51	1.20		11963	
					Dry	37.65	52.03	10.32	1.30		12980	14651
30844	[19]B. M. 58	8/18	Franklin	6	8.02	35.66	48.46	7.86	1.07		12128	
					Dry	38.77	52.68	8.55	1.16		13187	14566
31050	[19]B. M. 58	10/18	Franklin	6	7.35	36.70	47.88	8.07	1.02		12164	
					Dry	39.61	51.68	8.71	1.10		13129	14526
29741	[19]B. M. 21	3/18	Franklin	6	9.73	34.19	48.99	7.09	1.08		11997	
					Dry	37.88	54.27	7.85	1.20		13289	14562
29742	[19]B. M. 21	3/18	Franklin	6	10.34	33.70	46.90	9.06	.54		11529	
					Dry	37.59	52.31	10.10	.60		12857	14449
29743	[19]B. M. 21	3/18	Franklin	6	9.28	34.17	48.77	7.78	.74		11885	
					Dry	37.67	53.75	8.58	.82		13100	14465
23744	[19]B. M. 21	3/18	Franklin	6	9.17	34.29	49.15	7.39	1.17		12163	
					Dry	37.75	54.11	8.14	1.29		13390	14723

[17] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 123, p. 34, 1918.
[18] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 193, p. 30, 1922.
[19] Ibid., p. 31.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
29745	[19]B. M. 21	3/18	Franklin	6	10.56	34.81	44.73	9.90	.45	------	11354	------
					Dry	38.92	50.01	11.07	.50	------	12695	14433
29746	[19]B. M. 21	3/18	Franklin	6	10.36	32.12	47.21	10.31	.56	------	11326	------
					Dry	35.83	52.67	11.50	.62	------	12634	14446
29754	[19]B. M. 21	3/18	Franklin	6	9.50	36.82	49.82	3.86	.79	------	12515	------
					Dry	40.69	55.04	4.27	.87	------	13829	14524
30205	[20]B. M. 20	5/18	Franklin	6	7.64	31.37	50.03	10.96	1.06	------	11687	------
					Dry	33.96	54.17	11.87	1.15	------	12654	14554
30207	[20]B. M. 20	4/18	Franklin	6	8.86	31.23	49.28	10.63	1.10	------	11603	------
					Dry	34.27	54.07	11.66	1.21	------	12731	14606
26492	[20]B. M. 22	12/16	Franklin	6	9.54	32.91	48.41	9.14	.98	------	11772	------
					Dry	36.38	53.52	10.10	1.08	------	13014	14644
26493	[20]B. M. 22	12/16	Franklin	6	9.58	33.25	50.16	7.01	1.08	------	12051	------
					Dry	36.77	55.48	7.75	1.19	------	13329	14585
26494	[20]B. M. 22	12/16	Franklin	6	10.97	33.70	46.86	8.47	.99	------	11671	------
					Dry	37.85	52.64	9.51	1.11	------	13109	14812
26495	[20]B. M. 22	12/16	Franklin	6	10.26	33.17	48.39	8.18	1.31	------	11858	------
					Dry	36.96	53.93	9.11	1.46	------	13214	14705
26496	[20]B. M. 22	12/16	Franklin	6	9.68	32.90	48.35	9.07	1.09	------	11693	------
					Dry	36.43	53.53	10.04	1.21	------	12946	14260
30206	[20]B. M. 22	4/18	Franklin	6	8.49	34.11	48.71	8.69	1.11	------	12064	------
					Dry	37.28	53.22	9.50	1.21	------	13183	14731
30208	[20]B. M. 22	11/16	Franklin	6	8.05	34.51	47.67	9.77	1.06	------	11927	------
					Dry	37.53	51.85	10.62	1.15	------	12971	14635
30485	[20]B. M. 22	11/16	Franklin	6	9.66	34.06	47.27	9.01	1.17	------	11866	------
					Dry	37.70	52.33	9.97	1.30	------	13135	14650
30486	[20]B. M. 22	11/16	Franklin	6	10.04	33.61	48.01	8.34	1.10	------	11898	------
					Dry	37.36	53.37	9.27	1.22	------	13226	14739
5528	----------	8/12	Gallatin	6	10.82	33.83	42.43	12.92	4.93	.42	11263	------
					Dry	37.94	47.57	14.49	5.53	.47	11609	15193
5510	223	8/12	Gallatin	6	4.47	33.33	47.73	11.46	3.59	.05	12320	------
					Dry	36.98	49.96	13.06	3.76	.05	12895	15157
5511	223	8/12	Gallatin	6	4.10	36.79	50.38	8.73	3.83	.04	12849	------
					Dry	38.36	52.54	9.10	3.99	.04	13397	15001
5513	223	8/12	Gallatin	6	12.55	34.81	46.34	6.30	5.61	.01	12015	------
					Dry	39.81	52.98	7.21	6.41	.01	13739	15129
23426	[21]B. M. 57	11/15	Gallatin	6	3.70	37.72	49.17	9.41	3.03	------	12987	------
					Dry	39.17	51.06	9.77	3.15	------	13487	15375
4773	55	4/12	Jackson	6	10.88	31.71	48.90	8.51	.65	.30	11594	------
					Dry	35.57	54.88	9.55	.73	.34	13009	14531
4780	55	4/12	Jackson	6	7.17	36.36	45.25	11.22	3.92	.43	11678	------
					Dry	39.18	48.74	12.08	4.22	.47	12581	14617

[20] Ibid., p. 32.
[21] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 123, p. 34, 1918.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
4784	55	4/12	Jackson	6	8.82	35.30	44.96	10.92	3.46	.50	11547	
					Dry	38.72	49.30	11.98	3.79	.54	12663	14676
12647	183	6/21	Jackson	6	10.34	35.71	45.74	8.21	1.03	.03	11585	
					Dry	39.82	51.02	9.16	1.15	.03	12920	14376
12648	183	6/21	Jackson	6	10.00	32.81	47.33	9.86	1.27	.07	11356	
					Dry	36.46	52.58	10.96	1.41	.08	12618	14357
12649	183	6/21	Jackson	6	9.16	34.31	46.76	9.77	1.24	.20	11523	
					Dry	37.77	53.00	10.33	1.36	.22	12684	14317
12650	183	6/21	Jackson	6	9.86	33.70	45.30	11.14	2.04	.27	11169	
					Dry	37.38	50.26	12.36	2.26	.30	12391	14377
12651	183	6/21	Jackson	6	9.46	35.05	46.85	8.64	1.75	.07	11586	
					Dry	38.71	51.75	9.54	1.93	.07	12796	14326
12652	183	6/21	Jackson	6	9.66	35.94	45.96	8.44	1.28	.22	11583	
					Dry	39.78	50.87	9.35	1.42	.24	12751	14307
2611	224	1/10	Livingston	6	16.50	32.63	45.50	5.37	1.60		11297	
					Dry	39.07	54.49	6.44	1.92		13529	14600
5086	66	7/12	Macoupin	6	4.29	39.09	37.21	9.41	4.13	.32	10635	
					Dry	45.60	43.42	10.98	4.82	.37	12408	14234
5087	66	7/12	Macoupin	6	13.77	38.69	36.74	10.80	4.37	.62	10493	
					Dry	44.86	42.62	12.52	5.07	.71	12169	14236
5088	66	7/12	Macoupin	6	14.73	38.33	37.24	9.70	4.50	.30	10522	
					Dry	44.95	43.69	11.36	5.28	.35	12339	14237
5097	69	7/12	Macoupin	6	14.73	36.26	36.11	12.90	4.62	.28	10099	
					Dry	42.53	42.34	15.13	5.42	.33	11843	14342
5098	69	7/12	Macoupin	6	13.68	38.02	37.72	10.58	4.43	.21	10618	
					Dry	44.05	43.70	12.25	5.12	.25	12300	14346
5099	69	7/12	Macoupin	6	14.19	37.92	37.03	10.86	4.21	.39	10599	
					Dry	44.19	43.15	12.66	4.91	.45	12351	14476
5100	67	7/12	Macoupin	6	15.12	38.28	36.55	10.05	3.85	.31	10610	
					Dry	45.09	43.06	11.85	4.54	.37	12501	14488
5101	67	7/12	Macoupin	6	14.90	37.75	38.43	8.92	3.67	.45	10735	
					Dry	44.35	45.16	10.49	4.31	.53	12614	14367
5102	67	7/12	Macoupin	6	14.67	35.49	38.83	11.01	4.15	.22	10433	
					Dry	41.59	45.50	12.91	4.86	.26	12227	14370
5112	68	7/12	Macoupin	6	12.11	40.32	39.14	8.43	4.39	.38	11170	
					Dry	45.88	44.52	9.60	5.00	.43	12705	14335
5113	68	7/12	Macoupin	6	13.27	38.58	38.15	10.00	4.89	.27	10730	
					Dry	44.48	43.99	11.53	5.64	.31	12442	14400
5114	68	7/12	Macoupin	6	13.23	38.85	38.91	9.01	4.39	.28	10935	
					Dry	44.77	44.84	10.39	5.06	.32	12601	14359
81323	185	9/21	Macoupin	6	13.32	37.97	39.84	8.87	3.40	.31	10893	
					Dry	43.80	45.97	10.23	3.92	.36	12567	14252
81324	185	9/21	Macoupin	6	12.41	37.96	39.98	9.65	3.57	.29	10889	
					Dry	43.34	45.64	11.02	4.08	.33	12432	14241
81325	185	9/21	Macoupin	6	9.84	42.13	39.51	8.52	3.51	.24	11426	
					Dry	46.73	43.82	9.45	3.89	.27	12673	14237

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
81327	186	9/21	Macoupin	6	11.18	37.54	40.19	11.09	3.65	1.00	10841	
					Dry	42.27	45.24	12.49	4.11	1.13	12206	14243
81328	186	9/21	Macoupin	6	9.01	38.20	41.42	10.37	4.32	.58	11193	
					Dry	43.08	45.52	11.40	4.75	.64	12301	14177
81329	186	9/21	Macoupin	6	13.17	36.72	40.09	10.02	4.04	.40	10685	
					Dry	42.29	46.17	11.54	4.65	.46	12306	14206
81331	228	9/21	Macoupin	6	14.03	37.17	39.60	9.20	3.49		10753	
					Dry	43.24	46.06	10.70	4.06		12508	14273
81332	187	9/21	Macoupin	6	13.30	37.46	38.68	10.56	4.23	.36	10621	
					Dry	43.21	44.61	12.18	4.88	.42	12250	14264
81333	187	9/21	Macoupin	6	13.52	36.25	38.70	11.53	4.38	.63	10471	
					Dry	41.92	44.75	13.33	5.06	.73	12108	14314
81334	187	9/21	Macoupin	6	13.86	36.52	39.11	10.51	3.97	.22	10554	
					Dry	42.40	45.40	12.20	4.61	.26	12252	14261
81085	188	8/21	Macoupin	6	12.30	38.69	41.07	7.94	3.62	.15	11080	
					Dry	44.12	46.83	9.05	4.13	.17	12634	14127
81086	188	8/21	Macoupin	6	11.39	39.03	40.49	9.09	4.57	.17	11037	
					Dry	44.05	45.69	10.26	5.16	.19	12456	14170
81087	188	8/21	Macoupin	6	12.24	38.25	41.24	8.27	3.61	.11	11066	
					Dry	43.58	47.00	9.42	4.11	.13	12609	14163
81016	189	8/21	Macoupin	6	12.74	36.09	42.77	8.40	3.73	.15	10948	
					Dry	41.36	49.01	9.63	4.27	.17	12546	14134
81017	189	8/21	Macoupin	6	15.67	33.57	41.53	9.23	3.56	.10	10379	
					Dry	39.81	49.24	10.95	4.22	.12	12308	14090
81018	189	8/21	Macoupin	6	13.40	35.71	41.83	9.06	4.06	.10	10711	
					Dry	41.24	48.30	10.46	4.69	.12	12368	14087
81020	190	8/21	Macoupin	6	13.92	34.44	43.00	8.64	3.79	.17	10814	
					Dry	40.01	49.95	10.04	4.40	.20	12563	14229
81021	190	8/21	Macoupin	6	13.26	34.81	42.29	9.64	3.90	.07	10773	
					Dry	40.13	48.76	11.11	4.50	.08	12420	14257
81022	190	8/21	Macoupin	6	15.16	33.46	41.97	9.41	3.21	.22	10540	
					Dry	39.44	49.47	11.09	3.78	.26	12423	14235
1625	[22]B. M. 30	5/05	Macoupin	6	13.29	37.07	40.74	8.90	4.12		11162	
					Dry	42.75	46.99	10.26	4.75		12872	14637
1626	[22]B. M. 30	5/05	Macoupin	6	15.27	36.19	39.34	9.20	3.70			
					Dry	42.71	46.43	10.86	4.37			
1635	[23]B. M. 30	5/05	Macoupin	6	13.54	35.69	40.03	10.74	4.03		10807	
					Dry	41.28	46.30	12.42	4.66		12499	14596
1639	[23]B. M. 30	5/05	Macoupin	6	13.72	36.24	39.72	10.32	3.96		10870	
					Dry	42.00	46.04	11.96	4.59		12598	14625
4247	[23]B. M. 30	5/05	Macoupin	6	15.25	28.57	40.83	15.35	3.81		9790	
					Dry	33.71	48.18	18.11	4.50		11551	14526
2731	[23]B. M. 30	5/05	Macoupin	6	14.68	31.32	40.32	13.68	3.88		10053	
					Dry	36.71	47.26	16.03	4.55		11782	14407

[22] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 85, 1913.
[23] Ibid., p. 86.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
18545	[24]B. M. 31	1/14	Macoupin	6	12.90	37.80	39.77	9.53	4.23	------	10852	------
					Dry	43.40	45.66	10.94	4.86	------	12460	14285
18546	[24]B. M. 31	1/14	Macoupin	6	14.16	35.53	40.21	10.10	3.70	------	10615	------
					Dry	41.39	46.84	11.77	4.31	------	12366	14306
18553	[24]B. M. 31	1/14	Macoupin	6	13.59	37.20	39.33	9.88	3.86	------	10701	------
					Dry	43.05	45.52	11.43	4.47	------	12384	14272
18910	[24]B. M. 31	1/14	Macoupin	6	13.38	36.88	37.50	13.24	5.05	------	10361	------
					Dry	42.09	42.80	15.11	5.76	------	11825	14329
5067	72	7/12	Madison	6	13.08	38.03	37.07	11.82	5.22	.25	10543	------
					Dry	43.75	42.65	13.60	6.01	.28	12129	14423
5068	72	7/12	Madison	6	13.53	37.26	40.98	8.23	3.81	.30	10903	------
					Dry	43.84	45.53	10.63	4.37	.23	12587	14363
5069	72	7/12	Madison	6	14.86	37.32	38.76	9.06	3.73	.20	10717	------
					Dry	43.84	45.53	10.63	4.37	.23	12587	14363
5070	71	7/12	Madison	6	12.99	37.73	36.89	12.39	4.43	.72	10499	------
					Dry	43.36	42.40	14.24	5.09	.82	12066	14440
5071	71	7/12	Madison	6	12.14	41.13	38.00	8.73	3.52	.41	11206	------
					Dry	46.82	43.24	9.94	4.00	.47	12759	14426
5072	71	7/12	Madison	6	12.42	39.82	37.65	10.11	4.35	.72	10909	------
					Dry	45.46	43.00	11.54	4.96	.80	12456	14398
5075	73	7/12	Madison	6	14.65	39.08	38.03	8.24	3.59	.29	10865	------
					Dry	45.80	44.55	9.65	4.20	.34	12730	14347
5076	73	7/12	Madison	6	14.31	38.35	38.32	9.02	3.77	.31	10739	------
					Dry	44.75	44.72	10.53	4.40	.37	12532	14283
5078	73	7/12	Madison	6	15.18	38.40	38.30	8.12	3.94	.23	10751	------
					Dry	45.27	45.16	9.57	4.64	.27	12673	14284
5515	70	8/12	Madison	6	13.88	37.60	37.74	10.78	4.21	.53	10551	------
					Dry	43.65	43.82	12.53	4.89	.61	12250	14330
5517	70	8/12	Madison	6	12.44	39.10	38.20	10.26	5.23	.64	10818	------
					Dry	44.65	43.64	11.71	6.03	.73	12354	14343
5518	70	8/12	Madison	6	12.11	39.32	36.27	12.30	4.92	.47	10615	------
					Dry	44.74	41.26	14.00	5.60	.53	12076	14421
80942	191	8/21	Madison	6	13.76	37.50	37.63	11.71	4.52	.45	10556	------
					Dry	43.18	43.34	13.48	5.20	.52	12156	14405
80943	191	8/21	Madison	6	13.76	39.10	37.39	9.75	2.89	.75	10805	------
					Dry	45.34	43.35	11.31	3.35	.87	12529	14382
80944	191	8/21	Madison	6	12.01	38.41	38.46	11.12	3.68	.33	10763	------
					Dry	43.65	43.71	12.64	4.18	.38	12232	14300
80862	192	8/21	Madison	6	11.71	37.44	40.57	10.28	4.32	.38	10936	------
					Dry	42.41	45.95	11.64	4.89	.43	12386	14327
80863	192	8/21	Madison	6	11.19	38.00	40.84	9.97	4.12	.47	11066	------
					Dry	42.79	45.98	11.23	4.64	.53	12460	14603
80864	192	8/21	Madison	6	12.02	35.62	41.79	10.57	3.69	.48	10888	------
					Dry	40.49	47.50	12.01	4.19	.55	12376	14604

[24] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 123, p. 34, 1918.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
1556	[25]B. M. 32	4/05	Madison	6	17.02	30.60	35.59	16.79	3.29	------	9319	------
					Dry	36.88	42.89	20.23	3.96	------	11230	14900
1608A	[25]B. M. 32	4/05	Madison	6	12.27	37.22	39.16	11.35	4.66	------	------	------
					Dry	42.43	44.63	12.94	5.31	------	------	------
1609	[25]B. M. 32	4/05	Madison	6	11.87	36.57	39.98	11.58	4.75	------	10768	------
					Dry	41.50	45.36	13.14	5.39	------	12218	14422
1611	[25]B. M. 32	4/05	Madison	6	11.46	34.98	36.25	17.31	4.40	------	10026	------
					Dry	39.51	40.94	19.55	4.97	------	11324	14541
1780	[25]B. M. 32	4/05	Madison	6	10.83	36.24	39.75	13.18	4.53	------	10816	------
					Dry	40.64	44.58	14.78	5.08	------	12130	14616
1722	[26]B. M. 33	4/05	Madison	6	10.69	33.08	36.14	20.09	4.06	------	9713	------
					Dry	37.04	40.47	22.49	4.55	------	10876	14560
2774	[26]B. M. 34	1/06	Madison	6	13.07	34.85	42.02	10.06	3.59	------	10949	------
					Dry	40.09	48.34	11.57	4.13	------	12596	14533
2775	[26]B. M. 34	1/06	Madison	6	12.79	35.67	40.25	11.29	3.94	------	------	------
					Dry	40.90	46.15	12.95	4.52	------	------	------
2819	[26]B. M. 34	1/06	Madison	6	13.47	34.35	40.65	11.53	4.41	------	10510	------
					Dry	39.70	46.98	13.32	5.10	------	12126	14331
2803	[26]B. M. 34	1/06	Madison	6	15.68	31.28	37.45	15.59	3.98	------	9655	------
					Dry	37.10	44.41	18.49	4.72	------	11450	14480
3911	[26]B. M. 35	10/06	Madison	6	14.25	35.52	40.79	9.44	3.72	------	10892	------
					Dry	41.42	47.57	11.01	4.34	------	12703	14564
3913	[26]B. M. 35	10/06	Madison	6	12.69	37.40	41.15	8.76	3.62	------	11236	------
					Dry	42.89	47.13	10.03	4.15	------	12868	14569
3963	[26]B. M. 35	10/06	Madison	6	13.10	30.78	40.12	16.00	4.17	------	9983	------
					Dry	35.42	46.17	18.41	4.80	------	11488	14517
3958	[26]B. M. 35	10/06	Madison	6	12.47	33.12	41.85	12.56	4.37	------	10667	------
					Dry	37.84	47.81	14.35	4.99	------	12186	14598
3980	[26]B. M. 35	10/06	Madison	6	12.25	33.76	41.66	12.33	4.42	------	10719	------
					Dry	38.47	47.48	14.05	5.04	------	12215	14578
2772	[26]B. M. 36	1/06	Madison	6	13.51	34.64	41.70	10.15	4.01	------	10881	------
					Dry	40.05	48.21	11.74	4.64	------	12580	14566
2773	[26]B. M. 36	1/06	Madison	6	13.83	34.16	42.24	9.77	4.10	------	------	------
					Dry	39.64	49.02	11.34	4.76	------	------	------
2905	[26]B. M. 36	1/06	Madison	6	11.91	35.65	39.43	13.01	5.34	------	10615	------
					Dry	40.47	44.76	14.77	6.06	------	12049	14551
2896	[26]B. M. 36	1/06	Madison	6	13.03	32.65	39.79	14.53	4.35	------	10192	------
					Dry	37.54	45.75	16.71	5.01	------	11718	14479
1341	[26]B. M. 38	9/04	Madison	6	15.09	31.00	46.49	7.42	.83	------	11151	------
					Dry	36.51	54.75	8.74	.98	------	13133	14533
1342	[27]B. M. 39	9/04	Madison	6	14.42	32.18	44.59	8.81	1.52	------	------	------
					Dry	37.60	52.11	10.29	1.78	------	------	------
1417	[27]B. M. 39	9/04	Madison	6	12.91	31.90	43.55	11.64	1.32	------	10804	------
					Dry	36.63	50.00	13.37	1.52	------	12406	14554

[25] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 86, 1918.
[26] Ibid., p. 87.
[27] Ibid., p. 88.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
2270	[28]B. M. 39	9/04	Madison	6	15.23	31.42	44.32	9.03	1.59	------	10901	------
					Dry	37.06	52.29	10.65	1.88	------	12859	14593
2271	[28]B. M. 39	9/04	Madison	6	17.79	28.78	42.34	11.09	1.40	------	------	------
					Dry	35.01	51.50	13.49	1.70	------	------	------
2852	[28]B. M. 39	9/04	Madison	6	15.54	31.26	42.27	10.93	1.38	------	10507	------
					Dry	37.01	50.05	12.94	1.63	------	12438	14432
2920	[28]B. M. 39	9/04	Madison	6	15.30	30.59	43.40	10.71	1.43	------	------	------
					Dry	36.12	51.24	12.64	1.69	------	------	------
10956	[29]B. M. 40	9/10	Madison	6	12.94	35.76	41.92	9.38	3.65	------	10973	------
					Dry	41.07	48.16	10.77	4.19	------	12604	14399
10957	[29]B. M. 40	9/10	Madison	6	12.31	37.57	41.09	9.03	3.58	------	11115	------
					Dry	42.84	46.86	10.30	4.08	------	12676	14395
10958	[29]B. M. 40	9/10	Madison	6	12.81	36.31	41.35	9.53	3.28	------	11023	------
					Dry	41.64	47.43	10.93	3.76	------	12641	14676
10959	[29]B. M. 40	9/10	Madison	6	12.70	36.36	41.47	9.47	3.67	------	10989	------
					Dry	41.65	47.50	10.85	4.20	------	12587	14396
5039	87	6/12	Marion	6	10.06	37.96	41.09	10.89	3.92	.59	11289	------
					Dry	42.21	45.69	12.10	4.35	.66	12555	14589
5041	87	6/12	Marion	6	10.35	36.04	42.81	10.80	4.10	.25	11227	------
					Dry	40.20	47.75	12.05	4.57	.28	12522	14551
5044	87	6/12	Marion	6	10.96	36.54	40.68	11.82	4.00	.43	11002	------
					Dry	41.04	45.69	13.27	4.52	.48	12364	14583
80737	206	8/21	Marion	6	9.11	36.82	41.83	12.24	4.53	.32	11119	------
					Dry	40.51	46.02	13.47	4.98	.35	12233	14487
80738	206	8/21	Marion	6	9.05	37.00	41.78	12.17	4.93	.15	11143	------
					Dry	40.68	45.94	13.38	5.42	.16	12252	14838
80739	206	8/21	Marion	6	9.19	36.99	41.94	11.88	3.39	.74	11243	------
					Dry	40.73	46.19	13.08	3.73	.81	12381	14621
80740	206	8/21	Marion	6	11.32	35.62	42.16	10.90	3.98	.10	11056	------
					Dry	40.17	47.54	12.29	4.49	.11	12467	14528
80741	206	8/21	Marion	6	11.36	35.35	42.99	10.30	4.03	.15	11137	------
					Dry	39.88	48.50	11.62	4.55	.17	12564	14521
80742	206	8/21	Marion	6	9.59	36.93	42.67	10.81	3.51	.44	11311	------
					Dry	40.85	47.19	11.96	3.88	.49	12511	14499
80695	207	8/21	Marion	6	9.87	35.92	44.41	9.80	3.65	.16	11494	------
					Dry	39.85	49.28	10.87	4.05	.18	12753	14587
80696	207	8/21	Marion	6	10.63	37.26	42.04	10.07	2.87	.39	11259	------
					Dry	41.69	47.04	11.27	3.21	.44	12598	14451
80697	207	8/21	Marion	6	10.74	36.97	40.48	11.81	3.31	.76	11048	------
					Dry	41.42	45.35	13.23	3.71	.85	12377	14571
1725	[30]B. M. 52	6/05	Marion	6	10.25	37.43	39.79	12.53	3.70	------	11077	------
					Dry	41.70	44.34	13.96	4.12	------	12343	14680

[28] Ibid.
[29] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 85, p. 36, 1914.
[30] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 88, 1913.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
1726	[30]B. M. 52	6/05	Marion	6	11.88	35.84	43.45	8.83	3.25	------	-------	------
					Dry	40.67	49.31	10.02	3.69	------	-------	------
1761	[30]B. M. 52	6/05	Marion	6	9.95	34.76	42.06	13.23	3.87	------	10960	------
					Dry	38.60	46.71	14.69	4.30	------	12172	14620
5105	76	7/12	Montgomery	6	14.15	36.96	38.19	10.70	3.43	.91	10547	------
					Dry	43.05	44.48	12.47	4.00	1.06	12285	14329
5106	76	7/12	Montgomery	6	13.83	36.95	39.22	10.00	3.72	.91	10728	------
					Dry	42.88	45.51	11.61	4.32	1.05	12455	14382
5107	76	7/12	Montgomery	6	13.70	37.25	37.93	11.12	4.39	1.04	10444	------
					Dry	43.17	43.94	12.89	5.08	1.20	12102	14225
5516	77	8/12	Montgomery	6	14.00	36.88	40.02	9.10	3.84	.48	10761	------
					Dry	42.88	46.54	10.58	4.47	.57	12511	14268
81101	194	8/21	Montgomery	6	12.84	37.08	40.56	9.52	3.58	.71	10894	------
					Dry	42.54	46.54	10.92	4.11	.81	12499	14302
81102	194	8/21	Montgomery	6	13.28	36.02	40.55	10.15	4.15	.64	10671	------
					Dry	41.54	46.76	11.70	4.79	.74	12305	14239
81103	194	8/21	Montgomery	6	13.46	35.80	41.36	9.38	4.48	.13	10774	------
					Dry	41.37	47.79	10.84	5.18	.16	12450	14269
81093	195	8/21	Montgomery	6	12.65	36.14	41.55	9.66	3.87	.50	10793	------
					Dry	41.37	47.57	11.06	4.43	.57	12356	14171
81094	195	8/21	Montgomery	6	11.66	37.25	41.31	9.78	3.69	.69	11053	------
					Dry	42.17	46.76	11.07	4.18	.78	12512	14345
81095	195	8/21	Montgomery	6	14.32	34.82	41.97	8.89	3.94	.16	10687	------
					Dry	40.64	48.98	10.38	4.60	.19	12473	14530
81089	196	8/21	Montgomery	6	11.38	37.05	40.98	10.59	4.26	.96	10832	------
					Dry	41.81	46.24	11.95	4.81	1.08	12223	14189
81090	196	8/21	Montgomery	6	12.53	36.21	40.35	10.91	4.61	.85	10705	------
					Dry	41.40	46.13	12.47	5.27	.97	12258	14341
81091	196	8/21	Montgomery	6	12.47	37.13	40.54	9.86	4.41	.40	10861	------
					Dry	42.42	46.32	11.26	5.04	.46	12408	14284
81097	197	8/21	Montgomery	6	14.97	34.87	41.80	8.36	3.41	.44	10697	------
					Dry	41.01	49.16	9.83	4.01	.52	12580	14200
81098	197	8/21	Montgomery	6	14.49	34.60	42.45	8.46	3.83	.36	10643	------
					Dry	40.46	49.65	9.89	4.48	.42	12446	14070
81099	197	8/21	Montgomery	6	14.69	34.56	41.14	9.61	4.32	.47	10425	------
					Dry	40.51	48.23	11.26	5.06	.55	12220	14069
1661	[31]B. M. 43	5/05	Montgomery	6	12.90	33.77	42.25	11.08	3.78	------	10856	------
					Dry	38.77	48.51	12.72	4.34	------	12463	14599
1449	[31]B. M. 43	5/05	Montgomery	6	14.89	34.80	42.44	7.87	3.61	------	11016	------
					Dry	40.89	49.86	9.25	4.24	------	12944	14521
1450	[31]B. M. 43	5/05	Montgomery	6	13.94	33.93	41.22	10.91	3.79	------	-------	------
					Dry	39.43	47.89	12.68	4.40	------	-------	------
1557	[31]B. M. 43	5/05	Montgomery	6	14.43	29.48	42.81	13.28	4.01	------	10064	------
					Dry	34.45	50.03	15.52	4.69	------	11761	14289

[31] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 89, 1913.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
1702	[31]B. M. 43	5/05	Montgomery	6	11.93	29.99	43.90	14.18	4.29	------	10303	------
					Dry	34.05	49.85	16.10	4.87	------	11698	14329
1627	[31]B. M. 43	5/05	Montgomery	6	13.20	34.33	39.94	12.53	4.47	------	10514	------
					Dry	39.55	46.01	14.44	5.15	------	12112	14529
11352	[32]B. M. 44	11/10	Montgomery	6	13.23	34.45	42.37	9.95	3.57	------	------	------
					Dry	39.70	48.83	11.47	4.11	------	------	------
11353	[32]B. M. 44	11/10	Montgomery	6	12.99	32.86	40.33	13.82	4.06	------	------	------
					Dry	37.77	46.35	15.88	4.67	------	------	------
11354	[32]B. M. 44	11/10	Montgomery	6	13.31	33.62	41.34	11.73	3.75	------	10548	------
					Dry	38.78	47.69	13.53	4.33	------	12168	14394
21901	[33]B. M. 45	4/15	Montgomery	6	14.87	33.42	40.70	11.01	3.26	------	10478	------
					Dry	39.26	47.81	12.93	3.83	------	12308	14419
21902	[33]B. M. 45	4/15	Montgomery	6	12.70	35.52	40.16	11.62	4.15	------	10669	------
					Dry	40.69	46.00	13.31	4.75	------	12220	14432
21903	[33]B. M. 45	4/15	Montgomery	6	13.04	34.06	39.58	13.32	4.84	------	10301	------
					Dry	39.17	45.51	15.32	5.57	------	11846	14388
21904	[33]B. M. 45	4/15	Montgomery	6	13.43	35.06	40.96	10.55	3.82	------	10732	------
					Dry	40.50	47.31	12.19	4.41	------	12398	14425
21905	[33]B. M. 45	4/15	Montgomery	6	13.31	34.86	40.42	11.41	4.02	------	10620	------
					Dry	40.21	46.63	13.16	4.64	------	12251	14438
21906	[33]B. M. 46	4/15	Montgomery	6	13.48	34.84	40.13	11.55	4.03	------	10548	------
					Dry	40.27	46.38	13.35	4.66	------	12191	14402
5254	225	8/12	Moultrie	6	7.07	39.02	43.01	10.90	3.69	.36	11912	------
					Dry	41.99	46.28	11.73	3.97	.39	12819	14736
5255	225	8/12	Moultrie	6	7.18	38.09	41.38	13.35	5.18	.46	11573	------
					Dry	41.03	44.59	14.38	5.58	.49	12468	14973
5256	225	8/12	Moultrie	6	6.24	40.34	42.55	10.87	3.18	.89	12149	------
					Dry	43.03	45.38	11.59	3.39	.95	12957	14937
4756	54	3/12	Perry	6	10.32	34.03	46.19	9.46	1.07	.24	11395	------
					Dry	37.94	51.51	10.55	1.18	.26	12705	14380
4759	54	3/12	Perry	6	10.41	33.43	45.82	10.34	.88	.23	11486	------
					Dry	37.32	51.14	11.54	.98	.25	12822	14367
4760	54	3/12	Perry	6	10.22	33.32	47.60	8.86	1.04	.23	11270	------
					Dry	37.11	53.03	9.86	1.15	.25	12553	14383
4764	54	3/12	Perry	6	9.98	33.71	44.91	11.40	.84	.33	11205	------
					Dry	37.45	49.88	12.67	.93	.37	12447	14452
4766	54	3/12	Perry	6	9.64	33.49	45.60	11.27	.82	.35	11230	------
					Dry	37.06	50.47	12.47	.90	.39	12428	14394
4768	54	3/12	Perry	6	10.05	33.24	45.85	10.86	.93	.63	11257	------
					Dry	36.94	50.98	12.08	1.04	.70	12513	14424
5034	90	6/12	Perry	6	10.60	37.03	42.32	10.05	3.73	.62	11175	------
					Dry	41.42	47.35	11.23	4.17	.70	12500	14365
5037	90	6/12	Perry	6	11.20	37.29	40.57	10.94	3.20	.34	10911	------
					Dry	42.00	45.69	12.31	3.60	.39	12287	14288

[32] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 85, p. 37, 1914.
[33] Fieldner, A. C., and others, Analyses of coal. U. S. Bureau of Mines, Bull. 123, p. 35, 1918.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5038	90	6/12	Perry	6	10.60	35.99	43.05	10.36	4.18	.47	11012	
					Dry	40.25	48.16	11.59	4.67	.53	12317	14228
5040	90	6/12	Perry	6	11.60	37.03	42.17	9.20	3.84	.38	11107	
					Dry	41.89	47.71	10.40	4.34	.43	12570	14301
5042	90	6/12	Perry	6	10.82	37.83	41.52	9.83	2.98	.76	11210	
					Dry	42.42	46.56	11.02	3.34	.85	12570	14380
5043	90	6/12	Perry	6	10.89	36.81	41.23	11.07	3.71	.55	10826	
					Dry	41.29	46.27	12.44	4.16	.52	12277	14319
5048	88	7/12	Perry	6	9.37	36.87	41.05	12.71	4.62	.43	10936	
					Dry	40.68	45.29	14.02	4.83	.47	12067	14395
5049	88	7/12	Perry	6	9.34	37.97	41.32	11.37	3.16	1.42	11099	
					Dry	41.88	45.58	12.54	3.48	1.56	12243	14276
5050	88	7/12	Perry	6	10.11	36.44	41.45	12.00	3.59	.75	10915	
					Dry	40.54	40.12	13.34	3.99	.81	12141	14321
5514	89	8/12	Perry	6	12.43	35.55	42.86	9.16	4.80	.21	11063	
					Dry	40.59	48.94	10.47	5.48	.25	12632	14422
5519	89	8/12	Perry	6	12.76	35.18	44.32	7.74	1.66	.15	11357	
					Dry	41.79	49.34	8.87	1.90	.17	13018	14458
5520	89	8/12	Perry	6	12.17	36.42	42.41	9.00	1.96	.46	11200	
					Dry	41.46	48.28	10.26	2.23	.52	12753	14414
12596	175	5/21	Perry	6	10.11	35.92	43.55	10.42	3.62	.56	11661	
					Dry	39.96	48.45	11.59	4.03	.62	12422	14332
12597	175	5/21	Perry	6	10.16	35.53	44.84	9.47	3.46	.11	11368	
					Dry	39.55	49.91	10.54	3.85	.12	12654	14405
12598	175	5/21	Perry	6	10.16	35.49	42.89	11.46	3.92	.42	11041	
					Dry	39.50	47.74	12.76	4.36	.47	12290	14402
12574	176	5/21	Perry	6	9.26	39.03	42.31	9.40	3.38	.30	11449	
					Dry	43.01	46.63	10.36	3.73	.33	12617	14328
12575	176	5/21	Perry	6	9.52	36.11	43.88	10.49	3.47	.35	11330	
					Dry	39.91	48.50	11.59	3.84	.39	12522	14218
12576	176	5/21	Perry	6	10.01	36.39	43.99	9.61	3.87	.84	11313	
					Dry	40.44	48.88	10.68	3.19	.84	12572	14314
12577	176	5/21	Perry	6	10.61	36.25	43.49	9.65	3.40	.50	11125	
					Dry	40.55	48.65	10.80	3.68	.56	12445	14205
12578	176	5/21	Perry	6	10.14	35.55	43.07	11.24	3.49	.40	10979	
					Dry	39.56	47.93	12.51	3.89	.45	12218	14257
12579	176	5/21	Perry	6	11.52	34.89	43.18	10.41	2.99	.51	10887	
					Dry	39.43	48.80	11.77	3.38	.58	12305	14205
12595	177	5/21	Perry	6	9.45	35.01	41.93	13.61	3.84	.86	10763	
					Dry	38.66	46.31	15.03	4.24	.95	11886	14334
12620	178	5/21	Perry	6	9.29	35.59	42.81	12.31	3.31	.32	11019	
					Dry	39.24	47.19	13.57	3.65	.34	12148	14358
12621	178	5/21	Perry	6	10.19	34.23	40.62	13.96	5.43	.37	10486	
					Dry	38.12	46.34	15.54	6.05	.40	11676	14359
12622	178	5/21	Perry	6	9.84	35.15	43.16	11.85	3.54	.28	10942	
					Dry	38.98	47.87	13.15	3.93	.30	12137	14275

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
12664	179	6/21	Perry	6	8.79	36.91	43.31	10.99	3.43	.19	11300	
					Dry	40.47	47.48	12.05	3.76	.21	12201	14368
12665	179	6/21	Perry	6	8.88	37.82	42.73	10.57	3.38	.06	11290	
					Dry	41.51	46.89	11.60	3.71	.06	12204	14287
12623	180	6/21	Perry	6	8.29	34.61	48.18	8.92	1.07	.25	11703	
					Dry	37.74	52.54	9.72	1.17	.27	12761	14292
12624	180	6/21	Perry	6	8.91	33.28	47.11	10.70	.95	.05	11355	
					Dry	36.53	51.72	11.75	1.04	.06	12466	14311
12614	180	5/21	Perry	6	10.00	32.79	48.99	8.22	.77	.12	11570	
					Dry	36.44	54.43	9.13	.86	.14	12855	14288
12615	180	5/21	Perry	6	9.89	33.47	47.05	9.59	1.35	.43	11424	
					Dry	37.14	52.22	10.64	1.50	.48	12678	14372
12616	180	5/21	Perry	6	9.49	34.09	46.22	10.20	1.21	.18	11432	
					Dry	37.67	51.06	11.27	1.33	.20	12632	14425
31033	181	10/18	Perry	6	12.34	33.48	45.02	9.16	1.82		11171	
					Dry	38.19	51.36	10.45	2.08		12744	14434
31034	181	10.18	Perry	6	12.19	34.16	44.50	9.15	1.32		11245	
					Dry	38.90	50.68	10.42	1.50		12805	14479
31035	181	10/18	Perry	6	11.93	33.50	45.35	9.22	1.36		11257	
					Dry	38.04	51.49	10.47	1.54		12782	14447
31036	181	10/18	Perry	6	11.86	34.13	44.63	9.38	1.46		11236	
					Dry	38.72	50.64	10.64	1.66		12748	14426
12592	182	5/21	Perry	6	9.06	36.59	43.13	11.22	3.73	.37	11126	
					Dry	40.24	47.43	12.33	4.10	.41	12235	14246
12593	182	5/21	Perry	6	9.00	35.80	44.03	11.17	3.86	.46	11097	
					Dry	39.34	48.39	12.27	4.24	.51	12195	14194
12594	182	5/21	Perry	6	9.21	35.02	44.58	11.19	3.55	.40	11194	
					Dry	38.57	49.10	12.33	3.91	.44	12327	14350
12588	184	5/21	Perry	6	8.13	38.22	42.61	11.04	3.73	.58	11296	
					Dry	41.60	46.38	12.02	4.06	.64	12296	14262
12589	184	5/21	Perry	6	7.56	37.65	43.56	11.23	3.71	.52	11336	
					Dry	40.73	47.12	12.15	4.01	.57	12263	14245
12590	184	5/21	Perry	6	8.28	39.19	41.95	10.58	3.49	.43	11406	
					Dry	42.73	45.74	11.53	3.81	.47	12436	14329
12591	184	5/21	Perry	6	8.00	37.60	42.27	12.13	3.38	.57	11124	
					Dry	40.87	45.95	13.18	3.67	.62	12091	14218
20728	[34]B. M. 29	10/15	Perry	6	10.88	32.97	47.20	8.95	1.15		11380	
					Dry	37.00	52.96	10.04	1.29		12769	14411
20729	[34]B. M. 29	10/15	Perry	6	10.20	33.08	49.63	7.09	.80		11749	
					Dry	36.84	55.26	7.90	.89		13082	14329
20730	[34]B. M. 29	10/15	Perry	6	11.47	32.05	48.44	8.04	.92		11446	
					Dry	36.20	54.72	9.08	1.04		12929	14368
20731	[34]B. M. 29	10/15	Perry	6	10.64	32.78	48.93	7.65	.68		11621	
					Dry	36.68	54.76	8.56	.76		13005	14352

[34] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 123, p. 35, 1918.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
20732	[34]B. M. 29	10/15	Perry	6	11.54	32.16	49.35	6.95	.85	------	11578	------
					Dry	36.36	55.78	7.86	.96	------	13088	14332
20733	[34]B. M. 29	10/15	Perry	6	10.99	32.24	48.32	8.45	.72	------	11446	------
					Dry	36.22	54.29	9.49	.81	------	12859	14340
20734	[34]B. M. 29	10/15	Perry	6	11.03	32.40	48.64	7.93	.86	------	11578	------
					Dry	36.41	54.68	8.91	.97	------	13010	14426
26462	[35]	12/16	Perry	6	10.45	33.92	47.88	7.75	.83	------	11729	------
					Dry	37.88	53.97	8.65	.93	------	13097	14476
26463	[35]	12/16	Perry	6	10.66	33.04	47.60	8.70	.82	------	11590	------
					Dry	36.98	53.28	9.74	.92	------	12973	14529
26464	[35]	12/11	Perry	6	10.61	33.04	46.72	9.63	1.02	------	11412	------
					Dry	36.96	52.27	10.77	1.14	------	12767	14485
26465	[35]	12/16	Perry	6	11.26	33.84	46.18	8.72	.80	------	11484	------
					Dry	38.13	52.04	9.83	.90	------	12942	14509
26466	[35]	12/16	Perry	6	11.75	33.49	45.94	8.82	.78	------	11392	------
					Dry	37.95	52.06	9.99	.88	------	12908	14497
26467	[35]	12/16	Perry	6	11.47	32.81	47.22	8.50	1.08	------	11484	------
					Dry	37.06	53.34	9.60	1.22	------	12973	14514
26469	[35]	12/16	Perry	6	13.73	33.99	49.58	2.70	.77	------	12064	------
					Dry	39.40	57.47	3.13	.89	------	13984	14542
5045	83	8/12	Randolph	6	11.38	36.94	40.25	11.43	4.16	.72	10823	------
					Dry	41.68	45.41	12.91	4.69	.81	12212	14348
5046	83	8/12	Randolph	6	10.62	38.10	39.12	12.16	4.45	.42	10849	------
					Dry	42.63	43.77	13.60	4.98	.47	12137	14400
5047	83	8/12	Randolph	6	11.39	36.80	41.04	10.77	4.11	.60	10895	------
					Dry	41.53	46.32	12.15	4.63	.67	12294	14306
12583	229	5/21	Randolph	6	8.46	37.00	44.26	10.28	3.69	.29	11333	------
					Dry	40.42	48.35	11.23	4.03	.32	12381	14219
12584	229	5/21	Randolph	6	8.71	37.46	42.94	10.89	4.45	.086	11155	------
					Dry	41.04	47.04	11.92	4.88	.094	12220	14181
12585	229	5/21	Randolph	6	8.00	38.05	43.63	10.32	3.69	.162	11338	------
					Dry	41.36	47.42	11.22	4.01	.176	12324	14149
12562	208	5/21	Randolph	6	9.54	36.55	43.35	10.56	3.21	.58	11251	------
					Dry	40.41	47.92	11.67	3.55	.64	12438	14349
12563	208	5/21	Randolph	6	9.52	37.01	40.86	12.61	4.90	.46	10971	------
					Dry	40.90	45.16	13.94	5.42	.51	12125	14463
12564	208	5/21	Randolph	6	9.69	37.31	41.70	11.30	4.15	.50	11135	------
					Dry	41.31	46.17	12.52	4.59	.55	12330	14412
12565	208	5/21	Randolph	6	11.07	36.15	41.17	11.61	2.90	.69	10902	------
					Dry	40.65	46.30	13.05	3.47	.78	12259	14373
12566	208	5/21	Randolph	6	10.58	35.65	39.85	13.92	3.20	.93	10526	------
					Dry	39.86	44.57	15.57	3.58	.98	11772	14273
12567	208	5/21	Randolph	6	10.65	36.25	40.89	12.21	4.32	.52	10885	------
					Dry	40.57	45.76	13.67	4.84	.58	12182	14458

[35] U. S. Bureau of Mines, unpublished analyses.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
12580	209	5/21	Randolph	6	10.35	37.35	41.41	10.69	3.73	.51	10991	
					Dry	41.75	46.30	11.95	4.17	.57	12287	14244
12581	209	5/21	Randolph	6	8.95	36.48	41.87	12.70	4.72	.66	10874	
					Dry	40.06	45.99	13.95	5.19	.73	11943	14233
12582	209	5/21	Randolph	6	9.44	36.89	42.42	11.25	4.31	.75	11016	
					Dry	40.73	46.84	12.43	4.76	.83	12165	14205
12570	210	5/21	Randolph	6	9.62	36.49	42.58	11.31	3.61	.21	11215	
					Dry	40.37	47.11	12.52	3.99	.23	12409	14485
12571	210	5/21	Randolph	6	9.03	37.38	43.63	9.96	3.42	.39	11456	
					Dry	41.09	47.96	10.95	3.76	.43	12593	14408
12572	210	5/21	Randolph	6	9.27	35.55	43.78	11.40	3.10	.29	11230	
					Dry	39.18	48.25	12.57	3.42	.32	12378	14439
12573	210	5/21	Randolph	6	9.42	35.40	41.85	13.33	3.91	.41	10858	
					Dry	39.08	46.20	14.72	4.32	.45	11987	14404
5115	75	8/12	Sangamon	6	14.97	36.90	38.36	9.77	3.53	.59	10598	
					Dry	43.39	45.12	11.49	4.16	.67	12466	14361
5116	75	8/12	Sangamon	6	14.51	37.60	39.69	8.20	3.44	.22	10911	
					Dry	43.98	46.43	9.59	4.02	.25	12763	14373
5117	75	8/12	Sangamon	6	12.98	38.23	38.92	9.87	4.32	.56	10845	
					Dry	43.94	44.72	11.34	4.96	.65	12463	14368
5130	74	7/12	Sangamon	6	15.22	38.23	37.36	9.19	4.38	.38	10579	
					Dry	45.09	44.07	10.84	5.17	.45	12478	14301
5131	74	7/12	Sangamon	6	13.10	38.86	37.25	10.79	5.08	.41	10592	
					Dry	44.72	42.86	12.42	5.86	.47	12187	14268
5132	74	7/12	Sangamon	6	14.43	38.14	37.07	10.36	4.77	.40	10495	
					Dry	44.58	43.32	12.10	5.58	.47	12265	14292
81319	193	9/21	Sangamon	6	13.16	36.32	39.36	11.16	4.98	.51	10553	
					Dry	41.82	45.33	12.85	5.73	.59	12152	14301
81320	193	9/21	Sangamon	6	13.25	36.73	40.75	9.27	3.53	.63	10884	
					Dry	42.34	46.97	10.69	4.07	.73	12546	14314
81321	193	9/21	Sangamon	6	12.95	36.40	40.52	10.13	3.52	.56	10817	
					Dry	41.82	46.54	11.64	4.04	.64	12427	14346
2897	[36]B. M. 42	2/06	Sangamon	6	14.29	37.17	40.36	8.18	4.41		11007	
					Dry	43.37	47.09	9.54	5.15		12841	14485
2898	[36]B. M. 42	2/06	Sangamon	6	14.18	34.85	41.11	9.86	4.36			
					Dry	40.61	47.90	11.49	5.08			
3052	[6]B. M. 42	2/06	Sangamon	6	16.00	32.41	37.82	13.77	4.05		9940	
					Dry	38.58	45.03	16.39	4.82		11833	14553
5056	79	7/12	St. Clair	6	10.69	40.16	37.87	11.28	4.55	.58	11063	
					Dry	44.97	42.39	12.64	5.10	.65	12387	14522
5058	79	7/12	St. Clair	6	12.12	38.61	40.61	8.66	3.10	.35	11217	
					Dry	43.93	46.22	9.85	3.52	.39	12764	14399
5059	79	7/12	St. Clair	6	11.12	40.54	38.27	10.07	4.18	.32	11145	
					Dry	45.61	43.06	11.33	4.70	.36	12540	14483

[36] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 91, 1913.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5055	78	7/12	St. Clair	6	13.06	38.21	37.36	11.37	3.21	1.17	10741	
					Dry	43.95	42.96	13.09	3.70	1.35	12354	14515
5060	78	7/12	St. Clair	6	11.44	38.73	38.11	11.72	4.26	.56	10841	
					Dry	43.73	43.04	13.23	4.81	.64	12242	14447
5061	78	7/12	St. Clair	6	10.75	39.19	38.88	11.18	3.41	.67	11041	
					Dry	43.91	43.56	12.53	3.82	.75	12371	14438
5077	81	7/12	St. Clair	6	11.35	39.68	38.59	10.38	4.05	.58	11036	
					Dry	44.75	43.54	11.71	4.57	.65	12449	14404
5079	81	7/12	St. Clair	6	10.85	40.75	38.36	10.04	4.09	.58	11192	
					Dry	45.71	43.03	11.26	4.58	.65	12554	14445
5080	81	7/12	St. Clair	6	11.50	40.68	37.91	9.91	3.96	.46	10908	
					Dry	45.96	42.84	11.20	4.47	.52	12597	14482
5108	82	7/12	St. Clair	6	10.99	38.96	58.79	11.26	4.36	.36	11047	
					Dry	43.77	43.59	12.64	4.90	.40	12411	14544
5109	82	7/12	St. Clair	6	13.42	39.23	36.92	10.43	4.92	.26	10753	
					Dry	45.31	42.65	12.04	5.69	.31	12419	14474
5110	82	7/12	St. Clair	6	11.40	40.96	36.89	10.75	4.10	.57	11052	
					Dry	46.23	41.63	12.14	4.63	.63	12472	14511
5524	80	7/12	St. Clair	6	10.11	39.72	38.87	11.30	3.69	.78	11051	
					Dry	44.19	43.24	12.57	4.10	.86	12294	14361
5525	80	8/12	St. Clair	6	9.83	39.84	37.97	12.36	4.02	.87	10958	
					Dry	44.19	42.11	13.70	4.45	.96	12152	14415
5526	80	8/12	St. Clair	6	10.19	38.44	40.41	10.96	3.95	.68	11127	
					Dry	42.79	45.00	12.21	4.49	.78	12388	14418
80827	200	8/21	St. Clair	6	14.93	30.71	42.72	11.64	2.22	.24	10340	
					Dry	36.10	50.22	13.68	2.61	.27	12155	14346
80828	200	8/21	St. Clair	6	12.71	31.53	45.31	10.45	1.65	.58	10809	
					Dry	36.12	51.91	11.97	1.89	.66	12383	14282
80829	200	8/21	St. Clair	6	13.68	32.10	42.59	11.63	1.51	1.25	10573	
					Dry	37.19	49.34	13.47	1.75	1.45	12249	14394
80823	201	8/21	St. Clair	6	11.64	37.40	41.80	9.16	3.66	.35	11177	
					Dry	42.33	47.30	10.37	4.14	.40	12649	14376
80824	201	8/21	St. Clair	6	11.26	37.92	39.03	11.79	3.66	.67	10931	
					Dry	42.73	43.98	13.29	4.12	.75	12318	14521
80825	201	8/21	St. Clair	6	12.08	37.02	41.58	9.32	3.77	.17	11153	
					Dry	42.10	47.30	10.60	4.29	.19	12685	14715
12536	202	5/21	St. Clair	6	11.45	37.39	38.66	12.50	5.21	.32	10739	
					Dry	42.22	43.66	14.12	5.88	.36	12128	14517
12537	202	5/21	St. Clair	6	10.65	35.54	40.93	12.88	4.21	.88	10782	
					Dry	39.77	45.81	14.42	4.71	.99	12067	14459
12538	202	5/21	St. Clair	6	11.17	39.20	39.20	10.43	4.44	.31	11073	
					Dry	44.13	44.13	11.74	5.00	.35	12465	14444
12541	203	5/21	St. Clair	6	9.72	39.13	40.02	11.13	4.87	.72	11228	
					Dry	43.34	44.33	12.33	5.39	.80	12437	14534
12542	203	5/21	St. Clair	6	9.26	40.97	39.09	10.68	4.36	.53	11308	
					Dry	45.15	43.08	11.77	4.80	.59	12462	14438

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
12543	203	5/21	St. Clair	6	11.17	39.71	37.52	11.60	4.63	.69	10826	------
					Dry	44.70	42.24	13.06	5.21	.78	12187	14362
12544	203	5/21	St. Clair	6	10.59	39.83	39.99	9.59	4.09	.32	11103	------
					Dry	44.54	44.73	10.73	4.57	.36	12419	14192
12545	203	5/21	St. Clair	6	11.33	39.64	39.04	9.99	3.59	.18	11153	------
					Dry	44.70	44.03	11.27	4.05	.20	12578	14458
12546	203	5/21	St. Clair	6	10.00	40.32	40.28	9.40	4.43	.55	11386	------
					Dry	44.80	44.76	10.44	4.92	.61	12651	14422
12559	204	5/21	St. Clair	6	11.52	37.20	41.67	9.61	2.82	.10	11155	------
					Dry	42.05	47.09	10.86	3.19	.10	12607	14394
12556	205	5/21	St. Clair	6	10.39	36.91	41.73	10.97	2.89	.74	11004	------
					Dry	41.19	46.57	12.24	3.23	.83	12280	14255
12557	205	5/21	St. Clair	6	9.26	37.77	41.08	11.89	3.01	.37	11170	------
					Dry	41.62	45.27	13.11	3.32	.41	12310	14438
12558	205	5/21	St. Clair	6	9.36	37.18	40.86	12.60	4.02	.55	10959	------
					Dry	41.02	45.08	13.90	4.44	.61	12091	14378
4250	[37]B. M. 49	11/06	St. Clair	6	13.17	34.79	41.75	10.29	3.22	------	------	------
					Dry	40.07	48.08	11.85	3.71	------	------	------
4251	[38]B. M. 49	11/06	St. Clair	6	14.38	33.92	42.95	8.75	3.13	------	10858	------
					Dry	39.62	50.16	10.22	3.66	------	12681	14373
4376	[38]B. M. 49	11/06	St. Clair	6	13.10	32.16	41.49	13.25	3.66	------	10383	------
					Dry	37.01	47.74	15.25	4.21	------	11959	14465
1095	[39]B. M. 50	9/04	St. Clair	6	11.17	39.31	39.20	10.32	4.22	------	11223	------
					Dry	44.25	44.13	11.62	4.75	------	12634	14610
1096	[39]B. M. 50	9/04	St. Clair	6	10.06	40.33	39.54	10.07	4.04	------	------	------
					Dry	44.84	43.96	11.20	4.49	------	------	------
1261	[39]B. M. 50	9/04	St. Clair	6	9.75	37.48	39.57	13.20	4.10	------	11025	------
					Dry	41.53	43.84	14.63	4.54	------	12217	14672
1152	[39]B. M. 50	9/04	St. Clair	6	12.03	31.86	33.67	22.44	4.00	------	9149	------
					Dry	36.22	38.27	25.51	4.55	------	10400	14541
3910	[39]B. M. 51	10/06	St. Clair	6	10.73	39.60	40.41	9.26	4.12	------	------	------
					Dry	44.36	45.27	10.37	4.62	------	------	------
3912	[39]B. M. 51	10/06	St. Clair	6	9.88	42.26	37.05	10.81	3.83	------	11439	------
					Dry	46.89	41.12	11.99	4.25	------	12694	14733
4364	[39]B. M. 51	10/06	St. Clair	6	11.69	35.70	39.42	13.19	4.38	------	10699	------
					Dry	40.43	44.63	14.94	4.96	------	12116	14624
4670	93	2/12	Vermilion	6	13.68	36.28	41.37	8.67	2.78	.45	11101	------
					Dry	42.03	47.92	10.05	3.23	.52	12861	14537
4671	93	2/12	Vermilion	6	15.50	33.32	43.11	8.07	1.86	.46	10976	------
					Dry	39.43	51.03	9.54	2.20	.62	12989	14558
4674	93	2/12	Vermilion	6	15.69	34.52	42.22	7.57	1.56	.53	11019	------
					Dry	40.95	50.07	8.98	1.85	.63	13085	14553

[37] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 89, 1913.
[38] Ibid., p. 90.
[39] Ibid., p. 89.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
4676	93	2/12	Vermilion	6	14.56	35.04	41.82	8.58	2.09	.74	11006	
					Dry	41.01	48.95	10.04	2.45	.86	12881	14527
4678	93	2/12	Vermilion	6	16.06	34.67	40.75	8.52	1.79	.90	10810	
					Dry	41.32	48.53	10.15	2.14	1.07	12879	14537
4679	93	2/12	Vermilion	6	15.95	34.66	42.06	7.33	1.41	.39	11041	
					Dry	41.23	50.05	8.72	1.68	.46	13136	14557
4702	92	3/12	Vermilion	6	15.53	33.60	39.46	11.41	2.32	.98	10404	
					Dry	39.78	46.70	13.52	2.75	1.15	12317	14520
4703	92	3/12	Vermilion	6	15.70	32.38	39.80	11.36	2.57	1.06	10392	
					Dry	38.81	47.72	13.47	3.04	1.26	12328	14535
4704	92	3/12	Vermilion	6	15.27	33.98	40.88	9.87	2.26	.69	10718	
					Dry	40.10	48.24	11.66	2.66	.81	12649	14563
4706	95	3/12	Vermilion	6	11.87	40.37	39.52	8.24	3.07	.74	11416	
					Dry	45.80	44.86	9.34	3.48	.84	12953	14525
4707	95	3/12	Vermilion	6	13.14	38.81	38.11	9.94	4.18	.88	10949	
					Dry	44.69	43.87	11.44	4.82	1.02	12604	14549
4740	91	6/12	Vermilion	6	13.58	35.20	39.83	11.39	3.19	.83	10821	
					Dry	40.73	46.09	13.18	3.69	.96	12521	14733
4741	91	6/12	Vermilion	6	13.63	34.56	41.19	10.62	2.91	.78	10954	
					Dry	40.01	47.69	12.30	3.36	.90	12683	14747
4742	91	6/12	Vermilion	6	14.50	35.98	40.49	9.03	2.43	.44	11090	
					Dry	42.09	47.35	10.56	2.83	.52	12971	14740
4743	91	6/12	Vermilion	6	14.20	35.79	42.05	7.96	1.83	.34	11295	
					Dry	41.71	49.01	9.28	2.13	.39	13165	14703
4744	91	6/12	Vermilion	6	13.99	35.26	42.68	8.07	1.67	.68	11271	
					Dry	40.99	49.63	9.38	1.94	1.14	13104	14706
4745	91	6/12	Vermilion	6	14.79	34.44	42.69	8.08	1.72	.98	11053	
					Dry	40.42	50.10	9.48	2.02	1.15	12971	14519
4746	91	6/12	Vermilion	6	15.14	33.70	40.19	10.97	2.50	.61	10663	
					Dry	39.72	47.34	12.94	2.95	.72	12565	14712
84222	212	2/22	Vermilion	6	13.6	34.0	42.6	9.8	2.4	.83	11020	
					Dry	39.3	49.5	11.2	2.8	.96	12750	14601
84223	212	2/22	Vermilion	6	13.8	35.2	41.3	9.7	2.7	.69	11010	
					Dry	40.8	48.0	11.2	3.1	.80	12760	14620
84224	212	2/22	Vermilion	6	15.3	32.8	44.1	7.8	1.8	.80	11100	
					Dry	38.7	52.1	9.2	2.1	.94	13110	14627
14682	[40]B. M. 53	/10	Vermilion	6	16.16	34.09	39.19	10.56	1.74		10433	
					Dry	40.66	46.75	12.59	2.08		12443	14472
25413	[41]B. M. 54	6/16	Vermilion	6	15.62	35.59	39.97	8.82	1.68		10845	
					Dry	42.18	47.37	10.45	1.99		12852	14554
5030	86	6/12	Washington	6	12.45	37.22	39.81	11.52	3.62	.67	10874	
					Dry	42.03	44.96	13.01	4.09	.76	12281	14426
5033	86	6/12	Washington	6	10.24	39.06	39.79	10.91	4.18	.30	11180	
					Dry	43.51	44.33	12.16	4.65	.34	12456	14499

[40] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 85, p. 37, 1914.
[41] Fieldner, A. C., and others, Analyses of coal: U. S. Bureau of Mines Bull. 123, p. 35, 1918.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5035	86	6/12	Washington	6	10.69 Dry	38.76 43.41	39.01 43.66	11.54 12.93	3.98 4.47	.51 .57	10963 12275	14418
80680	226	8/21	Washington	6	9.58 Dry	38.50 42.58	39.87 44.09	12.05 13.33	4.63 5.12	.49 .54	10906 12061	14260
80681	226	8/21	Washington	6	9.41 Dry	39.02 43.07	40.33 44.52	11.24 12.41	3.59 3.96	.41 .45	11172 12333	14374
80682	226	8/21	Washington	6	9.29 Dry	38.45 42.39	38.94 42.93	13.32 14.68	4.70 5.18	.66 .73	10796 11902	14321
80594	228	7/21	White	6	8.20 Dry	34.68 37.78	48.79 53.15	8.33 9.07	2.93 3.19	.73 .80	12079 13158	14700
80595	228	7/21	White	6	7.66 Dry	36.01 39.08	45.62 49.51	10.51 11.41	2.75 2.98	.96 1.04	11701 12699	14586
80596	228	7/21	White	6	9.22 Dry	35.05 38.61	47.88 52.74	7.85 8.65	2.89 3.18	.23 .25	11991 13209	14677
4998	65	6/12	Williamson	6	9.35 Dry	32.83 36.21	50.07 55.24	7.75 8.55	1.05 1.16	.26 .29	12017 13256	14644
5004	65	6/12	Williamson	6	9.99 Dry	33.79 37.53	48.56 53.96	7.66 8.51	.99 1.10	.06 .06	11899 13218	14593
5005	65	6/12	Williamson	6	8.58 Dry	33.95 37.14	48.31 52.84	9.16 10.02	3.10 3.39	.14 .16	11845 12956	14644
4996	60	6/12	Williamson	6	8.32 Dry	34.61 37.75	47.56 51.88	9.51 10.37	2.25 2.46	.24 .26	11978 13066	14801
5000	60	6/12	Williamson	6	7.53 Dry	34.90 37.74	47.37 51.23	10.20 11.03	3.23 3.49	.60 .65	11799 12760	14607
5006	60	6/12	Williamson	6	8.81 Dry	32.13 35.62	51.85 56.38	7.21 8.00	1.00 1.11	.13 .16	11962 13264	14572
5121	61	6/12	Williamson	6	9.44 Dry	33.63 37.13	49.58 54.75	7.35 8.12	1.28 1.42	.19 .21	12092 13354	14685
5133	61	7/12	Williamson	6	8.99 Dry	34.22 37.62	49.51 54.39	7.28 7.99	1.70 1.87	.04 .04	12149 13349	14674
5134	61	7/12	Williamson	6	9.38 Dry	33.62 37.10	50.01 55.18	6.99 7.72	1.12 1.24	.14 .16	12138 13394	14654
5122	59	7/12	Williamson	6	9.79 Dry	33.28 36.89	48.66 53.94	8.27 9.17	1.32 1.46	.44 .49	11891 13181	14681
5123	59	7/12	Williamson	6	10.67 Dry	32.54 36.42	47.32 52.97	9.47 10.61	1.53 1.71	.15 .17	11619 13006	14748
5124	59	7/12	Williamson	6	10.96 Dry	33.14 37.24	45.86 51.49	10.04 11.27	1.72 1.93	.55 .62	11383 12784	14624
5125	62	7/12	Williamson	6	9.97 Dry	32.20 35.76	49.62 55.12	8.21 9.12	1.47 1.63	.22 .25	11814 13123	14610
5126	62	7/12	Williamson	6	8.37 Dry	34.19 37.31	50.18 54.77	7.26 7.92	1.03 1.12	.18 .20	12254 13374	14663
5127	62	7/12	Williamson	6	9.06 Dry	32.93 36.20	49.98 54.97	8.03 8.83	1.03 1.13	.24 .27	12010 13207	14637
5170	64	7/12	Williamson	6	11.51 Dry	30.75 34.76	49.74 56.20	8.00 9.04	.84 .90	.32 .36	11554 13057	14501

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
5169	64	7/12	Williamson	6	9.13	32.03	51.06	7.77	1.10	.33	12044	------
					Dry	35.25	56.20	8.55	1.21	.36	13254	14613
5172	64	7/12	Williamson	6	7.38	35.59	47.56	9.47	.86	.51	12017	------
					Dry	38.42	51.35	10.23	.93	.55	12974	14617
5180	63	7/12	Williamson	6	10.38	32.76	48.10	8.76	1.50	.16	11735	------
					Dry	36.56	53.67	9.77	1.67	.18	13072	14672
5181	63	7/12	Williamson	6	8.78	34.25	47.56	9.41	2.49	.53	11885	------
					Dry	37.54	52.14	10.32	2.73	.58	13029	14758
5182	63	7/12	Williamson	6	9.26	33.36	48.70	8.68	1.83	.39	11955	------
					Dry	36.76	53.68	9.56	2.01	.43	13176	14761
80603	148	7/21	Williamson	6	8.00	33.66	50.86	7.48	1.08	.13	12266	------
					Dry	36.59	55.28	8.13	1.17	.14	13333	14655
80602	148	7/21	Williamson	6	8.14	32.87	49.99	9.00	1.43	.14	12015	------
					Dry	35.78	54.42	9.80	1.56	.16	13080	14681
80604	148	7/21	Williamson	6	7.85	33.92	49.60	8.63	1.14	.18	12107	------
					Dry	36.81	53.83	9.36	1.24	.20	13138	14656
80611	149	7/21	Williamson	6	5.62	36.04	44.78	13.56	4.21	.69	11621	------
					Dry	38.19	47.44	14.37	4.46	81	12313	14738
80610	149	7/21	Williamson	6	5.65	36.49	47.69	10.17	3.54	.55	12100	------
					Dry	38.68	50.54	10.78	3.75	.62	12825	14644
80612	149	7/21	Williamson	6	7.66	32.76	51.12	8.46	1.51	.05	12074	------
					Dry	35.48	55.36	9.16	1.64	.06	13076	14621
12793	150	6/21	Williamson	6	6.14	34.47	48.04	11.35	3.57	.25	11722	------
					Dry	36.73	51.18	12.09	3.80	.27	12489	14494
12794	150	6/21	Williamson	6	5.96	35.07	47.56	11.41	4.37	.07	11791	------
					Dry	37.29	50.57	12.14	4.65	.07	12538	14561
12795	150	6/21	Williamson	6	5.85	35.46	47.48	11.11	4.06	.46	11845	------
					Dry	37.66	50.43	11.81	4.31	.48	12581	14568
80615	151	7/21	Williamson	6	7.15	37.17	46.55	9.13	3.03	.11	12028	------
					Dry	40.03	50.14	9.83	3.26	.12	12954	14603
80614	151	7/21	Williamson	6	6.33	36.22	46.84	10.61	3.29	.04	11900	------
					Dry	38.67	50.00	11.33	3.51	.05	12704	14597
80616	151	7/21	Williamson	6	7.25	35.84	47.88	9.03	2.04	.16	12118	------
					Dry	38.64	51.62	9.74	2.20	.17	13065	14675
12769	152	6/21	Williamson	6	6.76	31.08	52.76	9.40	1.16	.13	12128	------
					Dry	33.33	56.59	10.08	1.24	.14	13007	14639
12770	152	6/21	Williamson	6	7.19	32.65	50.12	10.04	1.36	.75	11928	------
					Dry	35.18	54.00	10.82	1.47	.81	12778	14603
12771	152	6/21	Williamson	6	7.14	33.07	52.02	7.77	1.44	.05	12297	------
					Dry	35.61	56.02	8.37	1.55	.05	13242	14610
30372	153	10/18	Williamson	6	9.13	32.21	47.97	10.69	.80	------	11500	------
					Dry	35.45	52.79	11.76	.88	------	12656	14543
30873	153	10/18	Williamson	6	8.84	32.52	49.81	8.83	1.09	------	11873	------
					Dry	35.67	54.64	9.69	1.20	------	13023	14584
30874	153	9/18	Williamson	6	9.75	33.36	51.37	5.52	.88	------	12280	------
					Dry	36.96	56.92	6.12	.98	------	13606	14601

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
30875	153	10/18	Williamson	6	10.82	31.11	49.02	9.05	.88	------	11646	------
					Dry	34.88	54.97	10.15	.99	------	13059	14700
12799	154	6/21	Williamson	6	7.75	31.88	51.20	9.17	1.45	.18	11987	------
					Dry	34.56	55.50	9.94	1.57	.20	12994	14611
12800	154	6/21	Williamson	6	8.53	32.12	52.30	7.05	1.13	.17	12253	------
					Dry	35.11	57.18	7.71	1.23	.19	13396	14654
12801	154	6/21	Williamson	6	7.42	32.85	50.39	9.34	1.01	.18	12084	------
					Dry	35.48	54.43	10.09	1.09	.20	12997	14687
12752	155	6/21	Williamson	6	7.83	32.54	51.91	7.72	1.35	.14	12092	------
					Dry	35.30	56.32	8.38	1.47	.16	13045	14471
12753	155	6/21	Williamson	6	7.51	34.23	50.61	7.65	1.28	.15	12179	------
					Dry	37.01	54.72	8.27	1.38	.17	13099	14504
12754	155	6/21	Williamson	6	9.29	31.49	50.75	8.47	.93	.15	11781	------
					Dry	34.72	55.94	9.34	1.03	.16	12987	14480
12822	156	6/21	Williamson	6	8.38	31.25	53.08	7.29	1.12	.05	12067	------
					Dry	39.11	57.93	7.96	1.22	.05	13171	14449
12823	156	6/21	Williamson	6	9.18	31.10	52.33	7.39	1.32	.16	11956	------
					Dry	34.25	57.61	8.14	1.45	.18	13164	14468
12824	156	6/21	Williamson	6	8.71	31.98	52.07	7.24	.94	.12	12062	------
					Dry	35.03	57.04	7.93	1.03	.14	13213	14483
12841	156	6/21	Williamson	6	7.42	37.81	53.51	7.26	1.22	.07	12250	------
					Dry	34.36	57.80	7.84	1.32	.07	13166	14500
12842	156	6/21	Williamson	6	7.53	32.41	53.95	6.11	2.41	.22	12416	------
					Dry	35.05	58.34	6.61	2.61	.24	13297	14543
80598	157	7/21	Williamson	6	7.19	35.82	47.55	9.44	2.90	.26	12074	------
					Dry	38.59	51.24	10.17	3.12	.28	13009	14722
80599	157	7/21	Williamson	6	8.17	35.03	46.87	9.93	3.08	.29	11893	------
					Dry	38.15	51.04	10.81	3.35	.30	12951	14782
80600	157	7/21	Williamson	6	9.25	32.70	50.57	7.48	1.52	.17	12056	------
					Dry	36.03	55.73	8.24	1.67	.19	13285	14650
12819	158	6/21	Williamson	6	7.47	32.15	51.38	9.00	2.37	.32	11885	------
					Dry	34.75	55.52	9.73	2.56	.35	12845	14551
12820	158	6/21	Williamson	6	8.24	30.97	51.39	9.40	2.75	.00	11776	------
					Dry	33.75	56.10	10.25	3.00	.00	12683	14531
12821	158	6/21	Williamson	6	9.91	30.11	52.87	7.11	1.55	.02	11923	------
					Dry	33.42	58.69	7.89	1.72	.02	13148	14523
12796	159	6/21	Williamson	6	7.79	32.17	52.09	7.95	1.72	.06	12157	------
					Dry	34.89	56.49	8.62	1.87	.06	13184	14599
12797	159	6/21	Williamson	6	6.89	37.72	48.39	11.00	3.99	.25	11768	------
					Dry	36.22	51.96	11.81	4.29	.27	12424	14635
12798	159	6/21	Williamson	6	8.10	30.89	50.72	10.29	3.62	.09	11717	------
					Dry	33.61	55.19	11.20	3.94	.09	12553	14642
12868	160	7/21	Williamson	6	8.81	31.54	50.60	9.05	1.46	.06	11783	------
					Dry	34.59	55.49	9.92	1.60	.06	12841	14524
12869	160	7/21	Williamson	6	8.52	31.66	52.11	7.71	1.17	.09	12094	------
					Dry	34.61	56.96	8.43	1.29	.09	13155	14586

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
12870	160	7/21	Williamson	6	6.88	34.57	49.39	9.16	3.79	.02	12022	------
					Dry	37.12	53.04	9.84	4.07	.02	12706	14582
28810	161	7/17	Williamson	6	8.31	32.40	50.75	8.54	1.33	------	11965	------
					Dry	35.34	55.35	9.31	1.45	------	13048	14553
28811	161	8/17	Williamson	6	9.13	31.48	51.00	8.39	.97	------	11822	------
					Dry	34.64	56.13	9.23	1.07	------	13010	14485
28812	161	7/17	Williamson	6	8.82	35.15	47.90	8.13	1.07	------	11965	------
					Dry	38.55	52.53	8.92	1.17	------	13122	14557
28813	161	7/17	Williamson	6	9.31	32.93	49.63	8.13	.82	------	11902	------
					Dry	36.31	54.73	8.96	.90	------	13124	14559
28814	161	7/17	Williamson	6	9.78	33.08	49.93	7.21	.75	------	11965	------
					Dry	36.67	55.34	7.99	.83	------	13262	14541
30863	162	9/18	Williamson	6	9.72	32.84	50.65	6.79	.96	------	12026	------
					Dry	36.38	56.10	7.52	1.06	------	13322	14533
30864	162	9/18	Williamson	6	9.40	34.38	47.35	8.87	1.28	------	11801	------
					Dry	37.95	52.26	9.79	1.41	------	13027	14614
30865	162	9/18	Williamson	6	10.58	32.47	46.30	10.65	1.57	------	11322	------
					Dry	36.31	51.78	11.91	1.76	------	12661	14590
13540	163	3/22	Williamson	6	6.63	36.47	47.40	9.49	3.06	------	12133	------
					Dry	39.06	50.77	10.17	3.30	------	12995	14713
13543	163	3/22	Williamson	6	7.59	33.61	49.25	9.55	2.72	------	11974	------
					Dry	36.37	53.29	10.34	2.94	------	12958	14687
13544	163	3/22	Williamson	6	6.01	35.21	47.68	11.10	3.54	------	11867	------
					Dry	37.46	50.73	11.81	3.77	------	12526	14484
13542	163	3/22	Williamson	6	7.11	34.56	46.85	11.48	2.89	------	11668	------
					Dry	37.20	50.44	12.35	3.11	------	12561	14603
13539	163	3/22	Williamson	6	6.49	35.49	46.95	11.07	3.49	------	11821	------
					Dry	37.95	50.21	11.84	3.73	------	12641	14621
13541	163	3/22	Williamson	6	5.93	34.60	47.58	11.89	3.27	------	11788	------
					Dry	36.78	50.58	12.64	3.48	------	12532	14637
13538	164	3/22	Williamson	6	7.31	34.18	46.48	12.02	3.07	------	11635	------
					Dry	36.88	50.15	12.97	3.31	------	12553	14726
80653	165	8/21	Williamson	6	6.51	34.93	46.12	12.44	4.21	1.01	11697	------
					Dry	37.36	49.33	13.31	4.50	1.08	12511	14773
80652	165	8/21	Williamson	6	8.79	32.97	48.73	9.51	1.61	.60	11819	------
					Dry	36.15	53.42	10.43	1.77	.66	12958	14663
80651	165	8/21	Williamson	6	8.82	31.24	52.45	7.49	.92	.49	12047	------
					Dry	34.26	57.53	8.21	1.01	.54	13212	14530
12838	166	6/21	Williamson	6	7.85	32.46	49.17	10.52	3.03	.82	11675	------
					Dry	35.23	53.36	11.41	3.28	.88	12508	14564
12839	166	6/21	Williamson	6	8.08	32.30	50.78	8.84	2.00	.21	11867	------
					Dry	35.14	55.24	9.62	2.18	.23	12801	14479
12840	166	6/21	Williamson	6	6.47	33.63	48.02	11.88	3.57	.64	11659	------
					Dry	35.96	51.34	12.70	3.71	.69	12279	14578
12875	167	7/21	Williamson	6	8.10	31.22	53.02	7.66	1.15	.13	12156	------
					Dry	33.97	57.69	8.34	1.25	.14	13164	14595

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
12876	167	7/21	Williamson	6	8.79	32.42	48.41	10.38	1.59	.48	11573	
					Dry	35.54	53.08	11.38	1.74	.53	12688	14524
12877	167	7/21	Williamson	6	6.47	34.62	49.61	9.30	2.92	.20	12046	
					Dry	37.01	53.05	9.94	3.12	.22	12723	14533
12881	168	7/21	Williamson	6	5.00	37.42	46.61	10.97	3.13	.28	12108	
					Dry	39.39	49.06	11.55	3.29	.30	12580	14676
12882	168	7/21	Williamson	6	4.94	36.99	46.71	11.36	3.39	.44	12106	
					Dry	38.91	49.14	11.95	3.57	.46	12557	14750
12883	168	7/21	Williamson	6	5.73	35.37	44.97	13.93	4.17	.36	11514	
					Dry	37.52	47.71	14.77	4.42	.38	12215	14695
12772	169	6/21	Williamson	6	5.48	36.28	47.15	11.09	3.78	.61	11879	
					Dry	38.38	49.89	11.73	4.00	.65	12568	14545
12773	169	6/21	Williamson	6	5.88	35.63	46.19	12.30	3.77	.45	11631	
					Dry	37.86	49.07	13.07	4.01	.47	12158	14529
12774	169	6/21	Williamson	6	6.95	34.41	48.47	10.17	4.02	.03	11848	
					Dry	36.98	52.09	10.93	4.32	.03	12517	14585
80625	170	7/21	Williamson	6	6.40	36.71	47.70	9.19	3.41	.04	12150	
					Dry	39.22	50.96	9.82	3.64	.04	12981	14644
80626	171	7/21	Williamson	6	7.29	34.93	47.65	10.13	3.78	.04	11745	
					Dry	37.68	51.39	10.93	4.08	.04	12669	14334
80670	172	8/21	Williamson	6	6.40	36.38	48.20	9.02	3.45	.04	12179	
					Dry	38.87	51.49	9.64	3.69	.04	13012	14648
80673	173	8/21	Williamson	6	7.14	35.39	44.61	12.86	4.35	.63	11481	
					Dry	38.11	48.04	13.85	4.68	.68	12364	14708
80671	173	8/21	Williamson	6	6.24	36.41	44.45	12.90	3.56	.90	11672	
					Dry	38.83	47.41	13.76	3.80	.96	12449	14761
80672	173	8/21	Williamson	6	7.49	36.37	46.95	9.19	2.73	.04	12080	
					Dry	39.31	50.76	9.93	2.95	.04	13058	14894
10632	[42]174		Williamson	6	6.40	33.26	50.68	9.66	2.29		12109	
					Dry	35.53	54.15	10.32	2.45		12936	14642
10658	[42]174	2/19	Williamson	6	7.47	33.79	49.41	9.33	1.77		11970	
					Dry	36.52	53.39	10.09	1.92		12933	14578
13537	227	3/22	Williamson	6	9.09	31.33	52.10	8.42	1.09		11999	
					Dry	34.15	56.69	9.16	1.20		13199	14688
1683	[43]B. M. 23	6/05	Williamson	6	8.29	31.19	49.69	10.83	2.81		11837	
					Dry	34.01	54.18	11.81	3.06		12906	14903
1688	[43]B. M. 23	6/05	Williamson	6	8.41	34.27	45.44	11.88	3.63			
					Dry	37.42	49.61	12.97	3.96			
1762	[43]B. M. 23	6/05	Williamson	6	8.20	32.26	46.59	12.95	3.48		11362	
					Dry	35.14	50.75	14.11	3.79		12377	14564

[42] Analyses of a sample of forked coal.
[43] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 91, 1913.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
3907	[43]B. M. 23	6/05	Williamson	6	12.61	30.08	46.81	10.50	2.37	------	11066	------
					Dry	34.42	53.56	12.02	2.71	------	12663	14645
4083	[43]B. M. 23	6/05	Williamson	6	15.31	28.93	45.29	10.47	2.31	------	10820	------
					Dry	34.16	53.48	12.36	2.74	------	12776	14843
4201	[43]B. M. 23	6/05	Williamson	6	15.87	28.19	46.42	9.52	2.34	------	10784	------
					Dry	33.51	55.17	11.32	2.78	------	12818	14699
1634	[43]B. M. 24	5/05	Williamson	6	8.30	33.75	48.69	9.26	2.82	------	11999	------
					Dry	36.80	53.10	10.10	3.08	------	13084	14795
1654	[43]B. M. 24	5/05	Williamson	6	7.76	31.44	50.19	10.61	1.97	------	11957	------
					Dry	34.08	54.42	11.50	2.14	------	12964	14879
1660	[44]B. M. 24	5/05	Williamson	6	8.86	31.25	48.23	11.66	2.46	------	11702	------
					Dry	34.29	52.92	12.79	2.70	------	12839	14996
1718	[44]B. M. 24	5/05	Williamson	6	8.61	32.40	51.33	7.66	1.65	------	12236	------
					Dry	35.45	56.17	8.38	1.81	------	13388	14782
1653	[45]B. M. 24	5/05	Williamson	6	7.64	32.12	49.80	10.44	2.01	------	11939	------
					Dry	34.78	53.92	11.30	2.18	------	12928	14802
1802	[45]B. M. 24	5/05	Williamson	6	10.14	30.99	51.43	7.44	1.52	------	12116	------
					Dry	34.49	57.23	8.28	1.69	------	13482	14863
5238	[45]B. M. 24	6/07	Williamson	6	9.18	27.30	55.40	8.12	.90	------	12015	------
					Dry	30.06	61.00	8.94	.99	------	13230	14675
5215	[45]B. M. 24	6/07	Williamson	6	7.88	31.20	49.89	11.03	2.99	------	11741	------
					Dry	33.87	54.16	11.97	3.25	------	12746	14754
1731	[45]B. M. 25	6/05	Williamson	6	9.37	30.69	52.57	7.37	1.25	------	12058	------
					Dry	33.86	58.01	8.13	1.38	------	13306	14633
1732	[45]B. M. 25	6/05	Williamson	6	8.59	31.07	53.37	6.97	1.78	------	-------	------
					Dry	33.99	58.38	7.63	1.95	------	-------	------
1820	[45]B. M. 25	6/05	Williamson	6	8.43	30.08	51.89	9.60	1.14	------	11959	------
					Dry	32.85	56.67	10.48	1.24	------	13061	14771
3629	[45]B. M. 25	6/05	Williamson	6	8.72	30.38	53.28	7.62	1.00	------	12200	------
					Dry	33.28	58.37	8.35	1.10	------	13365	14726
3632	[46]B. M. 25	6/05	Williamson	6	8.88	29.49	53.60	8.03	.99	------	-------	------
					Dry	32.37	58.82	8.81	1.09	------	-------	------
3636	[46]B. M. 25	6/05	Williamson	6	8.80	29.85	53.83	7.52	1.13	------	12222	------
					Dry	32.73	59.02	8.25	1.24	------	13401	14754
3789	[46]B. M. 25	6/05	Williamson	6	7.78	29.85	52.39	9.98	1.32	------	11959	------
					Dry	32.37	56.81	10.82	1.43	------	12969	14734
1170	[46]B. M. 26	6/05	Williamson	6	7.50	31.68	53.67	7.15	.99	------	12386	------
					Dry	34.25	58.02	7.73	1.07	------	13388	14642

[44] Ibid., p. 92.
[45] Lord, N. W., and others, Analyses of coals: U. S. Bureau of Mines Bull. 22, pt. 1, p. 92, 1913.
[46] Ibid, p. 93.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Continued.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
1171	[46]B. M. 26	6/05	Williamson	6	7.34	34.29	50.84	7.53	2.04	------	------	------
					Dry	37.01	54.86	8.13	2.20	------	------	------
1318	[46]B. M. 26	6/05	Williamson	6	8.50	29.47	50.75	11.28	1.72	------	11776	------
					Dry	32.21	55.46	12.33	1.88	------	12870	14916
19714	[47]	7/14	Williamson	7	7.28	32.03	50.00	10.69	1.91	------	11804	------
					Dry	34.54	53.93	11.53	2.06	------	12731	14612
17719	[48]B. M. 27	8/13	Williamson	6	8.77	32.64	51.41	7.18	1.10	------	12177	------
					Dry	35.78	56.35	7.87	1.21	------	13347	14626
17721	[48]B. M. 27	8/13	Williamson	6	8.70	31.78	51.89	7.63	1.00	------	12173	------
					Dry	34.81	56.83	8.36	1.10	------	13334	14694
17720	[48]B. M. 27	8/13	Williamson	6	9.37	32.83	49.63	8.17	1.70	------	11988	------
					Dry	36.22	54.77	9.01	1.88	------	13228	14717
28810	[49]B. M. 28	8/17	Williamson	6	8.31	32.40	50.75	8.54	1.33	------	11965	------
					Dry	35.34	55.35	9.31	1.45	------	13048	14553
28811	[49]B. M. 28	8/17	Williamson	6	9.13	31.48	51.00	8.39	.97	------	11822	------
					Dry	34.64	56.13	9.23	1.07	------	13010	14485
28812	[49]B. M. 28	8/17	Williamson	6	8.82	35.15	47.90	8.13	1.07	------	11965	------
					Dry	38.55	52.53	8.92	1.17	------	13122	14559
28813	[49]B. M 28	8/17	Williamson	6	9.31	32.93	49.63	8.13	.82	------	11902	------
					Dry	36.31	54.73	8.96	.90	------	13124	14559
28814	[49]B. M. 28	8/17	Williamson	6	9.78	33.08	49.93	7.21	.75	------	11965	------
					Dry	36.67	55.34	7.99	.83	------	13262	14381
					No. 7 Coal.							
5416	99	8/12	LaSalle	7	13.82	41.42	35.90	8.86	3.95	.51	11174	------
					Dry	48.06	41.67	10.27	4.58	.59	12966	14744
5414	99	8/12	LaSalle	7	12.87	42.40	37.35	7.88	3.86	.00	11468	------
					Dry	48.67	42.86	8.47	4.44	.00	13161	14635
5417	99	8/12	LaSalle	7	13.99	38.81	40.12	7.08	3.23	.00	11401	------
					Dry	45.12	46.65	8.23	3.76	.00	13255	14675
4711	94	3/12	Vermilion	7	12.20	39.53	38.38	9.89	3.76	.46	11243	------
					Dry	45.03	43.70	11.27	4.29	.52	12804	14730
4713	94	3/12	Vermilion	7	12.70	39.20	39.24	8.86	2.79	.52	11399	------
					Dry	44.90	44.95	10.15	3.19	.59	13057	14776
4714	94	3/12	Vermilion	7	12.76	38.84	38.31	10.09	3.91	.61	11106	------
					Dry	44.53	43.91	11.56	4.48	.70	12788	14773
4716	94	3/12	Vermilion	7	12.67	39.01	37.43	10.89	3.54	.84	11041	------
					Dry	44.67	42.86	12.47	4.06	.96	12644	14734
4722	94	3/12	Vermilion	7	13.53	37.39	39.57	9.51	3.20	.46	11045	------
					Dry	43.24	45.76	11.00	3.70	.54	12773	14622
4724	94	3/12	Vermilion	7	13.27	37.25	40.65	8.83	3.27	.38	11209	------
					Dry	42.95	46.87	10.18	3.77	.44	12925	14650

[47] Fieldner, A. C., and others, Analyses of coals: U. S. Bureau of Mines Bull. 123, p. 36, 1918. Run of mine sample. Not included in averages.

[48] Ibid, p. 36.

[49] U. S. Bureau of Mines, unpublished analyses.

TABLE 2.—*Analyses of mine samples (not exactly indicative of commercial output)*—Concluded.

Laboratory number	Index number	Date	County	Coal bed	Proximate analysis of coal 1st: "As received," with total moisture 2nd: "Dry" or moisture free				Sulphur	CO_2	B. t. u.	Unit coal
					Moisture	Volatile matter	Fixed carbon	Ash				
4727	97	3/12	Vermilion	7	12.92	36.98	38.94	11.16	2.90	.70	10924	------
					Dry	42.46	44.73	12.81	3.33	.80	12544	14715
4734	97	3/12	Vermilion	7	13.10	38.42	39.14	9.34	2.26	.56	11281	------
					Dry	44.22	45.03	10.75	2.59	.64	12981	14778
4736	97	3/12	Vermilion	7	13.41	37.33	38.87	10.39	2.54	.46	11065	------
					Dry	43.11	44.89	12.00	2.93	.53	12778	14787
84226	211	2/22	Vermilion	7	13.1	37.7	36.8	9.4	2.8	.59	11110	------
					Dry	43.4	45.8	10.8	3.2	.69	12770	14564
84227	211	2/22	Vermilion	7	14.1	37.0	39.3	9.6	2.9	.86	11030	------
					Dry	43.1	45.7	11.2	3.4	1.0	12840	14727
84228	211	2/22	Vermilion	7	13.7	37.0	39.5	9.8	3.2	.70	11050	------
					Dry	42.9	45.7	11.4	3.7	.81	12800	14724

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts.*

DISTRICT NO. 1—BUREAU CO., NO. 2 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
1	16.19	37.79	38.06	8.00	3.24	.82	10787	----------
	Dry	45.06	45.40	9.54	3.86	.98	12869	14476
8	16.50	38.48	37.59	7.43	2.40	1.16	10868	----------
	Dry	46.08	45.02	8.90	2.90	1.39	13016	14493
10	16.13	38.82	38.36	6.69	3.15	.70	10994	----------
	Dry	46.28	45.74	7.98	3.76	.84	13108	14463
Average	16.27	38.35	38.00	7.38	2.93	.89	10883	----------
	Dry	45.80	45.39	8.81	3.50	1.40	12997	14477

DISTRICT NO. 1—GRUNDY CO., NO. 2 COAL

5	16.01	39.32	38.51	6.16	2.75	1.32	11104	----------
	Dry	46.83	45.84	7.33	3.28	1.57	13221	14463
6	19.53	37.59	37.94	4.94	2.01	.70	10818	----------
	Dry	46.71	47.15	6.14	2.61	.87	13444	14447
7	16.29	38.46	40.53	4.72	2.17	.48	11394	----------
	Dry	45.94	48.42	5.64	2.59	.57	13613	14579
Average	17.28	38.48	39.02	5.27	2.33	.83	11113	----------
	Dry	46.49	47.14	6.37	2.82	1.00	13426	14496

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts.*—Continued.

DISTRICT NO. 1—LA SALLE CO., NO. 2 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
2	14.60	39.88	36.97	8.55	3.97	.81	10904	----------
	Dry	46.70	43.29	10.01	4.65	.95	12768	14475
3	15,05	39.76	37.00	8.19	3.30	.59	10899	----------
	Dry	46.80	43.56	9.64	3.88	.69	12830	14448
9	17.45	38.98	34.52	9.04	3.18	1.49	10391	----------
	Dry	47.22	41.82	10.95	3.85	1.81	12587	14402
102	14.7	34.9	42.3	8.06	3.26	.73	11056	----------
	Dry	40.9	49.6	9.46	3.86	.84	12960	14892
103	12.4	39.40	41.27	6.65	2.61	----------	11779	----------
	Dry	44.99	47.10	7.90	2.97	----------	13448	14805
B. M. 1	13.93	36.78	40.34	8.93	3.45	----------	11192	----------
	Dry	46.87	46.87	10.37	4.00	----------	12883	14767
Average	14.58	38.28	42.01	8.23	3.29	.80	11020	----------
	Dry	45.58	45.37	9.72	3.86	1.06	12912	14632

DISTRICT NO. 1—MARSHALL CO., NO. 2 COAL

4	16.93	37.57	39.57	5.93	2.53	.37	11188	----------
	Dry	45.22	47.64	7.14	3.05	.44	13468	14696
11	13.28	40.58	37.71	8.43	3.04	.60	11435	----------
	Dry	46.80	43.48	9.72	3.51	.69	13186	14896
Average	15.10	39.06	38.68	7.16	2.79	.48	11315	----------
	Dry	46.01	45.56	8.43	3.28	.56	13327	14796

EXTRA SAMPLE—LA SALLE CO., NO. 5 COAL

	14.76	41.33	34.26	9.65	3.38	.61	10692	----------
	Dry	48.49	40.19	11.32	3.97	.71	12543	14397

DISTRICT NO. 1—LIVINGSTON CO., NO. 5 COAL

215	9.40	35.69	41.09	13.80	4.74	----------	11258	----------
	Dry	40.05	45.35	15.26	5.24	----------	12422	15084
216	13.76	36.00	38.96	11.50	3.15	----------	10850	----------
	Dry	41.48	45.18	13.34	3.66	----------	12581	14836
Average	11.58	35.84	40.02	12.65	3.94	----------	11054	----------
	Dry	40.26	45.26	14.30	4.45	----------	12501	14960

DISTRICT No. 1—LA SALLE CO., NO. 7 COAL

99	13.56	40.87	37.80	7.77	3.68	.17	11347	----------
	Dry	47.28	43.73	8.99	4.26	.20	13127	14685

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 2—JACKSON CO., NO. 2 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
12	9.62	33.02	51.09	6.27	1.13	.69	12260	----------
	Dry	36.53	56.53	6.94	1.25	.76	13565	14705
13	10.18	33.40	51.90	4.52	.97	.29	12614	----------
	Dry	37.18	57.79	5.03	1.08	.32	14044	14888
14	8.56	34.18	50.25	7.01	1.54	.09	12418	----------
	Dry	37.39	54.95	7.66	1.68	.10	13581	14864
15	8.70	34.77	51.34	5.19	1.42	.09	12651	----------
	Dry	38.08	56.23	5.69	1.55	.12	13856	14815
16	9.34	34.55	50.52	5.59	1.40	.26	12490	----------
	Dry	38.11	55.72	6.17	1.54	.29	13777	14820
104	4.56	36.32	45.22	13.90	7.12	.03	11778	----------
	Dry	38.06	47.38	14.57	7.47	.03	12167	14927
Average	8.49	34.37	50.05	7.08	2.26	.24	12368	----------
	Dry	37.55	54.76	7.67	2.42	.27	13498	14836

DISTRICT NO. 3—CHRISTIAN CO., NO. 1 COAL

21	11.31	38.89	40.94	8.86	2.35	.43	11602	----------
	Dry	43.85	46.16	9.99	2.65	.48	13081	14717

DISTRICT NO. 3—FULTON CO., NO. 1 COAL

105	11.21	38.41	40.16	10.20	4.96	.62	11466	----------
	Dry	43.26	45.23	11.50	5.58	.70	12914	14950

DISTRICT NO. 3—MERCER CO., NO. 1 COAL

17	17.63	39.13	34.13	9.11	5.02	.70	10336	----------
	Dry	47.51	41.44	11.05	6.09	.85	12548	14373
18	14.58	39.07	37.00	9.35	4.79	.21	10880	----------
	Dry	45.74	43.31	10.95	5.61	.25	12737	14640
19	14.52	39.26	36.32	9.90	4.24	.68	10809	----------
	Dry	45.93	42.49	11.58	4.96	.80	12645	14624
Average	15.58	39.17	35.80	9.45	4.69	.53	10673	----------
	Dry	46.40	42.41	11.19	5.55	.63	12643	14546

DISTRICT NO. 3—McDONOUGH CO., NO. 2 COAL

22	17.40	33.30	41.47	7.82	2.02	.27	10811	----------
	Dry	40.31	50.23	9.48	2.45	.33	13091	14663
213	15.86	35.08	40.27	8.79	3.86	----------	10798	----------
	Dry	41.69	47.85	10.45	4.58	----------	12832	14621
Average	16.63	34.19	40.37	8.31	2.94	----------	10804	----------
	Dry	41.00	49.04	9.96	3.51	----------	12961	14642

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 3—SCHUYLER CO., NO. 2 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
214	14.53	37.83	42.08	7.54	4.54	----------	11731	----------
	Dry	43.26	48.11	8.62	5.19	----------	13411	14967

DISTRICT NO. 4—McLEAN CO., NO. 2 COAL

100	11.26	42.21	37.73	8.80	3.03	.98	11566	----------
	Dry	47.57	42.52	9.91	3.41	1.10	13034	14714
B. M.	10.06	35.93	39.16	14.83	2.97	----------	11149	----------
55	Dry	39.95	43.55	16.49	3.31	----------	12422	15028
Average	10.66	39.07	38.44	11.81	3.00	----------	11357	----------
	Dry	43.76	43.03	13.20	3.36	----------	12728	14871

DISTRICT NO. 4—FULTON CO., NO. 5 COAL

28	16.68	36.68	36.76	9.88	2.90	1.36	10375	----------
	Dry	44.02	44.12	11.86	3.48	1.63	12452	14403
29	16.38	35.96	36.88	10.78	3.47	1.02	10230	----------
	Dry	43.01	44.10	12.89	4.15	1.22	12234	14349
30	16.18	35.17	37.77	10.88	3.06	1.53	10296	----------
	Dry	41.96	45.06	12.98	3.65	1.82	12284	14402
31	16.88	36.32	36.32	10.48	2.98	1.25	10269	----------
	Dry	43.70	43.70	12.61	3.58	1.50	12355	14424
32	14.66	37.24	37.71	10.39	3.28	1.54	10651	----------
	Dry	43.64	44.18	12.18	3.84	1.81	12481	14502
110	15.43	33.62	39.47	11.48	2.50	1.41	10389	----------
	Dry	39.76	46.67	13.57	2.66	1.67	12285	14473
111	14.61	34.05	38.64	13.22	3.03	2.22	10130	----------
	Dry	39.88	46.25	14.86	3.55	2.60	11865	14289
112	15.26	35.88	38.61	11.12	2.79	1.54	10522	----------
	Dry	41.30	45.56	13.12	3.29	1.78	12818	14596
113	14.25	34.79	39.19	11.75	3.18	1.45	10622	----------
	Dry	40.57	45.71	13.71	3.71	1.69	12383	14656
114	14.81	35.86	38.43	10.88	2.89	1.60	10123	----------
	Dry	37.10	45.11	12.78	3.40	1.87	12265	14339
115	15.25	33.50	40.50	10.25	3.10	1.16	10610	----------
	Dry	39.50	47.80	12.70	3.70	1.37	12520	14580
116	15.69	35.03	38.29	10.97	3.88	.51	10467	----------
	Dry	41.55	45.43	13.01	4.61	.61	12416	14609
117	13.5	34.4	38.8	13.3	3.5	----------	10410	----------
	Dry	39.8	44.8	15.4	4.1	----------	12040	14589
118	12.78	38.60	30.32	11.53	3.80	1.03	10903	----------
	Dry	40.40	49.66	13.26	4.36	1.18	12296	14746
Average	15.88	35.50	37.68	11.40	3.16	1.35	10428	----------
	Dry	41.15	45.58	13.53	3.72	1.58	12335	14496

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 4—LOGAN CO., NO. 5 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
33	14.20	37.19	37.44	11.37	3.34	1.42	10490	
	Dry	43.35	43.40	13.25	3.89	1.66	12226	14400
109	13.53	35.58	40.82	10.06	2.95	1.05	10924	
	Dry	41.14	47.20	11.64	3.09	1.15	12633	14590
B. M.	15.32	32.52	39.81	12.34	3.70		10371	
37	Dry	38.41	47.01	14.57	4.37		12234	14671
Average	14.35	35.09	39.35	11.25	3.33	1.23	10595	
	Dry	37.96	45.87	13.15	3.78	1.40	12364	14553

DISTRICT NO. 4—MACON CO., NO. 5 COAL

41	14.48	36.00	38.05	11.47	3.32	.90	10445	
	Dry	42.10	44.49	13.41	3.88	1 05	12214	14420
42	13.83	37.35	39.62	9.20	3.83	.09	10877	
	Dry	43.34	45.98	10.68	4.45	.11	12623	14418
123	12.82	35.45	43.07	8.64	3.23	.13	11010	
	Dry	40.67	49.41	9.91	3.71	.15	12668	14305
Average	13.71	36.26	40.24	9.77	3.46	.37	10777	
	Dry	42.03	46.62	11.33	4.01	.43	12501	14381

DISTRICT NO. 4—McLEAN CO., NO. 5 COAL

100	13.32	38.00	36.21	12.47	3.73	1.20	10580	
	Dry	43.84	41.78	14.38	4.30	1.39	12206	14604

DISTRICT NO. 4—MENARD CO., NO. 5 COAL

34	17.33	35.88	38.62	8.17	3.44	.50	10499	
	Dry	43.40	46.72	9.88	4.16	.60	12700	14478

DISTRICT NO. 4—PEORIA CO., NO. 5 COAL

25	14.92	36.92	37.21	11.02	3.44	1.21	10951	
	Dry	43.30	43.74	12.95	4.04	1.42	12448	14614
26	15.00	36.48	36.75	11.77	3.08	1.80	10421	
	Dry	42.91	43.24	13.85	3.62	2.12	12260	14614
106	13.40	30.33	44.80	11.46	3.80	1.05	10736	
	Dry	35.03	51.76	13.20	4.40	1.20	11980	14670
107	10.73	34.56	39.96	11.36	2.96	1.77	10673	
	Dry	40.16	46.60	13.23	3.40	2.05	12423	14617
B. M.	15.45	32.05	40.11	14.54	3.84		10732	
2	Dry	40.87	47.45	17.18	4.29		12693	14687
B. M.	15.38	34.34	38.65	11.63	2.90		10414	
3	Dry	40.58	45.65	13.74	3.43		12415	14575
Average	14.14	34.11	39.58	11.96	3.33	1.45	10654	
	Dry	40.47	46.40	14.02	3.86	1.69	12369	14629

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 4—SANGAMON CO., NO. 5 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
36	15.34	36.54	37.83	10.29	3.67	.59	10519	----------
	Dry	43.16	44.68	12.16	4.33	.70	12425	14450
37	13.78	37.82	37.69	10.73	4.11	.47	10625	----------
	Dry	43.86	43.71	12.44	4.77	.55	12323	14396
38	14.26	38.07	37.48	10.19	4.14	.37	10649	----------
	Dry	44.40	43.71	11.89	4.83	.43	12420	14410
39	13.31	37.43	36.66	12.60	4.72	.94	10398	----------
	Dry	43.17	42.29	14.54	5.45	1.09	11995	14420
40	15.06	36.69	38.15	10.10	4.08	.59	10584	----------
	Dry	43.19	44.92	11.89	4.80	.69	12460	14403
119	14.06	35.85	39.54	10.54	3.74	.43	10686	----------
	Dry	41.71	46.01	12.26	4.31	.50	12434	14479
120	13.62	36.81	39.24	10.32	3.93	.79	10786	----------
	Dry	42.62	45.42	11.95	4.55	.92	12487	14452
121	10.73	34.55	40.77	10.28	3.75	.45	10741	----------
	Dry	40.30	47.83	11.96	4.37	.52	12491	14502
122	13.15	35.62	41.28	9.93	3.90	.62	10812	----------
	Dry	41.02	47.54	11.44	4.49	.72	12449	14434
B. M. 41	13.70	34.47	40.58	11.23	3.81	----------	10696	----------
	Dry	39.95	47.03	13.01	4.42	----------	12332	13969
Average	13.70	36.38	38.92	10.62	3.98	.51	10650	----------
	Dry	42.33	45.31	12.32	4.63	.68	12381	14391

DISTRICT NO. 4—TAZEWELL CO., NO. 5 COAL

27	14.38	37.74	38.23	9.66	3.10	1.20	10809	----------
	Dry	44.08	44.65	11.28	3.62	1.40	12624	14496
108	15.76	34.36	40.60	9.26	3.30	.75	10660	----------
	Dry	40.80	48.23	10.76	3.90	.89	12656	14764
Average	15.07	36.05	39.41	9.46	3.20	.97	10734	----------
	Dry	42.44	46.44	11.02	3.76	1.14	12640	14630

DISTRICT NO. 5—GALLATIN CO., NO. 5 COAL

47	5.72	35.77	46.71	11.80	3.47	1.01	12053	----------
	Dry	37.94	49.54	12.52	3.68	1.07	12784	14919
Extra	4.13	34.21	52.80	8.86	3.23	.02	12987	----------
	Dry	35.68	55.07	9.25	3.37	03	13546	15175
135	3.96	35.38	50.23	10.41	3.37	.25	12601	----------
	Dry	36.84	52.31	10.85	3.51	.26	12997	14997
Average	4.60	35.12	49.91	10.36	3.36	.43	12547	----------
	Dry	36.82	52.31	10.87	3.52	.45	13309	15030

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 5—SALINE CO., NO. 5 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
43	6.97	35.98	49.69	7.36	2.05	.32	12550	----------
	Dry	38.68	53.41	7.92	2.20	.34	13490	14829
44	6.70	35.31	49.55	8.44	2.56	.02	12401	----------
	Dry	37.85	53.11	9.04	2.74	.02	13291	14824
45	7.03	34.78	50.27	7.92	2.48	.26	12420	----------
	Dry	37.41	54.07	8.52	2.67	.28	13359	14806
46	7.96	34.68	48.54	8.82	2.79	.46	12077	----------
	Dry	37.68	52.74	9.58	3.03	.50	13122	14741
48	7.67	33.90	50.26	8.17	2.56	.70	12234	----------
	Dry	36.72	54.43	8.85	2.77	.76	13250	14739
49	5.20	38.06	45.90	10.84	4.60	.59	12193	----------
	Dry	40.15	48.42	11.43	4.85	.62	12862	14824
124	6.83	33.25	51.85	8.03	2.24	.22	12435	----------
	Dry	35.70	55.67	8.62	2.40	.23	13353	14806
125	6.59	33.50	52.08	7.82	2.37	.09	12526	----------
	Dry	35.87	55.75	8.37	2.54	.09	13743	14831
126	6.01	34.05	52.34	7.58	2.56	.16	12582	----------
	Dry	36.23	55.70	8.06	2.61	.16	13341	14784
127	5.68	33.78	52.85	7.94	2.13	.42	12614	----------
	Dry	35.82	55.75	8.42	2.26	.44	13708	14780
128	6.51	32.24	51.31	9.93	1.87	.06	12175	----------
	Dry	34.48	54.87	10.63	2.01	.06	13022	14782
129	5.98	34.17	52.82	7.02	2.01	.09	12715	----------
	Dry	36.34	56.21	7.47	2.17	.09	13524	14840
130	6.22	33.33	51.47	8.96	2.71	.16	12339	----------
	Dry	35.54	54.89	9.56	2.83	.17	13358	14772
B. M. 5	7.61	32.64	51.65	8.24	2.08	----------	12225	----------
	Dry	35.05	55.99	8.95	2.22	----------	13316	15208
B. M. 6	5.78	33.39	52.81	8.01	2.26	----------	12718	----------
	Dry	35.44	56.06	8.50	2.72	----------	13498	15120
B. M. 7	7.07	34.56	51.07	7.29	2.15	----------	12560	----------
	Dry	37.19	54.95	7.85	2.31	----------	13516	15120
B. M. 8	4.83	38.49	46.74	9.73	4.03	----------	12441	----------
	Dry	40.65	49.12	10.22	4.23	----------	13073	14842
Average	6.08	34.37	51.05	8.47	2.83	.22	12521	----------
	Dry	36.61	54.36	9.02	2.96	.24	13377	14922

DISTRICT NO. 5—GALLATIN CO., NO. 6 COAL

Extra	7.54	34.96	45.68	11.82	4.34	.23	11916	----------
	Dry	37.81	49.41	12.78	4.70	.25	12888	15136
223	7.04	34.97	48.15	8.83	4.37	.03	12394	----------
	Dry	38.38	51.82	9.79	4.72	.03	13677	15095
Average	7.29	34.96	46.91	10.33	4.36	.13	12155	----------
	Dry	38.09	50.61	11.29	4.71	.14	13283	15115

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

EXTRA SAMPLE—GALLATIN CO., COAL MARKED "BELL"

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
	3.40	33.33	55.18	8.09	4.25	.03	13401	
	Dry	34.50	57.12	8.38	4.40	.03	13872	15420

DISTRICT NO. 5—WHITE CO., NO. 6 COAL

228	8.36	35.24	47.43	8.89	2.85	.64	11923	
	Dry	38.49	51.80	9.71	3.11	.69	13022	14654

DISTRICT NO. 6—FRANKLIN CO., NO. 6 COAL

50	9.34	34.84	48.03	7.79	1.04	.38	12004	
	Dry	38.42	52.99	8.59	1.15	.42	13241	14633
51	10.28	33.42	49.05	7.25	1.18	.10	11890	
	Dry	37.26	54.66	8.08	1.32	.11	13252	14562
52	6.77	38.35	44.62	10.26	3.13	.91	11875	
	Dry	41.14	47.85	11.00	3.36	.98	12737	14554
53	10.18	32.78	48.88	8.16	.64	.61	11661	
	Dry	36.50	54.41	9.09	.71	.68	12983	14419
56	8.10	36.30	45.34	10.26	2.51	.74	11826	
	Dry	39.50	49.34	11.16	2.73	.80	12758	14601
57	9.67	35.69	49.55	8.54	.95	.32	11756	
	Dry	32.24	54.86	9.45	1.05	.35	13015	14529
58	8.93	34.51	48.80	7.76	.74	.36	11937	
	Dry	37.89	53.59	8.52	.81	.40	13108	14463
134	8.28	33.23	47.34	8.80	1.26	.20	11962	
	Dry	36.22	54.17	9.59	1.38	.22	12885	14487
136	7.37	35.16	47.39	9.66	2.50	.37	11757	
	Dry	37.98	51.57	10.43	2.72	.40	12602	14433
137	10.21	34.29	47.70	7.79	.79		11813	
	Dry	35.67	53.13	8.65	.88		13155	14556
138	9.84	34.30	47.93	7.91	.76		11824	
	Dry	39.09	53.16	8.78	.84		13113	14392
139	7.87	35.15	47.60	9.36	2.28	.22	11790	
	Dry	38.14	51.70	10.14	2.47	.24	14351	14461
140	6.84	35.05	49.22	8.87	2.54	.18	11964	
	Dry	37.61	52.86	9.52	2.71	.19	12708	14412
141	10.19	33.35	48.66	7.79	1.11		11824	
	Dry	37.14	54.18	8.68	1.50		13166	14632
142	9.98	32.72	49.20	8.09	.83		11903	
	Dry	36.34	54.66	8.98	.92		13224	14675
143	10.18	34.19	48.54	7.12	1.30		11936	
	Dry	36.74	54.04	7.92	1.44		12827	14700
144	10.46	32.35	49.66	7.51	.73		11807	
	Dry	36.13	55.47	8.38	.82		13216	14550
145	8.48	32.16	50.88	8.46	1.03	.16	11917	
	Dry	35.16	55.45	9.24	1.13	.17	12969	14503

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 6—FRANKLIN CO., NO. 6 COAL—Concluded.

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
146	9.28	31.39	50.06	9.27	.69	----------	11908	----------
	Dry	38.84	55.18	10.21	.76	----------	12962	14558
147	8.42	33.91	46.45	10.20	3.27	----------	11569	----------
	Dry	37.43	51.29	11.25	3.61	----------	12773	14649
B. M. 9	9.35	32.41	49.39	8.84	1.41	----------	11858	----------
	Dry	35.76	52.92	9.75	1.55	----------	13016	14686
B. M. 10	8.61	33.69	48.47	9.21	1.09	----------	11921	----------
	Dry	36.87	53.04	10.07	1.19	----------	13020	14688
B. M. 11	9.50	31.98	47.08	11.44	1.45	----------	11506	----------
	Dry	35.34	52.02	12.64	1.60	----------	12713	14780
B. M. 12	10.63	28.83	52.03	8.48	5.53	----------	11585	----------
	Dry	32.26	58.24	9.49	6.20	----------	12734	14909
B. M. 13	9.00	34.27	48.08	8.64	1.06	----------	11980	----------
	Dry	37.66	52.83	9.50	1.17	----------	13165	14712
B. M. 14	9.18	33.93	48.51	8.36	.92	----------	11911	----------
	Dry	37.36	53.42	9.37	1.01	----------	13116	14620
B. M. 15	9.96	32.86	49.06	8.11	.80	----------	11901	----------
	Dry	36.49	54.49	9.01	.89	----------	13215	14672
B. M. 16	7.14	30.69	50.47	9.27	.51	----------	11727	----------
	Dry	33.93	55.80	10.26	.57	----------	12964	14602
B. M. 17	8.99	32.21	49.75	9.29	.88	----------	11788	----------
	Dry	35.39	54.40	11.94	.97	----------	12953	14673
B. M. 18	9.83	32.76	49.52	7.87	1.00	----------	11901	----------
	Dry	36.34	54.93	8.73	1.11	----------	13199	14609
B. M. 19	10.21	32.45	49.33	8.01	1.02	----------	11152	----------
	Dry	36.13	54.94	8.92	1.18	----------	13162	14605
B. M. 20	8.25	31.30	49.65	10.79	1.08	----------	11645	----------
	Dry	34.11	54.12	11.76	1.18	----------	12128	14580
B. M. 21	9.84	34.58	47.93	7.91	.76	----------	11824	----------
	Dry	38.04	53.16	8.78	.84	----------	13113	14514
B. M. 22	9.58	33.58	48.20	8.63	1.09	----------	11866	----------
	Dry	37.14	53.31	9.54	1.21	----------	13125	14640
B. M. 58	8.33	34.91	48.45	8.29	1.09	----------	12050	----------
	Dry	38.07	52.87	9.05	1.18	----------	13146	14618
Average	9.11	33.53	48.59	8.68	1.39	.37	11815	----------
	Dry	36.75	53.57	9.61	1.54	.41	13023	14590

DISTRICT NO. 6—JACKSON CO., NO. 6 COAL

55	8.96	34.44	46.40	10.20	2.65	.40	11609	----------
	Dry	37.83	50.97	11.20	2.91	.44	12751	14608
183	9.74	34.58	46.62	9.34	1.43	.14	11467	----------
	Dry	38.32	51.58	10.28	1.58	.15	12693	14343
Average	9.35	34.51	46.51	9.77	2.04	.27	11538	----------
	Dry	38.07	51.27	10.74	2.24	.29	12722	14475

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 6—PERRY CO., NO. 6 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
54	9.92	32.72	46.97	10.39	.92	.25	11335	----------
	Dry	36.81	52.15	11.53	1.02	.28	12583	14407
175	10.14	35.64	43.76	10.45	3.66	.36	11356	----------
	Dry	39.67	48.70	11.63	4.08	.40	12455	14379
178	9.77	34.99	42.19	12.70	4.09	.32	10815	----------
	Dry	38.78	47.13	14.06	4.54	.34	11987	14330
179	8.83	37.36	43.02	10.78	3.40	.12	11295	----------
	Dry	40.99	47.18	11.82	3.73	.13	12202	14327
180	9.31	33.64	47.51	9.52	1.07	.20	11596	----------
	Dry	37.10	52.39	10.50	1.18	.23	12278	14337
181	12.08	33.81	44.87	9.22	.99	----------	11227	----------
	Dry	38.46	51.04	10.49	1.69	----------	12769	14446
B. M.	10.96	32.52	48.64	7.86	.85	----------	11542	----------
29	Dry	36.53	54.63	8.83	.96	----------	12963	14365
Average	10.14	34.38	45.28	10.13	2.14	.25	11309	----------
	Dry	38.33	50.46	11.26	2.45	.27	12462	14370

DISTRICT NO. 6—WILLIAMSON CO., NO. 6 COAL

59	10.47	32.99	47.27	9.27	1.52	.38	11630	----------
	Dry	36.85	52.80	10.35	1.70	.43	12990	14684
60	8.22	34.00	48.79	8.99	2.16	.33	11959	----------
	Dry	37.04	53.16	9.80	2.35	.36	13030	14660
61	9.27	33.83	49.70	7.20	1.37	.13	12127	----------
	Dry	37.28	54.78	7.94	1.51	.14	13366	14671
62	9.13	33.09	49.94	7.84	1.17	.22	12028	----------
	Dry	36.42	54.95	8.63	1.29	.24	13236	14637
63	9.47	33.45	48.13	8.95	1.94	.36	11852	----------
	Dry	36.96	53.16	9.88	2.14	.40	13092	14730
64	9.34	32.77	49.48	8.41	.92	.52	11872	----------
	Dry	36.15	54.58	9.27	1.01	.57	13095	14577
65	9.31	33.52	48.98	8.19	1.70	.13	11919	----------
	Dry	36.96	54.01	9.03	1.88	.14	13143	14627
148	7.99	33.48	50.15	8.37	1.21	.15	12129	----------
	Dry	36.39	54.51	9.09	1.32	.16	13183	14664
149	6.31	35.09	47.86	10.73	3.08	.43	11931	----------
	Dry	37.45	51.11	11.43	3.28	.49	12738	14697
150	5.98	35.00	47.69	11.29	4.00	.26	11786	----------
	Dry	37.23	50.72	12.01	4.25	.27	12536	14550
151	6.91	36.41	47.09	9.59	2.78	.10	12015	----------
	Dry	39.11	50.58	10.30	2.99	.11	12907	14625
152	7.03	32.26	51.63	9.07	1.32	.31	12117	----------
	Dry	34.70	55.53	9.75	1.42	.33	13009	14617
153	9.63	32.30	49.54	8.52	.91	----------	11824	----------
	Dry	37.49	54.83	9.43	1.01	----------	13086	14607
154	7.90	32.28	51.29	8.52	1.19	.17	12108	----------
	Dry	35.05	55.70	9.24	1.29	.19	13129	14530
155	8.21	32.75	51.09	7.94	1.18	.14	12017	----------
	Dry	35.67	55.66	8.66	1.29	.16	13043	14485
156	8.24	32.91	52.98	7.05	1.40	.12	12150	----------
	Dry	34.56	57.74	7.28	1.54	.13	13202	14448

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 6—WILLIAMSON CO., NO. 6 COAL—Concluded.

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
157	8.20	34.51	48.33	8.95	2.50	.24	12007	----------
	Dry	37.59	52.67	9.74	2.71	.25	13081	14718
158	8.54	31.07	51.88	8.50	2.22	.17	11861	----------
	Dry	33.97	56.73	9.29	2.42	.18	12892	14535
159	7.59	33.59	50.40	9.74	3.11	.13	11880	----------
	Dry	34.90	54.54	10.54	3.36	.14	12720	14625
160	8.07	32.59	50.70	8.64	2.14	.05	11966	----------
	Dry	35.44	55.16	9.39	2.32	.05	12900	14564
161	9.07	33.00	49.84	8.08	.98	----------	11923	----------
	Dry	36.30	54.81	8.88	1.08	----------	13115	14539
162	9.90	33.23	48.10	8.77	1.27	----------	11716	----------
	Dry	36.88	53.38	9.74	1.41	----------	13003	14579
163	6.62	34.97	47.61	10.75	3.16	----------	11875	----------
	Dry	37.92	51.17	11.52	3.28	----------	12702	14624
164	7.31	34.18	46.48	12.02	3.07	----------	11635	----------
	Dry	36.88	50.15	12.97	3.31	----------	12553	14726
165	8.04	33.04	49.10	9.81	2.24	.70	11854	----------
	Dry	35.92	53.42	10.65	2.42	.76	12893	14655
166	7.46	32.79	49.32	10.41	2.86	.55	11733	----------
	Dry	35.44	53.31	11.24	3.05	.60	12529	14540
167	7.78	32.75	50.34	9.11	1.88	.27	11925	----------
	Dry	35.50	54.60	9.88	2.03	.29	12858	14550
168	5.22	36.59	46.09	12.08	3.55	.36	11909	----------
	Dry	38.60	48.63	12.75	3.76	.38	12450	14707
169	6.10	35.44	47.27	11.18	3.85	.36	11786	----------
	Dry	37.74	50.35	11.91	4.11	.38	12414	14553
170	6.40	36.71	47.70	9.19	3.41	.04	12150	----------
	Dry	39.22	50.96	9.82	3.64	.04	12981	14644
171	7.29	34.93	47.65	10.13	3.78	.04	11745	----------
	Dry	37.68	51.39	10.93	4.08	.04	12669	14334
172	6.40	36.38	48.20	9.02	3.45	.04	12179	----------
	Dry	38.87	51.49	9.64	3.69	.04	13012	14648
173	6.95	36.05	45.33	11.65	3.54	.52	11744	----------
	Dry	38.75	48.73	12.51	3.81	.56	12623	14787
174	6.93	33.52	50.04	9.49	2.03	----------	12039	----------
	Dry	36.02	53.77	10.20	2.18	----------	12934	14610
B. M. 23	11.44	30.82	46.70	11.02	2.82	----------	11191	----------
	Dry	34.77	52.79	12.43	3.17	----------	12708	12275
B. M. 24	9.89	31.30	50.62	9.52	1.79	----------	11983	----------
	Dry	34.22	55.38	10.40	2.23	----------	13085	14815
B. M. 25	8.65	30.20	52.99	8.17	1.23	----------	12079	----------
	Dry	33.06	58.01	8.92	1.34	----------	13220	14725
B. M. 26	7.78	31.81	51.75	8.65	1.58	----------	12081	----------
	Dry	34.49	53.20	9.39	1.71	----------	13129	14779
B. M. 27	8.94	32.41	50.97	7.66	1.26	----------	12112	----------
	Dry	35.56	55.98	8.41	1.39	----------	13303	14679
B. M. 28	9.07	33.00	49.84	8.18	.98	----------	11923	----------
	Dry	36.30	54.81	8.88	1.08	----------	13073	14507
Average	8.07	33.52	50.12	9.26	2.17	.25	11549	----------
	Dry	36.43	53.48	10.05	2.34	.27	12940	14463

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 7—BOND CO., NO. 6 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
218	11.96	35.09	42.31	10.30	3.38	.66	10806	
	Dry	39.86	48.06	12.07	3.84	.70	12274	14240

DISTRICT NO. 7—CHRISTIAN CO., NO. 1 COAL

21	11.31	38.89	40.94	8.86	2.35	.43	11602	
	Dry	43.85	46.16	9.99	2.65	.48	13081	14717

DISTRICT NO. 7—CHRISTIAN CO., NO. 2 COAL

21	12.96	38.96	40.94	6.92	3.13	.20	11591	
	Dry	45.01	47.04	7.95	3.60	.24	13319	14691

DISTRICT NO. 7—CHRISTIAN CO., NO. 6 COAL

219	12.00	37.22	39.77	11.01	3.85	.45	10798	
	Dry	42.29	45.19	12.51	4.38	.51	12271	14455
220	13.91	36.39	39.32	10.36	4.00	.54	10682	
	Dry	42.28	45.68	12.02	4.65	.63	12410	14493
221	12.04	37.09	40.60	10.25	4.17	.22	10887	
	Dry	42.17	46.16	11.66	4.74	.26	12438	14293
222	12.10	37.64	41.00	9.17	3.71	.11	11043	
	Dry	42.83	46.73	10.43	4.22	.13	12565	13917
B. M. 56	12.67	37.27	39.44	10.55	3.65		10919	
	Dry	42.75	45.17	12.08	4.38		12504	14442
Average	12.54	37.12	40.03	10.27	3.89	.33	10866	
	Dry	42.46	45.79	11.74	4.47	.38	12438	14320

DISTRICT NO. 7—CLINTON CO., NO. 6 COAL

84	12.86	37.26	39.53	10.35	4.26	.58	10755	
	Dry	42.76	45.36	11.88	4.89	.66	12342	14335
85	12.39	36.88	40.68	10.05	3.52	.72	10836	
	Dry	42.10	46.43	11.47	4.02	.82	12368	14245
198	11.09	36.99	41.04	10.86	3.51	.61	10887	
	Dry	41.61	46.17	12.21	3.95	.69	12242	14450
199	11.17	34.93	43.26	10.64	3.58	.44	10920	
	Dry	39.32	48.69	11.98	4.03	.50	12294	13853
B. M. 46	11.71	35.21	42.63	10.44	4.06		11011	
	Dry	39.88	48.29	11.82	4.59		12441	14363
B. M. 47	12.53	33.43	44.20	9.83	3.96		10947	
	Dry	38.15	50.55	11.23	4.52		12503	14801
B. M. 48	14.75	29.62	45.98	9.64	1.57		10726	
	Dry	34.75	53.94	11.31	1.84		12629	14447
Average	12.35	34.90	42.47	10.25	3.49	.58	10871	
	Dry	39.79	48.49	13.12	3.97	.66	12402	14356

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 7—MACOUPIN CO., NO. 6 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
66	14.26	38.70	37.07	9.97	4.34	.41	10549	
	Dry	45.14	43.24	11.62	5.06	.48	12304	14236
67	14.19	37.48	38.24	9.99	3.92	.33	10558	
	Dry	43.68	44.57	11.75	4.57	.39	12447	14408
68	12.87	39.24	38.73	9.16	4.56	.30	10964	
	Dry	45.04	44.45	10.51	5.23	.35	12583	14365
69	14.20	37.40	36.95	11.45	4.42	.29	10438	
	Dry	43.59	43.06	13.35	5.15	.34	12165	14388
185	11.85	39.35	39.77	9.01	3.49	.28	11069	
	Dry	44.62	45.14	10.23	3.96	.32	12557	14243
186	10.78	37.82	40.56	10.49	4.00	.66	10906	
	Dry	42.54	45.64	11.81	4.50	.74	12271	14208
187	13.56	36.74	38.83	10.80	4.19	.40	10549	
	Dry	42.51	44.92	12.57	4.85	.47	12203	14279
188	11.97	38.65	40.90	8.42	3.93	.14	11061	
	Dry	43.91	46.50	9.57	4.46	.16	12566	14189
189	13.93	35.12	42.04	8.89	3.78	.11	11012	
	Dry	40.80	48.85	10.34	4.39	.13	12407	14129
190	14.11	34.23	42.42	9.23	3.63	.15	10709	
	Dry	39.86	49.39	10.74	4.22	.18	12466	14191
228	14.03	37.17	39.60	9.20	3.49	----------	10753	
	Dry	43.24	46.06	10.70	4.06	----------	12508	14273
B. M. 30	14.29	34.18	40.16	11.36	3.91	----------	10536	
	Dry	39.86	46.86	13.27	4.57	----------	12260	14558
B. M. 31	14.25	36.85	39.20	10.68	4.21	----------	10632	
	Dry	42.48	45.20	12.31	4.85	----------	12258	14298
Average	13.36	37.32	39.58	9.92	4.01	.30	10752	
	Dry	42.86	45.42	11.46	4.63	.35	12380	14290

DISTRICT NO. 7—MADISON CO., NO. 6 COAL

70	12.81	38.67	37.40	11.12	4.80	.44	10661	
	Dry	44.35	42.91	12.75	5.51	.54	12227	14365
71	12.52	39.55	37.51	10.42	4.09	.61	10871	
	Dry	45.21	42.88	11.91	4.68	.70	12427	14421
72	13.82	37.54	38.94	9.70	4.25	.25	10722	
	Dry	43.56	45.19	11.25	4.93	.29	12441	14391
73	14.71	38.61	38.22	8.46	3.76	.28	10785	
	Dry	45.27	44.81	9.92	4.41	.33	12645	14305
191	12.97	38.33	37.82	10.86	3.69	.51	10708	
	Dry	44.05	43.46	12.47	4.24	.59	12305	14362
192	11.64	37.02	41.06	10.27	4.04	.44	10963	
	Dry	41.89	46.47	11.62	4.57	.50	12407	14511
B. M. 32	12.69	35.12	36.14	14.04	4.32	----------	10232	
	Dry	40.19	43.68	15.80	4.94	----------	11750	14619
B. M. 33	10.69	33.08	36.14	20.09	4.06	----------	9713	
	Dry	37.04	40.47	22.49	4.55	----------	10876	14560
B. M. 34	13.25	34.03	40.09	12.11	3.98	----------	10371	
	Dry	39.44	46.47	14.08	4.61	----------	12057	14448

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 7—MADISON CO., NO. 6 COAL—Concluded.

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
B. M.	12.95	34.11	41.11	11.81	4.06	----------	10699	----------
35	Dry	39.19	47.23	13.57	4.66	----------	12292	14565
B. M.	13.07	34.27	40.79	11.86	4.45	----------	10562	----------
36	Dry	39.42	46.93	13.64	5.11	----------	12115	14532
B. M.	15.09	31.00	46.49	7.42	.83	----------	11151	----------
38	Dry	36.51	54.75	8.74	.98	----------	13133	14533
B. M.	15.19	31.02	43.41	10.36	1.44	----------	10737	----------
39	Dry	36.57	51.19	12.23	1.70	----------	12567	14526
B. M.	12.69	36.50	41.45	9.35	3.72	----------	11025	----------
40	Dry	41.80	47.76	10.71	4.05	----------	12627	14466
Average	13.14	35.63	44.31	12.50	3.67	.42	10657	----------
	Dry	41.03	46.01	12.94	4.21	.49	12276	14471

DISTRICT NO. 7—MARION CO., NO. 6 COAL

87	10.46	36.85	41.53	11.16	4.01	.42	11174	----------
	Dry	41.15	46.38	12.47	4.48	.47	12480	14574
206	9.93	36.45	42.22	11.38	4.06	.31	11168	----------
	Dry	40.47	46.89	12.63	4.50	.34	12401	14582
207	10.41	36.71	42.31	10.56	3.27	.43	11267	----------
	Dry	40.98	47.22	11.79	3.65	.49	12576	14536
B. M.	10.69	36.01	41.76	11.53	3.60	----------	11018	----------
52	Dry	40.32	46.78	12.89	4.03	----------	12257	14650
Average	10.37	36.50	41.95	11.15	3.96	.29	11156	----------
	Dry	40.75	46.81	12.44	4.16	.32	12428	14585

DISTRICT NO. 7—MONTGOMERY CO., NO. 6 COAL

76	13.89	37.05	38.44	10.62	3.85	.94	10574	----------
	Dry	43.04	44.64	12.32	4.47	1.10	12280	14312
77	14.40	36.70	39.84	9.06	3.83	.49	10709	----------
	Dry	42.88	46.54	10.58	4.47	.57	12511	14268
194	13.19	36.30	40.62	9.68	4.07	.49	10779	----------
	Dry	41.81	47.03	11.15	4.69	.57	12418	14270
195	12.87	36.07	41.61	9.44	3.83	.45	10844	----------
	Dry	41.39	47.77	10.83	4.40	.51	12447	14348
196	12.27	36.79	40.62	10.45	4.42	.73	10799	----------
	Dry	41.87	46.23	11.89	5.04	.83	12296	14271
197	14.71	34.67	41.79	8.79	3.85	.42	10588	----------
	Dry	40.66	49.01	10.32	4.51	.49	12415	14113
B. M.	13.54	38.85	42.09	11.64	3.99	----------	10550	----------
43	Dry	44.47	48.69	13.45	4.61	----------	12195	14453
B. M.	13.17	33.64	41.34	11.83	----------	----------	10548	----------
44	Dry	38.75	47.62	13.62	----------	----------	12168	14394
B. M.	13.47	34.62	40.32	11.57	3.47	----------	10558	----------
45	Dry	40.01	46.60	13.37	4.64	----------	12202	14417
Average	13.50	34.96	40.74	10.34	3.91	.58	10661	----------
	Dry	41.65	47.12	11.94	4.60	.67	12325	14316

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 7—MOULTRIE CO., NO. 6 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
225	6.83	39.15	42.31	11.37	4.01	.57	11878	----------
	Dry	42.01	45.41	12.56	4.31	.61	12738	14882

DISTRICT NO. 7—PERRY CO., NO. 6 COAL

88	9.61	37.09	41.27	12.03	3.70	.86	10982	----------
	Dry	41.03	45.66	13.30	4.10	.95	12150	14331
89	12.45	36.14	42.77	8.64	2.80	.27	11207	----------
	Dry	41.28	48.85	9.87	3.20	.31	12801	14431
90	10.95	37.00	41.82	10.23	3.61	.56	11060	----------
	Dry	41.55	46.96	11.50	4.05	.63	12420	14314
176	10.17	36.37	43.32	10.13	3.43	.48	11180	----------
	Dry	40.48	48.23	11.28	3.61	.52	12446	14254
177	9.45	35.01	41.93	13.61	3.84	.86	10763	----------
	Dry	38.66	46.31	15.03	4.24	.95	11886	14334
182	9.09	36.52	43.91	11.19	3.71	.41	11139	----------
	Dry	39.38	48.30	12.31	4.08	.45	12252	14263
184	7.99	38.16	42.59	11.24	3.57	.52	11290	----------
	Dry	41.48	46.29	12.22	3.88	.56	12271	14263
Average	9.95	36.61	42.51	11.01	3.52	.56	11088	----------
	Dry	40.55	47.22	12.21	3.88	.62	12318	14312

DISTRICT NO. 7—RANDOLPH CO., NO. 6 COAL

83	11.13	37.28	40.14	11.45	4.24	.58	10855	----------
	Dry	41.95	45.17	12.89	4.77	.65	12214	14351
229	8.39	37.50	43.61	10.49	3.94	.17	11275	----------
	Dry	40.94	47.60	11.45	4.30	.19	12308	14180
208	10.17	36.48	41.30	12.03	3.78	.61	10940	----------
	Dry	40.61	45.98	13.40	4.24	.67	12184	14388
209	9.64	36.90	41.90	11.54	4.25	.64	10960	----------
	Dry	40.84	46.37	12.77	4.70	.71	12131	14227
210	9.33	36.21	42.96	11.50	3.51	.32	11189	----------
	Dry	39.93	47.38	12.69	3.87	.35	12341	14434
Average	9.73	36.87	41.99	11.40	3.94	.46	11043	----------
	Dry	40.85	46.50	12.64	4.37	.51	12235	14316

DISTRICT NO. 7—SANGAMON CO., NO. 6 COAL

74	14.25	38.42	37.22	10.11	4.75	.39	10556	----------
	Dry	44.80	43.42	11.79	5.54	.46	12310	14287
75	14.15	37.58	38.99	9.28	3.76	.45	10786	----------
	Dry	43.77	45.42	10.81	4.38	.52	12564	14369
193	13.12	36.48	40.21	10.18	4.01	.56	10751	----------
	Dry	41.97	46.28	11.72	4.61	.65	12375	14320
B. M. 42	14.82	34.81	39.76	10.60	4.27	----------	10473	----------
	Dry	40.85	46.67	12.47	5.01	----------	12337	14516
Average	14.08	36.82	39.04	10.04	4.19	.46	10641	----------
	Dry	42.84	45.44	11.69	4.88	.54	12396	14373

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts*—Continued.

DISTRICT NO. 7—SHELBY CO., NO. 5 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
217	10.74	36.59	41.48	10.84	3.70	.52	11050	
	Dry	41.15	46.64	12.20	4.16	.59	12426	14568

DISTRICT NO. 7—ST. CLAIR CO., NO. 6 COAL

78	11.75	38.71	38.12	11.43	3.63	.80	10874	
	Dry	43.86	43.19	12.95	4.11	.91	12322	14466
79	11.31	39.77	38.92	10.00	3.94	.63	11143	
	Dry	44.84	43.89	11.27	4.44	.71	12564	14468
80	10.04	39.33	39.09	11.54	3.91	.78	11045	
	Dry	43.72	43.45	12.83	4.35	.87	12278	14398
81	11.23	40.36	38.31	10.10	4.03	.54	11126	
	Dry	45.47	43.17	11.39	4.54	.61	12533	14444
82	11.94	39.72	37.53	10.81	4.46	.39	10949	
	Dry	45.10	42.62	12.27	5.07	.45	12434	14510
200	13.74	31.44	43.54	11.24	1.79	.69	10574	
	Dry	36.47	50.49	13.04	2.08	.79	12262	14341
201	11.66	37.78	40.80	10.09	3.69	.39	11087	
	Dry	42.38	46.19	11.42	4.18	.44	12550	14537
202	11.09	37.37	39.59	11.93	4.62	.50	10864	
	Dry	42.04	44.53	13.42	5.19	.56	12220	14473
203	12.26	39.93	39.32	10.39	4.32	.49	11167	
	Dry	44.63	43.86	11.60	4.97	.55	12456	14401
204	11.52	37.20	41.67	9.61	2.82	.10	11155	
	Dry	42.05	47.09	10.86	3.19	.10	12607	14394
205	9.67	37.28	41.22	11.82	3.30	.55	11044	
	Dry	41.27	45.64	13.08	3.66	.61	12227	14357
B. M.	13.55	34.52	42.06	10.76	3.33		10625	
49	Dry	38.90	48.66	12.44	3.86		12320	14419
B. M.	10.75	39.66	37.99	14.00	4.09		10132	
50	Dry	41.71	42.55	15.74	4.58		11750	14607
B. M.	10.78	39.18	38.96	11.08	4.11		11069	
51	Dry	43.89	43.67	12.43	4.61		12405	14678
Average	11.52	38.01	39.79	11.05	3.71	.53	10918	
	Dry	42.59	44.92	12.48	4.20	.60	12352	14463

DISTRICT NO. 7—WASHINGTON CO., NO. 6 COAL

86	11.13	38.20	39.39	11.28	3.91	.50	10964	
	Dry	42.98	44.32	12.70	4.40	.56	12337	14448
226	9.42	38.65	39.71	12.21	4.30	.52	10958	
	Dry	42.68	43.84	13.47	4.75	.57	12098	14318
Average	10.27	38.42	39.55	11.74	4.10	.51	10961	
	Dry	42.83	44.08	13.08	4.57	.56	12217	14383

TABLE 3.—*Average analyses and heat values for separate mines and by counties—grouped according to districts.*—Concluded.

DISTRICT NO. 8—VERMILION CO., NO. 6 COAL

Index number	Moisture	Volatile matter	Fixed carbon	Ash	Sulphur	CO_2	B. t. u.	"Unit coal"
91	14.44	35.04	40.99	9.53	2.37	.66	10982	----------
	Dry	40.95	47.91	11.14	2.77	.77	12836	14697
92	15.59	33.47	40.16	10.78	2.33	.89	10508	----------
	Dry	39.65	47.58	12.77	2.76	1.06	12449	14536
93	15.19	34.95	41.55	8.31	2.04	.65	10961	----------
	Dry	41.21	48.99	9.80	2.41	.77	12925	14533
95	12.59	40.16	38.53	8.72	3.49	.80	11228	----------
	Dry	45.94	44.08	9.98	3.99	.92	12845	14532
212	14.23	34.00	42.66	9.10	2.30	.77	11043	----------
	Dry	39.60	49.86	10.53	2.66	.90	12873	14616
B. M. 53	16.16	34.09	39.19	10.56	1.74	----------	10433	----------
	Dry	40.66	46.75	12.59	2.08	----------	12443	14472
B. M. 54	15.62	35.59	39.97	8.82	1.68	----------	10845	----------
	Dry	42.18	47.37	10.45	1.99	----------	12852	14554
Average	14.83	35.72	40.43	9.40	2.27	.75	10857	----------
	Dry	41.45	47.50	11.03	2.66	.88	12946	14562

DISTRICT NO. 8—VERMILION CO., NO. 7 COAL

94	12.69	38.78	38.89	9.64	3.34	.52	11221	----------
	Dry	44.42	44.54	11.04	3.83	.59	12852	14725
97	13.18	37.85	38.65	10.32	2.54	.60	11080	----------
	Dry	43.59	44.52	11.89	2.92	.69	12762	14754
211	13.63	37.23	39.53	9.60	7.13	----------	11030	----------
	Dry	43.13	45.73	11.13	8.33	----------	12803	14671
Average	13.16	37.95	39.02	9.85	4.33	.56	11110	----------
	Dry	39.02	44.93	11.35	5.02	.64	12805	14716

PUBLICATIONS

ILLINOIS MINING INVESTIGATIONS

ILLINOIS STATE GEOLOGICAL SURVEY DIVISION
URBANA, ILLINOIS

Bulletin 1. Preliminary report on organization and method of investigation, 1913.
Bulletin 3. Chemical study of Illinois coals, by S. W. Parr, 1916.
Bulletin 10. Coal resources of District I (Longwall), by G. H. Cady, 1915.
Bulletin 11. Coal resources of District VII, by Fred H. Kay, 1915.
Bulletin 14. Coal resources of District VIII (Danville), by Fred H. Kay and K. D. White, 1915.
Bulletin 15. Coal resources of District VI, by G. H. Cady, 1916.
Bulletin 16. Coal resources of District II (Jackson Co.), by G. H. Cady, 1917.
Bulletin 17. Surface subsidence in Illinois resulting from coal mining, by Lewis E. Young, 1916.
Bulletin 18. Tests on clay materials available in Illinois coal mines, by R. T. Stull and R. K. Hursh, 1917.
Bulletin 20. Carbonization of Illinois coals in inclined gas retorts, by F. K. Ovitz, 1918.
Bulletin 21. The manufacture of retort coal-gas in the central states, using low-sulphur coal from Illinois, Indiana, and western Kentucky, by W. A. Dunkley and W. W. Odell, 1918.
Bulletin 22. Water-gas manufacture with central district bituminous coals as generator fuel, by W. W. Odell and W. A. Dunkley, 1918.
Bulletin 23. Mines producing low-sulphur coal in the central district, by G. H. Cady, 1919.
Bulletin 24. Water-gas operating methods with central district bituminous coals as generator fuel. A summary of experiments on a commercial scale, by W. A. Dunkley and W. W. Odell, 1919.
Bulletin 25. Gas purification in the medium-size gas plants of Illinois, by W. A. Dunkley and C. E. Barnes, 1920.
Bulletin 26. Coal resources of District IV, by G. H. Cady, 1921.
Bulletin 27. Analyses of Illinois coal, compiled by G. W. Hawley, 1923.

ENGINEERING EXPERIMENT STATION
URBANA, ILLINOIS

Bulletin 2. Coal mining practice in District VIII (Danville), by S. O. Andros, 1913.
Bulletin 4. Coal mining practice in District VII, by S. O. Andros, 1914.
Bulletin 5. Coal mining practice in District I (Longwall), by S. O. Andros, 1914.
Bulletin 6. Coal mining practice in District V, by S. O. Andros, 1914.
Bulletin 7. Coal mining practice in District II, by S. O. Andros, 1914.
Bulletin 8. Coal mining practice in District VI, by S. O. Andros, 1914.
Bulletin 9. Coal mining practice in District III, by S. O. Andros, 1915.
Bulletin 12. Coal mining practice in District IV, by S. O. Andros, 1915.
Bulletin 13. Coal mining in Illinois, by S. O. Andros, 1915. (Complete resume of all the district reports.)
Bulletin 91. Subsidence resulting from mining, by L. E. Young and H. H. Stoek, 1916.
Bulletin 100. Percentage of extraction of bituminous coal with special reference to Illinois conditions, by C. M. Young, 1917.
Bulletin 113. Panel system of coal mining, by C. M. Young, 1919.
Bulletin 119. Some conditions affecting the usefulness of iron oxide for city gas purification, by W. A. Dunkley, 1921.
Bulletin 125. The distribution of the forms of sulphur in the coal bed, by H. F. Yancey and Thomas Fraser, 1921.

U. S. BUREAU OF MINES
WASHINGTON, D. C.

Bulletin 72. Occurrence of explosive gases in coal mines, by N. H. Darton, 1915.
Bulletin 83. The humidity of mine air, by R. Y. Williams, 1914.
Bulletin 99. Mine ventilation stoppings, by R. Y. Williams, 1915.
Bulletin 102. The inflammability of Illinois coal dusts, by J. K. Clement and L. A. Scholl, Jr., 1916.
Bulletin 137. Use of permissible explosives in the coal mines of Illinois, by J. R. Fleming and J. W. Koster, 1917.
Bulletin 138. Coking of Illinois coals, by F. K. Ovitz, 1917.
Technical Paper 190. Methane accumulations from interrupted ventilation, with special reference to coal mines in Illinois and Indiana, by H. I. Smith and Robert J. Hamon, 1918.
Technical Paper 246. Water-gas apparatus and the use of central district coal as generator fuel, by William W. Odell, 1921.
Technical Paper 268. Preparation and uses of tar and its simple crude derivatives, by W. W. Odell, 1922.
Technical Paper 284. Coal and coke mixtures as water-gas generator fuel, by W. W. Odell, 1921.